(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification⁷: C23C 2/02, 2/40

(21) International Application Number: PCT/JP02/05627

(22) International Filing Date: 6 June 2002 (06.06.2002)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
2001-170857	6 June 2001 (06.06.2001)	JP
2001-211942	12 July 2001 (12.07.2001)	JP
2001-304034	28 September 2001 (28.09.2001)	JP
2001-304035	28 September 2001 (28.09.2001)	JP
2001-304036	28 September 2001 (28.09.2001)	JP
2001-304037	28 September 2001 (28.09.2001)	JP
2002-131643	7 May 2002 (07.05.2002)	JP

(71) Applicant (for all designated States except US): NIP-PON STEEL CORPORATION [JP/JP]; 6-3, Otemachi 2-chome, Chiyoda-ku, Tokyo 100-8071 (JP).

(72) Inventors; and
(75) Inventors/Applicants (for US only): FUJITA, Nobuhiro [JP/JP]; C/O NIPPON STEEL CORPORATION, Technical Development Bureau, 20-1, Shintomi, Futtsu-shi, Chiba 293-8511 (JP). AZUMA, Masafumi [JP/JP]; C/O NIPPON STEEL CORPORATION, Technical Development Bureau, 20-1, Shintomi, Futtsu-shi, Chiba 293-8511

(JP). TAKAHASHI, Manabu [JP/JP]; C/O NIPPON STEEL CORPORATION, Technical Development Bureau, 20-1, Shintomi, Futtsu-shi, Chiba 293-8511 (JP). MORIMOTO, Yasuhide [JP/JP]; C/O NIPPON STEEL CORPORATION, Technical Development Bureau, 20-1, Shintomi, Futtsu-shi, Chiba 293-8511 (JP). KUROSAKI, Masao [JP/JP]; C/O NIPPON STEEL CORPORATION, YAWATA WORKS, 1-1, Tobihata-cho, Tobata-ku, Kitakyushu-shi, Fukuoka 804-8501 (JP). MIYASAKA, Akihiro [JP/JP]; C/O NIPPON STEEL CORPORATION, Technical Development Bureau, 20-1, Shintomi, Futtsu-shi, Chiba 293-8511 (JP).

(74) Agents: ISHIDA, Takashi et al.; A. AOKI, ISHIDA & ASSOCIATES, Toranomon 37 Mori Bldg., 5-1, Toranomon 3-chome, Minato-ku, Tokyo 105-8423 (JP).

(81) Designated States (national): AU, BR, CA, CN, IN, KR, US.

(84) Designated States (regional): European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR).

Published:
— without international search report and to be republished upon receipt of that report

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: HIGH-STRENGTH HOT-DIP GALVANIZED STEEL SHEET AND HOT-DIP GALVANNEALED STEEL SHEET HAVING FATIGUE RESISTANCE, CORROSION RESISTANCE, DUCTILITY AND PLATING ADHESION, AFTER SEVERE DEFORMATION, AND A METHOD OF PRODUCING THE SAME

(57) Abstract: The present invention provides: a high-strength high-ductility hot-dip galvanized steel sheet and hot-dip galvannealed steel sheet having high fatigue resistance and corrosion resistance; a high-strength hot-dip galvanized steel sheet excellent in ductility, which improves non-plating defects and plating adhesion after severe deformation, and a method of producing the same; a high-strength and high-ductility hot-dip galvanized steel sheet having high fatigue resistance and corrosion resistance; a high-strength hot-dip galvanized steel sheet and hot-dip galvannealed steel sheet having superior appearance and workability, which suppresses the generation of non-plating defects, and a method of producing the same; and a high-strength hot-dip galvannealed steel sheet and a high-strength hot-dip galvanized steel sheet, which suppress non-plating defects and surface defects and have both corrosion resistance, in particular corrosion resistance in an environment containing chlorine ion, and high ductility, and a method of producing the same.

DESCRIPTION

HIGH-STRENGTH HOT-DIP GALVANIZED STEEL SHEET AND
HOT-DIP GALVANNEALED STEEL SHEET HAVING FATIGUE
RESISTANCE, CORROSION RESISTANCE, DUCTILITY AND
PLATING ADHESION, AFTER SEVERE DEFORMATION, AND
A METHOD OF PRODUCING THE SAME

Technical Field

The present invention relates to a high-strength
high-ductility hot-dip galvanized steel sheet and hot-dip
galvannealed steel sheet, excellent in fatigue resistance
and corrosion resistance suitable for building materials,
household electric appliances and automobiles, and
excellent in corrosion resistance and workability in an
environment containing chloride ion, and a method of
producing the same.

Background Art

Hot-dip galvanizing is applied to steel sheets to
provide at corrosion prevention and the hot-dip
galvanized steel sheets and hot-dip galvannealed steel
sheet are widely used in building materials, household
electric appliances, automobiles, etc. As one of the
production methods, Sendzimir processing is a method
comprising the processes of, in a continuous line in
order: degreasing cleaning; heating a steel sheet in a
non-oxidizing atmosphere; annealing it in a reducing
atmosphere containing H_2 and N_2; cooling it to a
temperature close to the plating bath temperature;
dipping it in a molten zinc bath; and cooling it or
cooling it after forming an Fe-Zn alloy layer by
reheating. The Sendzimir processing method is widely
used for the treatment of steel sheets.

As for the annealing before the plating, a fully
reducing furnace method is employed sometimes, wherein

annealing is applied in a reducing atmosphere containing
H_2 and N_2 immediately after degreasing cleaning, without
taking the process of heating a steel sheet in a non-
oxidizing atmosphere. Further, employed also is the flux

5   method comprising the processes of: degreasing and
pickling a steel sheet; then applying a flux treatment
using ammonium chloride or the like; dipping the sheet in
a plating bath; and then cooling the sheet.

       In a plating bath used in those processing methods,

10   a small amount of Al is added to deoxidize the molten
zinc. In the Sendzimir method, a zinc plating bath
contains about 0.1% of Al in mass. It is known that, as
the Al in the bath has an affinity for Fe stronger than
Fe-Zn, when a steel is dipped in the plating bath, an Fe-

15   Al alloy layer, namely an Al concentrated layer, is
generated and the reaction of Fe-Zn is suppressed. Due
to the existence of an Al concentrated layer, the Al
content in a plated layer obtained becomes generally
higher than the Al content in a plating bath.

20   Recently, demands for a high strength plated steel
sheet excellent in workability are increasing in view of
an improvement in durability and a weight reduction of a
car body intended to improve the fuel efficiency of an
automobile. Si is added to a steel as an economical

25   strengthening method and, in particular, a high-ductility
high-strength steel sheet sometimes contains not less
than 1% of Si in mass. Further, a high-strength steel
contains various kinds of alloys and has severe
restrictions in its heat treatment method from the

30   viewpoint of securing high-strength by microstructure
control.

       Again, from the viewpoint of a plating operation, if
the Si content in a steel exceeds 0.3% in mass, in the

35   case of a conventional Sendzimir method which uses a
plating bath containing Al, plating wettability
deteriorates markedly and non-plating defects are

generated resulting in the deterioration of appearance.
It is said that the above drawback is caused by the
concentration of Si oxides on a steel sheet surface
during the reducing annealing and the poor wettability
5   between the Si oxides and molten zinc.

In case of a high-strength steel sheet, the added
elements are abundant as explained above, and therefore
the alloying heat treatment after plating is apt to be
applied at a higher temperature and for a longer time
10   than in the case of a mild steel. This is one of the
obstacles to securing good material quality.

Further, from the viewpoint of an improvement in the
durability of a structural member, fatigue resistance, in
addition to corrosion resistance, is also important.
15   That is, it is important to develop a high-strength steel
sheet having good plating producibility, good fatigue
resistance and good corrosion resistance simultaneously.

As a means of solving the problems, Japanese
Unexamined Patent Publication Nos. H3-28359 and H3-64437
20   disclose a method of improving plating performances by
applying a specific plating. However, this method has a
problem that the method requires either the installation
of a new plating apparatus in front of the annealing
furnace in a hot-dip plating line or an additional
25   preceding plating treatment in an electroplating line,
and this increases the costs. Further, with regard to
fatigue resistance and corrosion resistance, though it
has recently been disclosed that the addition of Cu is
effective, the compatibility with corrosion resistance is
30   not described at all.

Further, Si scale defects generated at the hot-
rolling process cause the deterioration of plating
appearance at subsequent processes. The reduction of Si
content in a steel is essential to suppress the Si scale
35   defects, but, in the case of a retained austenite steel
sheet or of a dual phase steel sheet which is a typical
high ductility type high-strength steel sheet, Si is an

additive element extremely effective in improving the
balance between strength and ductility. To cope with
this problem, a method of controlling the morphology of
generated oxides by controlling the atmosphere of
5   annealing or the like is disclosed. However, the method
requires special equipment and thus entails a new
equipment cost.

Yet further, when high-strength steel sheets are
adopted for the purpose of achieving weight reduction by
10   the reduction of the sheet thickness and the thinning of
the steel sheets proceeds, more enhanced corrosion
resistance may sometimes be required of even hot-dip
galvanized steel sheets or hot-dip galvannealed steel
sheets. For instance, an environment where rock salt is
15   sprayed as a snow melting agent is a severe environment
because it contains a comparatively large amount of Cl⁻
ions. In the case where a plated layer exfoliates
locally at the portions which are subjected to heavy
working or the plated layer itself has insufficient
20   corrosion resistance, a base material with excellent
corrosion resistance and the formation of a plated layer
with excellent corrosion resistance are required.

A steel sheet, which allows weight and thickness
reduction and is prepared taking into consideration
25   strengthening, the problems related to Si and improvement
in corrosion resistance, has not been developed.

Yet further, while aiming at improving the
producibility in plating a high-strength steel sheet,
Japanese Unexamined Patent Publication No. H5-230608
30   discloses a hot-dip galvanized steel sheet having a Zn-
Al-Mn-Fe system plated layer. However, though this
invention particularly takes the producibility into
consideration, it is not such an invention that takes the
plating adhesiveness into consideration when a high-
35   strength high-ductility material is subjected to a heavy
working.

Furthermore, aiming at enhancing the collision

energy absorbing capability, Japanese Unexamined Patent
Publication No. H11-189839 discloses a steel sheet:
having the main phase comprising ferrite and the average
grain size of the main phase being not more than 10μm;
5   having the second phase comprising austenite 3 to 50% in
volume or martensite 3 to 30% in volume and the average
grain size of the second phase being not more than 5 μm;
and containing bainite selectively. However, this
invention does not take plating wettability into
10   consideration and does not provide the corrosion
resistance which allows thickness reduction accompanying
increased strength.

Disclosure of the Invention
15   The present invention provides a high-strength
galvanized and galvannealed steels sheet which solve the
above-mentioned problems, is excellent in appearance and
workability, improves non-plating defects and plating
adhesion after severe deformation, and is excellent in
20   ductility, and a method of producing the same and,
further, it provides a high-strength high-ductility hot-
dip galvanized steel sheet and a high-strength high-
ductility galvannealed steel sheet which are excellent in
corrosion resistance and fatigue resistance, and a method
25   of producing the same.
         Further, the object of the present invention is to
provide a high-strength hot-dip galvanized steel sheet
and a high-strength hot-dip galvannealed steel sheet
which solve the above-mentioned problems, suppress non-
30   plating defects and surface defects, and have corrosion
resistance and high ductility, simultaneously, in an
environment particularly containing chlorine ion, and a
method of producing the same.
         The present inventors, as a result of various
35   studies, have found that it is possible to produce
galvanized and galvannealed steel sheets having good

workability even when heat treatment conditions were
mitigated and simultaneously improving corrosion
resistance and fatigue resistance of a high-strength
steel sheet, by regulating the microstructure of the
interface (hereafter referred to as "plated layer/base
layer interface") between a plated layer and a base layer
(steel layer). Further, they also found that the
wettability of molten zinc plating on a high-strength
steel sheet is improved by making the plated layer
contain specific elements in an appropriate amount. Yet
further, they found that the above effects were
heightened by reducing the concentration of Al in a
plated layer, and that a very good plated layer could be
obtained even in the case of a high-strength steel sheet
containing alloying elements in relatively large amount,
by controlling Si content: X (in mass %), Mn content: Y
(in mass %) and Al content: Z (in mass %) in the steel
sheet, and also Al content: A (in mass %) and Mn content:
B (in mass %) in the plated layer so as to satisfy the
following equation 1:

$$3-(X+Y/10+Z/3)-12.5\times(A-B) \geqq 0 \ldots 1$$

Furthermore, they found that a steel sheet having
high ductility could be produced even when the heat
treatment conditions were relieved, by adding alloying
elements selectively and in an appropriate amount and, in
addition, by regulating the microstructure of the steel
sheet.

The present inventors, as a result of various
studies, found that, in case of a high-strength steel
sheet, the wettability in hot-dip galvanizing was
improved, and the alloying reaction in alloying plating
was accelerated, by making the plated layer contain
specific elements in an appropriate amount and by
combining them with the components of the steel sheet.
The effect can be achieved mainly by controlling the

concentration of Al in the plated layer and that of Mn in the steel.

   They found that a very good plated layer could be obtained by controlling Mn content: X (in mass %) and Si content: Y (in mass %) in a steel, and Al content: Z (in mass %) in a plated layer so as to satisfy the following equation 2.

   $$0.6-(X/18+Y+Z) \geqq 0 \quad ... \quad 2$$

   The present inventors, as a result of various studies, found that, in case of a high-strength steel sheet, the wettability in hot-dip galvanizing and hot-dip galvannealing was improved, the alloying reaction in alloy plating was accelerated, and also ductility and corrosion resistance were improved, by making the plated layer contain specific elements in an appropriate amount and by combining them with the components of the steel sheet. The effect can be achieved mainly by controlling the concentrations of Al and Mo in the plated layer and that of Mo in the steel.

   That is, they found that a high-strength high-ductility hot-dip galvannealed coated steel sheet could be obtained by containing 0.001 to 4% of Al in mass in the plated layer and, in addition, by controlling Al content: A (in mass %) and Mo content: B (in mass %) in the plated layer, and Mo content: C (in mass %) in the steel so as to satisfy the following equation 3:

   $$100 \geqq (A/3+B/6)/(C/6) \geqq 0.01 \quad ... \quad 3$$

   The present invention has been accomplished based on the above findings and the gist of the present invention is as follows:

   (1) A high-strength high-ductility hot-dip galvanized steel sheet and hot-dip galvannealed steel sheet having high fatigue resistance and corrosion resistance, the hot-dip galvanized or galvannealed steel

sheet having a plated layer on the surface of the base
layer consisting of a steel sheet, characterized in that
the maximum depth of the grain boundary oxidized layer
formed at the interface between the plated layer and the
5   base layer is not more than 0.5 μm.

(2) A high-strength high-ductility hot-dip
galvanized steel sheet and hot-dip galvannealed steel
sheet having high fatigue resistance and corrosion
10   resistance, the hot-dip galvanized or galvannealed steel
sheet having a plated layer on the surface of the base
layer consisting of a steel sheet, characterized in that
the maximum depth of the grain boundary oxidized layer at
the interface between the plated layer and the base layer
15   is not more than 1 μm and the average grain size of the
main phase in the microstructure of the base layer is not
more than 20 μm.

(3) A high-strength high-ductility hot-dip
20   galvanized steel sheet and hot-dip galvannealed steel
sheet having high fatigue resistance and corrosion
resistance, the hot-dip galvanized or galvannealed steel
sheet having a plated layer on the surface of the base
layer consisting of a steel sheet, according to the item
25   (1) or (2), characterized in that the value obtained by
dividing the maximum depth of the grain boundary oxidized
layer formed at the interface between the plated layer
and the base layer by the average grain size of the main
phase in the microstructure of the base layer is not more
30   than 0.1.

(4) A high-strength high-ductility hot-dip
galvanized steel sheet and hot-dip galvannealed steel
sheet having high fatigue resistance and corrosion
35   resistance according to any one of the items (1) to (3),
characterized in that the steel sheet contains, in its

microstructure, ferrite or ferrite and bainite 50 to 97%
in volume as the main phase, and either or both of
martensite and austenite 3 to 50% in total volume as the
second phase.

(5) A high-strength high-ductility hot-dip
galvanized steel sheet and hot-dip galvannealed steel
sheet having high fatigue resistance and corrosion
resistance according to any one of the items (1) to (4),
characterized in that: the plated layer contains, in
mass,
    Al: 0.001 to 0.5%, and
    Mn: 0.001 to 2%,
with the balance consisting of Zn and unavoidable
impurities; and Si content: X (in mass %), Mn content: Y
(in mass %) and Al content: Z (in mass %) in the steel
sheet, and Al content: A (in mass %) and Mn content: B
(in mass %) in the plated layer satisfy the following
equation 1:
    $3-(X+Y/10+Z/3)-12.5 \times (A-B) \geqq 0 \ldots 1$

(6) A high-strength high-ductility hot-dip
galvannealed steel sheet having high fatigue resistance
and corrosion resistance according to the item (5),
characterized in that the plated layer contains Fe at 5
to 20% in mass.

(7) A high-strength hot-dip galvanized steel sheet
having high plating adhesion after severe deformation and
ductility, the hot-dip galvanized steel sheet having a
plated layer containing, in mass,
    Al: 0.001 to 0.5%, and
    Mn: 0.001 to 2%,
with the balance consisting of Zn and unavoidable
impurities, on the surface of a steel sheet consisting
of, in mass,

C: 0.0001 to 0.3%,

Si: 0.01 to 2.5%,

Mn: 0.01 to 3%,

Al: 0.001 to 4%, and

5   the balance consisting of Fe and unavoidable impurities,
characterized in that: Si content: X (in mass %), Mn
content: Y (in mass %) and Al content: Z (in mass %) in
the steel, and Al content: A (in mass %) and Mn content:
B (in mass %) in the plated layer satisfy the following

10   equation 1; and the microstructure of the steel sheet has
the main phase comprising ferrite at 70 to 97% in volume
and the average grain size of a main phase is not more
than 20 μm, and a second phase comprising austenite
and/or martensite at 3 to 30% in volume and the average

15   grain size of the second phase being not more than 10 μm:

$$3-(X+Y/10+Z/3)-12.5\times(A-B) \geqq 0 \ldots 1$$

(8) A high-strength hot-dip galvannealed steel sheet
having high plating adhesion after severe deformation and

20   ductility according to the item (7), characterized in
that the plated layer further contains Fe at 5 to 20% in
mass.

(9) A high-strength hot-dip galvanized steel sheet

25   and hot-dip galvannealed steel sheet having plating
adhesion after severe deformation and ductility according
to the item (7) or (8), characterized in that the average
grain size of austenite and/or martensite which
constitute(s) the second phase of the steel sheet is 0.01

30   to 0.7 times the average grain size of ferrite.

(10) A high-strength hot-dip galvanized steel sheet
and hot-dip galvannealed steel sheet having plating
adhesion after severe deformation and ductility according

35   to any one of the items (7) to (9), characterized in that
the microstructure of the steel sheet: has a main phase

comprising ferrite at 50 to 95% in volume and the average
grain size of the main phase being not more than 20 μm,
and a second phase comprising austenite and/or martensite
at 3 to 30% in volume and the average grain size of the
5   second phase being not more than 10 μm; and further
contains bainite at 2 to 47% in volume.

(11) A high-strength hot-dip galvanized steel sheet
and hot-dip galvannealed steel sheet having plating
10   adhesion after severe deformation and ductility according
to any one of the items (7) to (10), characterized in
that the steel further contains Mo at 0.001 to 5% in·
mass.

15   (12) A high-strength hot-dip galvanized steel sheet
and hot-dip galvannealed steel sheet having plating
adhesion after severe deformation and ductility according
to any one of the items (7) to (11), characterized in
that the steel further contains P at 0.0001 to 0.1% and S
20   at 0.0001 to 0.01%, in mass.

(13) A high-strength hot-dip galvanized steel sheet
and hot-dip galvannealed steel sheet having high fatigue
resistance and corrosion resistance according to any one
25   of the items (7) to (12), characterized in that the Si
content in the steel is 0.001 to 2.5%.

(14) A high-strength hot-dip galvannealed steel
sheet having superior appearance and workability, the
30   hot-dip galvannealed steel sheet having a plated layer
containing, in mass,
        Mn: 0.001 to 3%,
        Al: 0.001 to 4%,
        Mo: 0.0001 to 1%, and
35   Fe: 5 to 20%,
with the balance consisting of Zn and unavoidable

impurities, on the surface of a steel sheet consisting
of, in mass,

C: 0.0001 to 0.3%,

Si: 0.001 to less than 0.1%,

5   Mn: 0.01 to 3%,

Al: 0.001 to 4%,

Mo: 0.001 to 1%,

P: 0.0001 to 0.3%,

S: 0.0001 to 0.1%, and

10   the balance consisting of Fe and unavoidable impurities,
characterized in that: Mn content: X (in mass %) and Si
content: Y (in mass %) in the steel, and Al content: Z
(in mass %) in the plated layer satisfy the following
equation 2:

15       $0.6-(X/18+Y+Z) \geqq 0$ ... 2

(15) A high-strength hot-dip galvanized steel sheet
having superior appearance and workability, the hot-dip
galvanized steel sheet having a plated layer containing,

20   in mass,

Mn: 0.001 to 3%,

Al: 0.001 to 4%,

Mo: 0.0001 to 1%, and

Fe: less than 5%,

25   with the balance consisting of Zn and unavoidable
impurities, on the surface of a steel sheet consisting
of, in mass,

C: 0.0001 to 0.3%,

Si: 0.001 to less than 0.1%,

30   Mn: 0.01 to 3%,

Al: 0.001 to 4%,

Mo: 0.001 to 1%,

P: 0.0001 to 0.3%,

S: 0.0001 to 0.1%, and

35   the balance consisting of Fe and unavoidable impurities,
characterized in that: Mn content: X (in mass %) and Si
content: Y (in mass %) in the steel, and Al content: Z

(in mass %) in the plated layer satisfy the following
equation 2:

$$0.6-(X/18+Y+Z) \geq 0 \ldots 2$$

5   (16) A high-strength high-ductility hot-dip
galvannealed steel sheet having high corrosion
resistance, the hot-dip galvannealed steel sheet having a
plated layer containing, in mass,
          Al: 0.001 to 4%, and
10   Fe: 5 to 20%,
with the balance consisting of Zn and unavoidable
impurities, on the surface of a steel sheet consisting
of, in mass,
          C: 0.0001 to 0.3%,
15   Si: 0.001 to less than 0.1%,
          Mn: 0.001 to 3%,
          Al: 0.001 to 4%,
          Mo: 0.001 to 1%,
          P: 0.001 to 0.3%,
20   S: 0.0001 to 0.1%, and
the balance consisting of Fe and unavoidable impurities,
characterized in that: Al content: A (in mass %) and Mo
content: B (in mass %) in the plated layer, and Mo
content: C (in mass %) in the steel satisfy the following
25   equation 3; and the microstructure of the steel consists
of the main phase comprising ferrite or ferrite and
bainite 50 to 97% in volume and the balance consisting of
a complex structure containing either or both of
martensite and retained austenite 3 to 50% in volume:
30         $$100 \geq (A/3+B/6)/(C/6) \geq 0.01 \ldots 3$$

          (17) A high-strength high-ductility hot-dip
galvanized steel sheet having high corrosion resistance,
the hot-dip galvanized steel sheet having a plated layer
35   containing, in mass,
          Al: 0.001 to 4%, and

Fe: less than 5%,
with the balance consisting of Zn and unavoidable
impurities, on the surface of a steel sheet consisting
of, in mass,

C: 0.0001 to 0.3%,
Si: 0.001 to less than 0.1%,
Mn: 0.001 to 3%,
Al: 0.001 to 4%,
Mo: 0.001 to 1%,
P: 0.001 to 0.3%,
S: 0.0001 to 0.1%, and
the balance consisting of Fe and unavoidable impurities,
characterized in that: Al content: A (in mass %) and Mo
content: B (in mass %) in the plated layer, and Mo
content: C (in mass %) in the steel satisfy the following
equation 3; and the microstructure of the steel consists
of the main phase comprising ferrite or ferrite and
bainite 50 to 97% in volume and the balance consisting of
a complex structure containing either or both of
martensite and retained austenite at 3 to 50% in volume:

$$100 \geqq (A/3+B/6)/(C/6) \geqq 0.01 \ldots 3$$

(18) A high-strength hot-dip galvanized steel sheet
and hot-dip galvannealed steel sheet having superior
appearance and workability according to any one of the
items (14) to (17), characterized in that the
microstructure of the steel consists of the main phase
comprising ferrite or ferrite and bainite at 50 to 97% in
volume and the balance consisting of a complex structure
containing either or both of martensite and retained
austenite at 3 to 50% in total volume.

(19) A high-strength hot-dip galvanized steel sheet
and hot-dip galvannealed steel sheet having superior
appearance and workability according to any one of the
items (14) to (18), characterized in that the
microstructure of the steel sheet has a main phase

comprising ferrite at 70 to 97% in volume and the average
grain size of the main phase being not more than 20 μm,
and a second phase comprising austenite and/or martensite
at 3 to 30% in volume and the average grain size of the
second phase being not more than 10 μm.

(20) A high-strength hot-dip galvanized steel sheet
and hot-dip galvannealed steel sheet having superior
appearance and workability according to any one of the
items (14) to (19), characterized in that: the second
phase of the steel sheet is composed of austenite; and C
content: C (in mass %) and Mn content: Mn (in mass %) in
the steel, and the volume percentage of austenite: Vγ (in
%) and the volume percentage of ferrite and bainite: Vα
(in %) satisfy the following equation 4:

$$(Vγ+Vα)/VγxC+Mn/8 ≧ 2.0 ... 4$$

(21) A high-strength hot-dip galvanized steel sheet
and hot-dip galvannealed steel sheet having superior
appearance and workability according to any one of the
items (14) to (20), characterized in that the
microstructure of the steel sheet: has a main phase
comprising ferrite at 50 to 95% in volume and the average
grain size of the main phase being not more than 20 μm,
and a second phase comprising austenite and/or martensite
at 3 to 30% in volume and the average grain size of the
second phase being not more than 10 μm; and further
contains bainite at 2 to 47% in volume.

(22) A high-strength high-ductility hot-dip
galvanized steel sheet and hot-dip galvannealed steel
sheet having high corrosion resistance according to any
one of the items (14) to (21), characterized in that the
average grain size of austenite and/or martensite which
constitute(s) the second phase of the steel sheet is 0.01

- 16 -

to 0.6 times the average grain size of ferrite.

(23) A high-strength hot-dip galvanized steel sheet
having high plating adhesion after severe deformation and
ductility according to any one of the items (1) to (22),
characterized in that the plated layer further contains,
in mass, one or more of,

Ca: 0.001 to 0.1%,

Mg: 0.001 to 3%,

Si: 0.001 to 0.1%,

Mo: 0.001 to 0.1%,

W: 0.001 to 0.1%,

Zr: 0.001 to 0.1%,

Cs: 0.001 to 0.1%,

Rb: 0.001 to 0.1%,

K: 0.001 to 0.1%,

Ag: 0.001 to 5%,

Na: 0.001 to 0.05%,

Cd: 0.001 to 3%,

Cu: 0.001 to 3%,

Ni: 0.001 to 0.5%,

Co: 0.001 to 1%,

La: 0.001 to 0.1%,

Tl: 0.001 to 8%,

Nd: 0.001 to 0.1%,

Y: 0.001 to 0.1%,

In: 0.001 to 5%,

Be: 0.001 to 0.1%,

Cr: 0.001 to 0.05%,

Pb: 0.001 to 1%,

Hf: 0.001 to 0.1%,

Tc: 0.001 to 0.1%,

Ti: 0.001 to 0.1%,

Ge: 0.001 to 5%,

Ta: 0.001 to 0.1%,

V: 0.001 to 0.2%, and

B: 0.001 to 0.1%.

(24) A high-strength hot-dip galvanized steel sheet
and hot-dip galvannealed steel sheet having superior
appearance and workability according to any one of the
items (1) to (23), characterized in that the steel
further contains, in mass, one or more of,
        Cr: 0.001 to 25%,
        Ni: 0.001 to 10%,
        Cu: 0.001 to 5%,
        Co: 0.001 to 5%, and
        W: 0.001 to 5%.

(25) A high-strength hot-dip galvanized steel sheet
and hot-dip galvannealed steel sheet having superior
appearance and workability according to any one of the
items (1) to (24), characterized in that the steel
further contains, in mass, one or more of Nb, Ti, V, Zr,
Hf and Ta at 0.001 to 1% in total.

(26) A high-strength hot-dip galvanized steel sheet
and hot-dip galvannealed steel sheet having superior
appearance and workability according to any one of the
items (1) to (25), characterized in that the steel yet
further contains B at 0.0001 to 0.1% in mass.

(27) A high-strength hot-dip galvanized steel sheet
and hot-dip galvannealed steel sheet having superior
appearance and workability according to any one of the
items (1) to (26), characterized in that the steel yet
further contains one or more of Y, Rem, Ca, Mg and Ce at
0.0001 to 1% in mass.

(28) A high-strength high-ductility hot-dip
galvanized steel sheet and hot-dip galvannealed steel
sheet having high fatigue resistance and corrosion
resistance according to any one of the items (1) to (27),
characterized in that: the steel contains one or more of

SiO_2, MnO and Al_2O_3 at 0.1 to 70% in total area percentage
in the range from the interface between the plated layer
and the steel sheet to the depth of 10 μm; and the
following equation 5 is satisfied:

{MnO (in area percentage)+Al_2O_3 (in area
percentage)}/SiO_2 (in area percentage) $\geqq$ 0.1 ... 5

(29) A high-strength high-ductility hot-dip
galvanized steel sheet and hot-dip galvannealed steel
sheet having high fatigue resistance and corrosion
resistance according to any one of the items (1) to (28),
characterized in that the steel contains one or more of
Y_2O_3, ZrO_2, HfO_2, TiO_3, La_2O_3, Ce_2O_3, CeO_2, CaO and MgO at
0.0001 to 10.0% in total area percentage in the range
from the interface between the plated layer and the steel
sheet to the depth of 10 μm.

(30) A method of producing a high-strength hot-dip
galvanized steel sheet and hot-dip galvannealed steel
sheet having high plating adhesion after severe
deformation and ductility, characterized by: casting a
steel comprising the chemical components according to any
one of the items (1) to (29) or once cooling the cast
slab after the casting; then heating the cast slab again;
thereafter, hot-rolling the cast slab into a hot-rolled
steel sheet and coiling it, and then pickling and cold-
rolling the hot-rolled steel sheet; thereafter, annealing
the cold-rolled steel sheet for 10 seconds to 30 minutes
in the temperature range from not less than 0.1x(Ac_3 -
Ac_1)+Ac_1 (°C) to not more than Ac_3+50 (°C); then cooling
the steel sheet to the temperature range from 650 to
700°C at a cooling rate of 0.1 to 10°C/sec.; thereafter,
cooling the steel sheet to the temperature range from the
plating bath temperature to the plating bath temperature
+ 100°C at a cooling rate of 1 to 100°C/sec.; keeping the
steel sheet in the temperature range from the zinc

plating bath temperature to the zinc plating bath
temperature + 100°C for 1 to 3,000 seconds including the
subsequent dipping time; dipping the steel sheet in the
zinc plating bath; and, after that, cooling the steel
5   sheet to room temperature.

(31) A method of producing a high-strength hot-dip
galvanized steel sheet and hot-dip galvannealed steel
sheet according to any one of the items (1) to (29),
10   which hot-dip galvanized steel sheet being excellent in
appearance and workability, characterized by: casting a
steel comprising the chemical components according to any
one of the items (1) to (29) or once cooling the cast
slab after the casting; then heating the cast slab again
15   to a temperature of 1,180 to 1,250°C; finishing the hot-
rolling at a temperature of 880 to 1,100°C; then pickling
and cold-rolling the coiled hot-rolled steel sheet;
thereafter, annealing the cold-rolled steel sheet for 10
seconds to 30 minutes in the temperature range from not
20   less than $0.1x(Ac_3 - Ac_1)+Ac_1$ (°C) to not more than Ac_3+50
(°C); then cooling the steel sheet to the temperature
range from 650 to 700°C at a cooling rate of 0.1 to
10°C/sec.; thereafter, cooling the steel sheet to the
temperature range from the plating bath temperature -
25   50°C to the plating bath temperature + 50°C at a cooling
rate of 0.1 to 100°C/sec.; then dipping the steel sheet
in the plating bath; keeping the steel sheet in the
temperature range from the plating bath temperature -
50°C to the plating bath temperature + 50°C for 2 to 200
30   seconds including the dipping time; and, thereafter,
cooling the steel sheet to room temperature.

(32) A method of producing a high-strength high-
ductility hot-dip galvanized steel sheet and hot-dip
35   galvannealed steel sheet according to any one of the
items (1) to (29), the hot-dip galvanized steel sheet
being excellent in corrosion resistance, characterized

by: casting a steel comprising the chemical components
according to any one of the items (1) to (29) or once
cooling the cast slab after the casting; then heating the
cast slab again to a temperature of 1,200 to 1,300°C;
then rough-rolling the heated slab at the total reduction
rate of 60 to 99% and at a temperature of 1,000 to
1,150°C; then pickling and cold-rolling the finished and
coiled hot-rolled steel sheet; thereafter, annealing the
cold-rolled steel sheet for 10 seconds to 30 minutes in
the temperature range from not less than $0.12 \times (Ac_3 -$
$Ac_1)+Ac_1$ (°C) to not more than Ac_3+50 (°C); then, after
the annealing, cooling the steel sheet, when the highest
attained temperature during annealing is defined as Tmax
(°C), to the temperature range from Tmax - 200°C to Tmax
- 100°C at a cooling rate of Tmax/1,000 to Tmax/10
°C/sec.; thereafter, cooling the steel sheet to the
temperature range from the plating bath temperature -
30°C to the plating bath temperature + 50°C at a cooling
rate of 0.1 to 100°C/sec.; then dipping the steel sheet
in the plating bath; keeping the steel sheet in the
temperature range from the plating bath temperature -
30°C to the plating bath temperature + 50°C for 2 to 200
seconds including the dipping time; and, thereafter,
cooling the steel sheet to room temperature.

(33) A method of producing a high-strength high-
ductility hot-dip galvanized steel sheet and hot-dip
galvannealed steel sheet having high fatigue resistance
and corrosion resistance, characterized by: casting a
steel comprising the chemical components according to any
one of the items (1) to (29) or once cooling the cast
slab after the casting; then heating the cast slab again;
thereafter, hot-rolling the cast slab into a hot-rolled
steel sheet and coiling it, and then pickling and cold-
rolling the hot-rolled steel sheet; thereafter, annealing
the cold-rolled steel sheet controlling the annealing
temperature so that the highest temperature during

annealing may fall within the range from not less than
$0.1 \times (Ac_3 - Ac_1) + Ac_1$ (°C) to not more than $Ac_3 - 30$ (°C);
then cooling the steel sheet to the temperature range
from 650 to 710°C at a cooling rate of 0.1 to 10°C/sec.;
thereafter, cooling the steel sheet to the temperature
range from the zinc plating bath temperature to the zinc
plating bath temperature + 100°C at a cooling rate of 1
to 100°C/sec.; keeping the steel sheet in the temperature
range from the zinc plating bath temperature to the zinc
plating bath temperature + 100°C for 1 to 3,000 seconds
including the subsequent dipping time; dipping the steel
sheet in the zinc plating bath; and, after that, cooling
the steel sheet to room temperature.

(34) A high-strength hot-dip galvanized steel sheet
and hot-dip galvannealed steel sheet having high fatigue
resistance, corrosion resistance, and plating adhesion
after severe deformation and ductility and a method of
producing the same, according to any one of the items
(30) to (33), characterized by: after dipping the steel
sheet in the zinc plating bath, applying an alloying
treatment to the steel sheet at a temperature of 300 to
550°C and cooling it to room temperature.

Best Mode for Carrying out the Invention
        The present invention will be explained in detail
hereunder.

Embodiment 1
        The present inventors subjected a steel sheet, which
consisted of, in mass, 0.0001 to 0.3% of C, 0.001 to 2.5%
of Si, 0.01 to 3% of Mn, 0.001 to 4% of Al and the
balance consisting of Fe and unavoidable impurities, to
the processes of: annealing the steel sheet for 10
seconds to 30 minutes in the temperature range from not
less than $0.1 \times (Ac_3 - Ac_1) + Ac_1$ (°C) to not more than $Ac_3 + 50$
(°C); then cooling the steel sheet to the temperature

range from 650 to 700°C at a cooling rate of 0.1 to
10°C/sec.; thereafter, cooling the steel sheet to the
temperature range from the plating bath temperature (450
to 470°C) to the plating bath temperature + 100°C at a
cooling rate of 1 to 100°C/sec.; dipping the steel sheet
in the zinc plating bath at a temperature of 450 to 470°C
for 3 seconds; and heating the steel sheet at a
temperature of 500 to 550°C for 10 to 60 seconds.

Thereafter, a plating property was evaluated by
measuring the area of non-plated portions on the surface
of the plated steel sheet. Corrosion resistance was
evaluated by applying a repeated salt spray test.
Further, mechanical properties were evaluated by a
tensile test, and the fatigue property of the plated
steel sheet was evaluated by a plane bending fatigue test
applying a stress corresponding to 50% of the tensile
strength of the steel sheet.

Further, plating adhesion was evaluated by applying
60° bending and bending-back forming to the steel sheet
after giving 20% tensile strain, sticking a vinyl tape to
the portion where bending forming was applied and peeling
it off, and then quantifying the area where the plated
layer was peeled off by image analysis.

As a result, Si system oxides, in particular, were
observed abundantly at the crystal grain boundaries of
the interface between the plated layer and the base
layer, and the present inventors found that a high-
strength high-ductility hot-dip galvanized steel sheet
excellent in fatigue resistance and corrosion resistance
could be produced by controlling the maximum depth of the
grain boundary oxidized layer and the average grain size
of the main phase in the finally obtained microstructure
with regard to the relation between the shape of the
grain boundary oxidized layer and the fatigue property.

That is, the present inventors found that the
fatigue life of a hot-dip galvanized steel sheet could be
prolonged by controlling the maximum depth of the grain

boundary oxidized layer containing Si to 0.5 μm or less
in the finally obtained microstructure at the interface
between the plated layer and the base layer.
Furthermore, the fatigue life of a hot-dip galvanized
5   steel sheet can be further prolonged by selecting the
steel components and the production conditions which
allow the maximum depth of the grain boundary oxidized
layer to be 0.5 μm or less, preferably 0.2 μm or less.

       Further, the present inventors found that corrosion
10   resistance and fatigue resistance particularly after an
alloying treatment could be further improved by
restricting the kinds and area percentage of oxides in a
steel, which contained grain boundary oxides, in the
range from the interface between the plated layer and the
15   steel sheet to the depth of 10 μm. That is, a high-
strength high-ductility hot-dip galvanized or
galvannealed steel sheet excellent in corrosion
resistance and fatigue resistance can be obtained: by
making the steel contain one or more of SiO_2, MnO and
20   Al_2O_3, as oxides, at 0.4 to 70% in total area percentage
in the range from the interface between the plated layer
and the steel sheet to the depth of 10 μm; and by
controlling those area percentages so as to satisfy the
following expression:
25   {MnO (in area percentage)+Al_2O_3 (in area
percentage)}/SiO_2 (in area percentage) $\geq$ 0.1.

       The present inventors also found that corrosion
resistance and fatigue resistance after an alloying
30   treatment could also be improved by making a steel
contain, in addition to SiO_2, MnO and Al_2O_3, one or more
of Y_2O_3, ZrO_2, HfO_2, TiO_2, La_2O_3, Ce_2O_3, CeO_2, CaO and MgO by
0.0001 to 10.0% in total area percentage in the range
from the interface between the plated layer and the steel
35   sheet to the depth of 10 μm.

Here, the identification, observation and area
percentage measurement of oxides existing in a steel in
the range from the interface between the plated layer and
the steel sheet to the depth of 10 μm as stated above can
be carried out by using EPMA, FE-SEM and the like. In
the present invention, the area percentage was obtained
by measuring the area in more than 50 visual fields under
the magnification of 2,000 to 20,000 and then analyzing
the data using image analysis. The identification of
oxides was carried out by preparing an extracted replica
specimen and using TEM or EBSP. MnO, Al_2O_3 and SiO_2
described above were distinguished by finding the most
similar objects using element analysis and structure
identification, though sometimes there were cases where
objects were complex oxides containing other atoms or had
a structure containing many defects. The area percentage
can be obtained by the area scanning of each component
using EPMA, FE-SEM and the like. In this case, though
precise identification of each structure is difficult,
the judgement can be done from the shape and the
organization together with the above-mentioned structural
analysis. Thereafter, each area percentage can be
obtained by the image analysis of the data obtained from
the area scanning.

The present inventors found that the fatigue life
could be prolonged likewise by controlling the average
grain size of the main phase in a steel sheet to not more
than 20 μm and the maximum depth of the grain boundary
oxidized layer at the interface between the plated layer
and the base layer to not more than 1 μm into the
microstructure. Further, they found that a high-strength
high-ductility hot-dip galvanized steel sheet and hot-dip
galvannealed steel sheet having high fatigue resistance
and corrosion resistance could be obtained by controlling
the value obtained by dividing the maximum depth of the
grain boundary oxidized layer formed at the interface

between the plated layer and the base layer by the average grain size of the main phase to not more than 0.1 in the microstructure of the steel sheet.

Further, with regard to plating property and corrosion resistance, it was found that non-plating defects were not formed and rust formation in a repeated salt spray test was extremely small even in the case of a steel sheet particularly containing abundant Si as long as Si content: X (in mass %), Mn content: Y (in mass %) and Al content: Z (in mass %) in the steel sheet, and Al content: A (in mass %) and Mn content: B (in mass %) in the plated layer satisfy the following equation 1:

$$3-(X+Y/10+Z/3)-12.5\times(A-B) \geqq 0 \ \ldots \ 1$$

The equation 1 is newly found from multiple regression analysis of the data showing the influence of the components in a steel sheet and a plated layer on plating wettability.

Here, the components in a plated layer are defined to be a value measured by chemical analysis after the plated layer is dissolved with 5% hydrochloric acid solution containing an inhibitor.

Embodiment 2

The present inventors subjected a steel sheet consisting of, in mass,

    C: 0.0001 to 0.3%,
    Si: 0.001 to less than 0.1%,
    Mn: 0.01 to 3%,
    Al: 0.001 to 4%,
    Mo: 0.001 to 1%,
    P: 0.0001 to 0.3%,
    S: 0.0001 to 0.1%, and

the balance consisting of Fe and unavoidable impurities, to the processes of: annealing the steel sheet; dipping the steel sheet in the zinc plating bath at a temperature

of 450 to 470°C for 3 seconds; and further heating some
of the specimens for 10 to 60 seconds at a temperature of
500 to 530°C. Thereafter, the appearance was evaluated
by classifying the incidence of defects on the surface of
5   the plated steel sheet into five ranks. Mechanical
properties were also evaluated using a tensile test. As
a result, it was found that evaluation rank 5, which
meant appearance defects were scarcely observed, could be
obtained when Mn content in the steel was defined as X
10   (in mass %), Si content in the steel as Y (in mass %),
and Al content in the plated layer as Z (in mass %), and
X, Y and Z satisfied the following equation 2:

$$0.6-(X/18+Y+Z) \geqq 0 \ldots 2$$

15   The appearance of a plated steel sheet was evaluated
by visually observing the state of the formation of non-
plating defects and the state of the formation of flaws
and patterns and classifying them into the evaluation
ranks 1 to 5. The criteria of the evaluation are as
20   follows:
Evaluation rank 5: non-plating defects, flaws and
patterns are scarcely observed (not more than 1% in area
percentage),
Evaluation rank 4: non-plating defects, flaws and
25   patterns are trivial (more than 1% to not more than 10%
in area percentage),
Evaluation rank 3: non-plating defects, flaws and
patterns are few (more than 10% to not more than 50% in
area percentage),
30   Evaluation rank 2: non-plating defects, flaws and
patterns are plentiful (more than 50% in area
percentage),
Evaluation rank 1: plating does not wet a steel sheet
surface.
35

Embodiment 3
     The present inventors subjected a steel sheet

consisting of, in mass,

    C: 0.0001 to 0.3%,

    Si: 0.001 to less than 0.1%,

    Mn: 0.01 to 3%,

    Al: 0.001 to 4%,

    Mo: 0.001 to 1%,

    P: 0.0001 to 0.3%,

    S: 0.0001 to 0.1%, and

the balance consisting of Fe and unavoidable impurities, to the processes of: annealing the steel sheet; dipping the steel sheet in the zinc plating bath at a temperature of 450 to 470°C for 3 seconds; and further heating some of the specimens for 10 to 60 seconds at a temperature of 500 to 550°C. Thereafter, the steel sheet was subjected to full flat bending (R=1t), and the bent specimen was subjected to a cyclic corrosion test of up to 150 cycles based on the standard (JASO) of the Society of Automotive Engineers of Japan, Inc. (JSAE). The state of corrosion was evaluated by observing the surface appearance and cross-sectional appearance in not less than 20 visual fields using an optical microscope under the magnification of 200 to 1,000, observing the degree of the progress of the corrosion into the inside, and classifying the observation results into five ranks. The criteria of the evaluation are as follows:

Evaluation rank 5: degree of progress of corrosion: only the plated layer corrodes or the depth of corrosion in the base material is less than 50 μm,

Evaluation rank 4: degree of progress of corrosion: the depth of corrosion in the base material is 50 μm to less than 100 μm,

Evaluation rank 3: degree of progress of corrosion: the depth of corrosion in the base material is less than the half of the sheet thickness,

Evaluation rank 2: degree of progress of corrosion: the depth of corrosion in the base material is not less than

the half of the sheet thickness,
Evaluation rank 1: perforation.

As a result, it was found that good corrosion
resistance of evaluation rank 4 or 5 was secured when Al
content in the plated layer was in the range from 0.001
to 4% and defined as A (in mass %), Mo content in the
plated layer was defined as B (in mass %), and Mo content
in the steel as C (in mass %), and A, B and C satisfied
the following equation 3:

$$100 \geq (A/3+B/6)/(C/6) \geq 0.01 \ldots 3$$

The detailed reason why the generation of non-
plating defects is suppressed is not always clear, but it
is estimated that non-plating defects are generated
because the wettability between Al added in a plating
bath and SiO_2 formed on the surface of a steel sheet is
inferior. Therefore, it becomes possible to suppress the
generation of non-plating defects by adding elements
which remove the adverse effect of Al added in a zinc
bath. As a result of the earnest studies by the present
inventors, it was found that the above object could be
attained by adding Mn in an appropriate concentration
range. It is estimated that Mn forms an oxide film more
preferentially than Al added in a zinc bath and enhances
its reactivity with an Si system oxide film formed on the
surface of a steel sheet.

Further, it is estimated that the fact that the
generation of flaws caused by Si scales formed during
hot-rolling has been suppressed by reducing Si amount in
a steel is also effective in improving appearance.
Further, with regard to the deterioration of material
quality accompanying the reduction of Si content, it was
found that ductility could be secured by the adjustment
of production conditions and the addition of other
components such as Al and Mo and the reduction of Si
content and the addition of Al were effective in
accelerating alloying.

The detailed reason is not clear, but it is
estimated that it is caused by the generation of non-
plating defects, the shapes of other defects, and the
difference in corrosion resistance between the base
material and the plated layer (difference in electric
potential).

Here, though the deposited amount of plating is not
particularly regulated, it is preferable that the
deposited amount on one side is not less than 5 g/mm^2
from the viewpoint of corrosion resistance. Though an
upper layer plating is applied to a hot-dip galvanized
steel sheet of the present invention for the purpose of
improving painting property and weldability, and various
kinds of treatments such as a chromate treatment, a
phosphate treatment, a lubricity improving treatment, a
weldability improving treatment, etc. are applied to a
hot-dip galvanized steel sheet of the present invention,
those cases do not deviate from the present invention.

Preferable microstructure of base steel sheet
        Next, the preferable microstructure of a base steel
sheet will be explained hereunder. It is preferable to
make the main structure a ferrite phase for sufficiently
securing ductility. However, when higher strength is
required, a bainite phase may be contained, but, from the
viewpoint of securing ductility, it is desirable that the
main phase contains a single phase of ferrite or a
complex phase of ferrite and bainite (the expression
"ferrite or ferrite and bainite" described in this
DESCRIPTION means the same, unless otherwise specified)
at not less than 50%, preferably 70%, in volume. In the
case of a complex phase of ferrite and bainite too, it is
desirable that ferrite is contained at not less than 50%
in volume for securing ductility. On the other hand, for
securing high-strength and high ductility in a well
balanced manner, it is preferable to make ferrite or
ferrite and bainite be contained at not more than 97% in

volume. Further, for securing high-strength and high
ductility simultaneously, it is also desirable to make
the structure a complex structure containing retained
austenite and/or martensite. For securing high-strength
and high ductility simultaneously, it is preferable to
make retained austenite and/or martensite be contained by
not less than 3% in total volume. However, if the total
value exceeds 50%, the steel sheet tends to be brittle,
and therefore it is desirable to control the value to not
more than 30% in total volume.

For securing the high ductility of a steel sheet
itself, it is prescribed that the average grain size of
ferrite is not more than 20 µm and the average grain size
of austenite and/or martensite, which constitute(s) the
second phase, is not more than 10 µm. Here, it is
desirable to make the second phase composed of austenite
and/or martensite and to make the average grain size of
austenite and/or martensite not more than 0.7 times the
average grain size of ferrite which constitutes the main
phase. However, as it is difficult in actual production
to make the average grain size of austenite and/or
martensite, which constitute(s) the second phase, less
than 0.01 time the average grain size of ferrite, it is
preferable that the rate is not less than 0.01.

Furthermore, for securing good plating adhesion, and
high-strength and high ductility in a well-balanced
manner, it is prescribed that, in the case that the
second phase of a steel sheet is composed of austenite, C
content: C (in mass %) and Mn content: Mn (in mass %) in
the steel, and the volume percentage of austenite: Vγ (in
%) and the volume percentage of ferrite and bainite: Vα
(in %) satisfy the following equation 4:

$$(V\gamma + V\alpha)/V\gamma \times C + Mn/8 \geqq 2.0 \ldots 4$$

By satisfying the above expression, a steel sheet

particularly excellent in the balance between strength
and ductility and having good plating adhesion can be
obtained.

5   The volume percentage and the like in case of
containing bainite will be explained hereunder. A
bainite phase is useful for enhancing strength by being
contained'at not less than 2% in volume, and also, when
it coexists with an austenite phase, it contributes to
stabilizing austenite and, as a result, it is useful for
10   securing a high n-value. Further, the phase is basically
fine and contributes to the plating adhesiveness during
heavy working too. In particular, in the case where the
second phase is composed of austenite, by controlling the
volume percentage of bainite to not less than 2%, the
15   balance of plating adhesiveness and ductility improves
further. On the other hand, as ductility deteriorates
when bainite is excessively formed, the volume percentage
of the bainite phase is limited to not more than 47%.

In addition to the above, a steel sheet containing
20   one or more of carbides, nitrides, sulfides and oxides at
not more than 1% in volume, as the remainder portion in
the microstructure, may be included in a steel sheet used
in the present invention. Here, the identification, the
observation of the sites, the average grain sizes
25   (average circle-equivalent grain sizes) and volume
percentages of each phase, ferrite, bainite, austenite,
martensite, interface oxide layers and remainder
structures in a microstructure can be quantitatively
measured by etching the cross-section of a steel sheet in
30   the rolling direction or in the transverse direction with
a niter reagent or the reagent disclosed in Japanese
Unexamined Patent Publication No. S59-219473 and
observing the cross-section with an optical microscope
under the magnification of 500 to 1,000.

35   Here, there sometimes is a case that the grain size
of martensite can hardly be measured by an optical
microscope. In that case, the average circle-equivalent

grain size is obtained by observing the boundaries of martensite blocks, the boundaries of packets, or the aggregates thereof and measuring the grain sizes using a scanning electron microscope.

Further, the observation of the shape of a grain boundary oxide layer and the identification thereof at the interface between a plated layer and a base layer are carried out using an scanning electron microscope and a transmission electron microscope, and the maximum depth is measured by observing the depth in not less than 20 visual fields under a magnification of not less than 1,000 and identifying the maximum value.

An average grain size is defined as a value obtained by the procedure specified in JIS based on the results obtained by observing the objects in not less than 20 visual fields using above-mentioned method.

Next, a plated layer will be explained hereunder.

It is preferable that the Al content in a plated layer is controlled within the range from 0.001 to 0.5% in mass. This is because, when the Al content is less than 0.001% in mass, dross is formed remarkably and a good appearance cannot be obtained and, when Al is added in excess of 0.5% in mass, the alloying reaction is markedly suppressed and a hot-dip alloyed zinc-coated layer is hardly formed.

The reason why the Mn content in a plated layer is set within the range from 0.001 to 2% in mass is that, in this range, non-plating defects are not generated and a plated layer having good appearance can be obtained. When the Mn content exceeds 2% in mass, Mn-Zn compounds precipitate in a plating bath and are trapped in the plated layer, resulting in deteriorating appearance markedly.

Further, in the case where spot weldability and a painting property are desired in particular, these properties can be improved by applying an alloying treatment. Specifically, by applying an alloying

treatment at a temperature of 300 to 550°C after a steel
sheet is dipped in a zinc bath, Fe is taken into a plated
layer, and a high-strength hot-dip galvanized steel sheet
excellent in a painting property and spot weldability can
5   be obtained. When the Fe content after an alloying
treatment is less than 5% in mass, spot weldability is
insufficient. On the other hand, when Fe content exceeds
20% in mass, the adhesiveness of the plated layer itself
deteriorates and the plated layer is destroyed, falls
10   off, and sticks to dies during working, causing flaws
during forming. Therefore, the range of the Fe content
in a plated layer when an alloying treatment is applied
is set at 5 to 20% by mass.

Further, it was found that non-plating defects could
15   be suppressed by containing one or more of Ca, Mg, Si,
Mo, W, Zr, Cs, Rb, K, Ag, Na, Cd, Cu, Ni, Co, La, Tl, Nd,
Y, In, Be, Cr, Pb, Hf, Tc, Ti, Ge, Ta, V and B in a
plated layer.

Here, though the deposited amount of plating is not
20   particularly regulated, it is preferable that the
deposited amount on one side is not less than 5 g/mm^2
from the viewpoint of corrosion resistance. Though an
upper layer plating is applied to a hot-dip galvanized
steel sheet of the present invention for the purpose of
25   improving painting property and weldability, and various
kinds of treatments such as a chromate treatment, a
phosphate treatment, a lubricity improving treatment, a
weldability improving treatment, etc. are applied to a
hot-dip galvanized steel sheet of the present invention,
30   those cases do not deviate from the present invention.

As one of the impurities in a plated layer, Mn is on
example. When the Mn content in a plated layer increases
to exceed the usual level of the impurities, non-plating
defects are hardly generated. However, it is difficult
35   to increase the Mn content in a plated layer because of
the restrictions related to the current plating
equipment. Therefore, the present invention allows Mn

content to be less than 0.001% in mass, which is within
the level of impurity elements, and is an invention
wherein a steel sheet having a least amount of non-
plating defects and surface defects can be obtained even
though Mn is not intentionally added to a plating bath.

The reason for specifying the following elements to
be in the ranges of Ca: 0.001 to 0.1%, Mg: 0.001 to 3%,
Si: 0.001 to 0.1%, Mo: 0.001 to 0.1%, W: 0.001 to 0.1%,
Zr: 0.001 to 0.1%, Cs: 0.001 to 0.1%, Rb: 0.001 to 0.1%,
K: 0.001 to 0.1%, Ag: 0.001 to 5%, Na: 0.001 to 0.05%,
Cd: 0.001 to 3%, Cu: 0.001 to 3%, Ni: 0.001 to 0.5%, Co:
0.001 to 1%, La: 0.001 to 0.1%, Tl: 0.001 to 8%, Nd:
0.001 to 0.1%, Y: 0.001 to 0.1%, In: 0.001 to 5%, Be:
0.001 to 0.1%, Cr: 0.001 to 0.05%, Pb: 0.001 to 1%, Hf:
0.001 to 0.1%, Tc: 0.001 to 0.1%, Ti: 0.001 to 0.1%, Ge:
0.001 to 5%, Ta: 0.001 to 0.1%, V: 0.001 to 0.2% and B:
0.001 to 0.1%, in mass, is that, in each of the ranges,
non-plating defects are suppressed and a plated layer
having good appearance can be obtained. When each
element exceeds each upper limit, dross containing each
element is formed and therefore the plating appearance
deteriorates markedly.

Next, the reasons for restricting the ranges of the
components in a steel sheet according to the present
invention will be explained hereunder.

C is an element added in order to sufficiently
secure the volume percentage of the second phase required
for securing strength and ductility in a well balanced
manner. In particular, when the second phase is composed
of austenite, C contributes to not only the acquisition
of the volume percentage but also the stability thereof
and improves ductility greatly. The lower limit is set
at 0.0001% by mass for securing the strength and the
volume percentage of the second phase, and the upper
limit is set at 0.3% by mass as the upper limit for
preserving weldability.

Si is an element added in order to accelerate the

formation of ferrite, which constitutes the main phase,
and to suppress the formation of carbides, which
deteriorate the balance between strength and ductility,
and the lower limit is set at 0.01% in mass. On the
other hand, its excessive addition adversely affects
weldability and plating wettability. Further, as C
accelerates the formation of an internal grain boundary
oxidized layer, the C content has to be suppressed to a
low level. Therefore, the upper limit is set at 2.5% in
mass. In particular, when appearance, such as scale
defects and the like, rather than strength, is the
problem, it is determined that C may be reduced up to
0.001% in mass, which is in a range not causing
operational problems.

Mn is added for the purpose of not only the control
of plating wettability and plating adhesion but also the
enhancement of strength. Further, it is added for
suppressing the precipitation of carbides and the
formation of pearlite which cause the deterioration of
strength and ductility. For that reason, Mn content is
set at not less than 0.001% in mass. On the other hand,
since Mn delays bainite transformation which contributes
to the improvement of ductility when the second phase is
composed of austenite, and deteriorates weldability, the
upper limit of Mn is set at 3% in mass.

Al is effective in controlling plating wettability
and plating adhesion and also accelerating bainite
transformation which contributes to the improvement of
ductility, in particular, when the second phase is
composed of austenite, and also Al improves the balance
between strength and ductility. Further, Al is an
element effective in suppressing the formation of Si
system internal grain boundary oxides too. Therefore,
the Al addition amount is set at not less than 0.0001% in
mass. On the other hand, since its excessive addition
deteriorates weldability and plating wettability
remarkably and suppresses the synthesizing reaction

markedly, the upper limit is set at 4% in mass.

Mo is added in order to suppress the generation of carbides and pearlite which deteriorate the balance between strength and ductility, and is an important element for securing good balance between strength and ductility under mitigated heat treatment conditions. Therefore, the lower limit of Mo is set at 0.001% in mass. Further, since its excessive addition generates retained austenite, lowers stability and hardens ferrite, resulting in the deterioration of ductility, the upper limit is set at 5%, preferably 1%.

Mg, Ca, Ti, Y, Ce and Rem are added for the purpose of suppressing the generation of an Si system internal grain boundary oxidized layer which deteriorates plating wettability, fatigue resistance and corrosion resistance. As the elements do not generate grain boundary oxides, as do Si system oxides, but can generate comparatively fine oxides in a dispersed manner, the oxides themselves of those elements do not adversely affect fatigue resistance. Further, as the elements suppress the formation of an Si system internal grain boundary oxidized layer, the depth of the internal grain boundary oxidized layer can be reduced and the elements contribute to the extension of fatigue life. One or more of the elements may be added and the addition amount of the elements is set at not less than 0.0001% in total mass. On the other hand, since their excessive addition deteriorates producibility such as casting properties and hot workability, and the ductility of steel sheet products, the upper limit is set at 1% in mass.

Further, a steel according to the present invention may contain one or more of Cr, Ni, Cu, Co and W aiming at enhancing strength.

Cr is an element added for enhancing strength and suppressing the generation of carbides, and the addition amount is set at not less than 0.001% in mass. However, its addition amount exceeding 25% in mass badly affects

workability, and therefore the value is determined to be the upper limit.

Ni content is determined to be not less than 0.001% in mass for improving plating properties and enhancing strength. However, its addition amount exceeding 10% in mass badly affects workability, and therefore the value is determined to be the upper limit.

Cu is added in the amount of not less than 0.001% in mass for enhancing strength. However, its addition amount exceeding 5% in mass badly affects workability, and therefore the value is determined to be the upper limit.

Co is added in the amount of not less than 0.001% in mass for improving the balance between strength and ductility by the control of plating properties and bainite transformation. The upper limit is not specifically determined, but, as Co is an expensive element and an addition in a large amount is not economical, it is desirable to set the addition amount at not more than 5% in mass.

The reason why the W content is determined to be in the range from 0.001 to 5% in mass is that the effect of enhancing strength appears when the amount is not less than 0.001% in mass, and that the addition amount exceeding 5% in mass adversely affects workability.

Furthermore, a steel according to the present invention may contain one or more of Nb, Ti, V, Zr, Hf and Ta, which are strong carbide forming elements, aiming at enhancing the strength yet further.

Those elements form fine carbides, nitrides or carbonitrides and are very effective in strengthening a steel sheet. Therefore, it is determined that one or more of those elements is/are added by not less than 0.001% in mass at need. On the other hand, as those elements deteriorate ductility and hinder the concentration of C into retained austenite, the upper limit of the total addition amount is set at 1% by mass.

B can also be added as needed. B addition in the
amount of not less than 0.0001% in mass is effective in
strengthening grain boundaries and a steel material.
However, when the addition amount exceeds 0.1% in mass,
not only the effect is saturated but also the strength of
a steel sheet is increased more than necessary, resulting
in the deterioration of workability, and therefore the
upper limit is set at 0.1% in mass.

The reason why P content is determined to be in the
range from 0.0001 to 0.3% in mass is that the effect of
enhancing strength appears when the amount is not less
than 0.0001% in mass and ultra-low P is economically
disadvantageous, and that the addition amount exceeding
0.3% in mass adversely affects weldability and
producibility during casting and hot-rolling.

The reason why the S content is determined to be in
the range from 0.0001 to 0.1% in mass is that ultra-low S
of less than the lower limit of 0.0001% in mass is
economically disadvantageous, and that an addition amount
exceeding 0.1% in mass adversely affects weldability and
producibility during casting and hot-rolling.

P, S, Sn, etc. are unavoidable impurities. It is
desirable that P content is not more than 0.05%, S
content not more than 0.01% and Sn content not more than
0.01%, in mass. It is well known that the small addition
of P, in particular, is effective in improving the
balance between strength and ductility.

Methods of producing a high-strength hot-dip
galvanized steel sheet having such a structure as
mentioned above will be explained hereunder.

When a steel sheet according to the present
invention is produced by the processes of hot-rolling,
cold-rolling and annealing, a slab adjusted to a
prescribed components is cast or once cooled after the
casting, and then heated again at a temperature of not
less than 1,180°C and hot-rolled. At this time, it is
desirable that the reheating temperature is set at not

less than 1,150°C or at not more than 1,100°C to suppress
the formation of a grain boundary oxidized layer. When
the reheating temperature becomes very high, oxidized
scales tend to be formed on the whole surface
5   comparatively uniformly and thus the oxidation of grain
boundaries tends to be suppressed.

However, as heating to a temperature exceeding
1,250°C accelerates extraordinary oxidation locally, this
temperature is determined to be the upper limit.
10 Low temperature heating delays the formation of an
oxidized layer itself.

Further, for the purpose of suppressing the
formation of excessive internal oxidation, it is
determined that the hot-rolling is finished at a
15 temperature of not less than 880°C, and it is preferable
for the reduction of the grain boundary oxidation depth
of a product to remove surface scales by using a high-
pressure descaling apparatus or applying heavy pickling
after the hot-rolling. Thereafter, a steel sheet is
20 cold-rolled and annealed, and thus a final product is
obtained. In this case, it is common that the hot-roll
finishing temperature is controlled to a temperature of
not less than Ar_3 transformation temperature which is
determined by the chemical composition of a steel, but
25 the properties of a final steel sheet product are not
deteriorated as long as the temperature is up to about
10°C lower than Ar_3.

However, the hot-roll finishing temperature is set
at not more than 1,100°C to avoid the formation of
30 oxidized scales in a large amount.

Further, by controlling the coiling temperature
after cooling to not less than the bainite transformation
commencement temperature, which is determined by the
chemical composition of a steel, increasing the load more
35 than necessary during cold-rolling can be avoided.
However, that does not apply to the case where the total
reduction rate at cold-rolling is low, and, even though a

steel sheet is coiled at a temperature of not more than
the bainite transformation temperature of a steel, the
properties of the final steel sheet product are not
deteriorated. Further, the total reduction rate of cold-
rolling is determined from the relation between the final
thickness and the cold-rolling load, and as long as the
total reduction rate is not less than 40%, preferably
50%, that is effective in the reduction of grain boundary
oxidation depth and the properties of the final steel
sheet product are not deteriorated.

In the annealing process after cold-rolling, when
the annealing temperature is less than the value of
$0.1 \times (Ac_3 - Ac_1) + Ac_1$ (°C) which is expressed by the Ac_1
temperature and Ac_3 temperature (for example, refer to
"Tekko Zairyo Kagaku": W. C. Leslie, Supervisory
Translator: Nariyasu Koda, Maruzen, P273) which are
determined by the chemical composition of a steel, the
amount of austenite formed during annealing is small,
thus a retained austenite phase or a martensite phase
cannot remain in the final steel sheet, and therefore the
value is determined to be the lower limit of the
annealing temperature. Here, the higher the annealing
temperature is, the more the formation of a grain
boundary oxidized layer is accelerated.

As a high temperature annealing causes the formation
of a grain boundary oxidized layer to accelerate and the
production costs to increase, the upper limit of the
annealing temperature is determined to be $Ac_3 - 30$ (°C).
In particular, the closer to Ac_3 (°C) the annealing
temperature becomes, the more the formation of a grain
boundary oxidized layer is accelerated. The annealing
time is required to be not less than 10 seconds in this
temperature range for equalizing the temperature of a
steel sheet and securing austenite. However, when the
annealing time exceeds 30 minutes, the formation of a
grain boundary oxidized layer is accelerated and costs
increase. Therefore, the upper limit is set at 30

minutes.

The primary cooling thereafter is important in accelerating the transformation from an austenite phase to a ferrite phase and stabilizing the austenite by concentrating C in the austenite phase before the transformation.

When the maximum temperature during annealing is defined as Tmax (°C), a cooling rate of less than Tmax/1,000°C/sec. brings about disadvantages in the production such as to cause a process line to be longer and to cause the production rate to fall remarkably. On the other hand, when the cooling rate exceeds Tmax/10°C/sec., the ferrite transformation occurs insufficiently, the retained austenite in the final steel sheet product is hardly secured, and hard phases such as a martensite phase become abundant.

When the maximum temperature during annealing is defined as Tmax (°C) and the primary cooling is carried out up to a temperature of less than Tmax - 200°C, pearlite is generated and ferrite is not generated sufficiently during the cooling, and therefore the temperature is determined to be the lower limit. However, when the primary cooling terminates at a temperature exceeding Tmax - 100°C, then the progress of the ferrite transformation is insufficient, and therefore the temperature is determined to be the upper limit.

A cooling rate of less than 0.1°C/sec. causes the formation of a grain boundary oxidized layer to be accelerated and brings about disadvantages in the production to cause a process line to be longer and to cause the production rate to fall remarkably. Therefore, the lower limit of the cooling rate is set at 0.1°C/sec. On the other hand, when the cooling rate exceeds 10°C/sec., the ferrite transformation occurs insufficiently, the retained austenite in the final steel sheet product is hardly secured, and hard phases such as a martensite phase become abundant, and therefore the

upper limit is set at 10°C/sec.

When the primary cooling is carried out up to a
temperature of less than 650°C, pearlite is generated
during the cooling, C, which is an element stabilizing
5   austenite, is wasted, and a sufficient amount of retained
austenite is not obtained finally and, therefore, the
lower limit is set at 650°C. However, when the cooling
terminates at a temperature exceeding 710°C, the progress
of ferrite transformation is insufficient, the growth of
10   a grain boundary oxidized layer is accelerated, and
therefore, the upper limit is set at 710°C.

In the rapid cooling of the secondary cooling which
is carried out successively, the cooling rate has to be
at least not less than 0.1°C/sec., preferably not less
15   than 1°C/sec., so as not to generate a pearlite
transformation, the precipitation of iron carbides, and
the like, during the cooling.

However, as a cooling rate exceeding 100°C/sec. is
hardly implemented from the viewpoint of an equipment
20   capacity, the range of the cooling rate is determined to
be from 0.1 to 100°C/sec., preferably from 1.0 to
100°C/sec.

When the cooling termination temperature of the
secondary cooling is lower than the plating bath
25   temperature, operational problems arise and, when it
exceeds the plating bath temperature + 50 to + 100°C,
carbides precipitate for a short period of time, and
therefore the sufficient amount of retained austenite and
martensite cannot be secured. For those reasons, the
30   cooling termination temperature of the secondary cooling
is set in the range from the zinc plating bath
temperature to the zinc plating bath temperature + 50 to
100°C. It is preferable to hold a steel sheet thereafter
in the temperature range for not less than 1 second
35   including the dipping time in the plating bath for the
purpose of securing operational stability in the sheet
travelling, accelerating the formation of bainite as much

as possible, and sufficiently securing plating
wettability. When the holding time becomes long, it
badly affects productivity and carbides are generated,
and therefore it is preferable to restrict the holding
time to not more than 3,000 seconds excluding the time
required for an annealing treatment.

For stabilizing an austenite phase retained in a
steel sheet at the room temperature, it is essential to
increase the carbon concentration in austenite by
transforming a part of the austenite phase into a bainite
phase. For accelerating the bainite transformation
including in an alloying treatment process, it is
preferable to hold a steel sheet for 1 to 3,000 seconds,
preferably 15 seconds to 20 minutes, in the temperature
range from 300 to 550°C. When the temperature is less
than 300°C, the bainite transformation is hardly
generated. However, when the temperature exceeds 550°C,
carbides are formed and it becomes difficult to reserve a
retained austenite phase sufficiently, and therefore the
upper limit is set at 550°C.

For forming a martensite phase, it is not necessary
to make bainite transformation occur, which is different
from the case of a retained austenite phase. On the
other hand, as the formation of carbides and a pearlite
phase must be suppressed as in the case of a retained
austenite phase, it is necessary to apply an alloying
treatment sufficiently after the secondary cooling, and
it is determined that an alloying treatment is carried
out at a temperature of 300 to 550°C, preferably 400 to
550°C.

For securing oxides at an interface in a prescribed
amount, it is desirable to control the temperature and
working history from the hot-rolling stage. Firstly, it
is desirable to generate a surface oxidized layer as
evenly as possible by controlling: the heating
temperature of a slab to 1,150 to 1,230°C; the reduction
rate up to 1,000°C to not less than 50%; the finishing

temperature to not less than 850°C, preferably not less
than 880°C; and the coiling temperature to not more than
650°C, and, at the same time, to leave elements such as
Ti, Al, etc. in a solid solution state as much as

5   possible for suppressing the formation of Si oxides
during annealing. Further, it is desirable to remove a
oxide layer formed during hot-rolling as much as possible
by employing a high-pressure descaling or a heavy
pickling after the finish rolling. Further, it is

10   desirable to control the cold-rolling reduction rate to
not less than 30% using rolls not more than 1,000 mm in
diameter for the purpose of breaking the generated
oxides. In annealing thereafter, it is desirable to heat
a steel sheet at the rate of 5°C/sec. up to the

15   temperature range of not less than 750°C for the purpose
of accelerating the formation of other oxides by
suppressing the formation of SiO_2. On the other hand,
when the annealing temperature is high or the annealing
time is long, many oxides are generated and workability

20   and fatigue resistance are deteriorated. Therefore, as
determined in the present invention according to the item
(33), it is desirable to control the residence time to
not more than 60 minutes at an annealing temperature
whose highest temperature is in the range from not less

25   than $0.1 \times (Ac_3 - Ac_1) + Ac_1$ (°C) to not more than $Ac_3 - 30$
(°C).

Examples
       The present invention will hereunder be explained in
30   detail based on the examples.
Example 1 of Embodiment 1
       The present invention will hereunder be explained in
detail based on Example 1 of Embodiment 1.
       Steels having chemical compositions shown in Table 1
35   were heated to the temperature of 1,200°C; the hot-
rolling of the steels was finished at a temperature of
not less than the Ar_3 transformation temperature; and the

hot-rolled steel sheets were cooled and then coiled at a
temperature of not less than the bainite transformation
commencement temperature which was determined by the
chemical composition of each steel, pickled, and cold-

5   rolled into cold-rolled steel sheets 1.0 mm in thickness.

The steels, M-1, N-1, O-1, P-1 and Q-1, which will
be mentioned later, were hot-rolled on the conditions of
the reduction rate of 70% up to 1,000°C, the finishing
temperature of 900°C and the coiling temperature of

10   700°C, and were cold-rolled with the reduction rate of
50% using the rolls 800 mm in diameter. The other steels
were hot-rolled on the conditions of the reduction rate
of 70% up to 1,000°C, the finishing temperature of 900°C
and the coiling temperature of 600°C, and were cold-

15   rolled with the reduction rate of 50% using the rolls
1,200 mm in diameter.

Table 1-1 (Continued): Chemical composition

Steel code	C	Si	Mn	AL	Mo	Mg	Ca	Y	Ce	Rem	Cr	Ni
A	0.16	0.2	1.05	1.41								
B	0.13	0.5	0.97	1.09	0.16							
C	0.11	0.9	1.22	0.62		0.0015						
D	0.21	0.3	1.63	1.52	0.22		0.0008					
E	0.08	0.7	1.53	0.05				0.0005		0.001		
F	0.18	0.5	1.23	1.52	0.13				0.003			
G	0.09	0.8	1.41	0.03							0.11	0.84
H	0.25	0.01	1.74	1.63	0.11							
I	0.14	1.22	1.13	1.23	0.05							
J	0.13	2.32	1.25	0.96	0.07					0.005		
K	0.19	0.78	1.1	0.5	0.12							

Table 1-2 (Continued): Chemical composition

L	0.17	0.19	0.98	0.7	0.07			0.007			
M	0.19	0.04	1.45	0.99	0.12						
N	0.21	0.08	1.62	1.2	0.11						
O	0.2	0.01	1.51	1.15	0.13				0.008		
P	0.09	0.45	1.42	0.46	0.11		0.001				
Q	0.12	0.05	1.78	0.75	0.26						
CA	0.25	4.56	1.85	0.03							
CB	0.28	0.75	2.56	0.03	5.32						
CC	0.02	1.98	0.52	0.63		0.023					
CD	0.06	0.52	2.98	0.05	1.31				0.64	2.3	0.8
CE	0.23	0.01	2.61	0.04	0.5						0.3

Table 1-3 (Continued): Chemical composition

Steel code	Cu	Co	Ti	Nb	V	B	Zr	Hf	Ta	W	P	S	Remarks
A											0.02	0.005	Invented steel
B											0.01	0.004	Invented steel
C											0.01	0.006	Invented steel
D											0.015	0.002	Invented steel
E						0.0007					0.025	0.003	Invented steel
F			0.015								0.01	0.005	Invented steel
G	0.4										0.02	0.004	Invented steel
H		0.15									0.02	0.003	Invented steel
I				0.022	0.03						0.01	0.002	Invented steel
J											0.01	0.001	Invented steel
K								0.005		0.05	0.04	0.002	Invented steel

Table 1-4 (Continued): Chemical composition

	0.01			0.25	0.01	
L				0.02	0.002	Invented steel
M				0.005	0.002	Invented steel
N				0.012	0.001	Invented steel
O				0.007	0.002	Invented steel
P				0.01	0.003	Invented steel
Q				0.015	0.002	Invented steel
CA				0.01	0.003	Comparative steel
CB				0.02	0.004	Comparative steel
CC		1.15		0.01	0.004	Comparative steel
CD		1.2		0.02	0.005	Comparative steel
CE			0.15	0.02	0.002	Comparative steel

(Note) The underlined numerals are the conditions which are outside the range according to the present invention.

After that, the Ac_1 transformation temperature and the Ac_3 transformation temperature were calculated from the components (in mass %) of each steel according to the following equations:

$$Ac_1 = 723 - 10.7 \times Mn\% + 29.1 \times Si\%,$$

$$Ac_3 = 910 - 203 \times (C\%)^{1/2} + 44.7 \times Si\% + 31.5 \times Mo\% - 30 \times Mn\% - 11 \times Cr\% + 400 \times Al\%.$$

The steel sheets were plated by: heating them at a rate of 5°C/sec. to the annealing temperature calculated from the Ac_1 transformation temperature and the Ac_3 transformation temperature and retaining them in the N_2 atmosphere containing 10% of H_2; thereafter, cooing them up to 600 to 700°C at a cooling rate of 0.1 to 10°C/sec.; successively cooling them to the plating bath temperature at a cooling rate of 1 to 20°C/sec.; and dipping them in the zinc plating bath of 460°C for 3 seconds, wherein the compositions of the plating bath were varied.

Further, as the Fe-Zn alloying treatment, some of the steel sheets were retained in the temperature range from 300 to 550°C for 15 seconds to 20 minutes after they were plated and Fe contents in the plated layers were adjusted so as to be 5 to 20% in mass. The plating properties were evaluated by visually observing the state of dross entanglement on the surface and measuring the area of non-plated portions. The compositions of the plated layers were determined by dissolving the plated layers in a 5% hydrochloric acid solution containing an inhibitor and chemically analyzing the solution.

JIS #5 specimens for tensile test were prepared from the plated steel sheets (rolled at skin-pass line at the reduction rate of 0.5 - 2.0%) and mechanical properties thereof were measured. Further, the fracture lives were evaluated relatively by imposing a stress corresponding to 50% of the tensile strength in the plane bending fatigue test. Further, the corrosion resistance was evaluated by a repeated salt spray test.

As shown in Table 2, in the steels according to the present invention, the depth of the grain boundary oxidized layers is shallow and the fatigue life under a stress corresponding to 50% of the tensile strength exceeds 10^6 cycles of bending. Further, the strength and the elongation are well balanced and rust formation is not observed, allowing a good appearance even after the test.

Table 2-1-1 (Continued): Plating wettability, corrosion resistance, microstructure and fatigue resistance of each steel

Steel code	Treatment number	Application of alloying heat treatment after plating treatment	Appearance after repeated salt splay test	Depth of grain boundary oxidized layer/μm
A	1	No	Rust not formed	0.05
A	2	Yes	Rust not formed	0.07
A	3	Yes	Rust not formed	0.85
B	1	No	Rust not formed	0.09
B	2	Yes	Rust not formed	0.13
B	3	No	Rust not formed	1.05
C	1	Yes	Rust not formed	0.15
C	2	Yes	Rust formed	0.56
D	1	Yes	Rust not formed	0.11
D	2	Yes	Rust not formed	0.08
E	1	Yes	Rust not formed	0.23
E	1-1	Yes	Rust not formed	0.3
E	1-2	Yes	Rust not formed	0.24

Table 2-1-2 (Continued): Plating wettability, corrosion resistance, microstructure and fatigue resistance of each steel

E	1-3	Yes	Rust not formed	0.2
E	1-4	Yes	Rust not formed	0.33
E	1-5	Yes	Rust not formed	0.35
E	2	Yes	Rust formed	1.23
F	1	No	Rust not formed	0.09
F	2	Yes	Rust not formed	0.08
G	1	Yes	Rust not formed	0.07
G	2	Yes	Rust formed	1.1
H	1	No	Rust not formed	0.05
I	1	Yes	Rust not formed	0.42
I	1-1	Yes	Rust not formed	0.3
I	1-2	Yes	Rust not formed	0.35
I	1-3	Yes	Rust not formed	0.3
I	1-4	Yes	Rust not formed	0.28
I	1-5	Yes	Rust not formed	0.25

Table 2-1-3 (Continued): Plating wettability, corrosion resistance, microstructure and fatigue resistance of each steel

Steel code	Kind of main phase	Volume percentage of ferrite, or ferrite and bainite/%*	Average grain size of main phase/μm	Depth of grain boundary oxidized layer divided by average grain size of main phase	Volume percentage of martensite/%*
A	Ferrite	95	11	4.55E-03	0
A	Ferrite	95.5	9	7.78E-03	0
A	Ferrite	100	25	3.40E-02	0
B	Ferrite	94	8	1.13E-02	0
B	Ferrite	93.5	8	1.63E-02	1
B	Ferrite	93	23	4.57E-02	7
C	Ferrite	96	12	1.25E-02	0
C	Ferrite	100	27	2.07E-02	0
D	Ferrite	91	6	1.83E-02	1
D	Ferrite	91	5	1.60E-02	9
E	Ferrite	93	9	2.56E-02	7
E	Ferrite	93	10	3.00E-02	7
E	Ferrite	92	9	2.67E-02	8

Table 2-1-4 (Continued): Plating wettability, corrosion resistance, microstructure and fatigue resistance of each steel

E	Ferrite	93	9	2.22E-02	7
E	Ferrite	93	11	3.00E-02	7
E	Ferrite	92	9	3.89E-02	8
E	Ferrite	94	15	8.20E-02	6
F	Ferrite	93	10	9.00E-03	0
F	Ferrite	93	9	8.89E-03	1
G	Ferrite	95	7	1.00E-02	1
G	Ferrite	96	10	1.10E-01	1
H	Ferrite	89	6	8.33E-03	0
I	Ferrite	94	5	8.40E-02	0
I	Ferrite	94	6	5.00E-02	0
I	Ferrite	93	5	7.00E-02	0
I	Ferrite	94	6	5.00E-02	0
I	Ferrite	94	6	4.67E-02	0
I	Ferrite	94	6	4.17E-02	0

Table 2-1-5 (Continued): Plating wettability, corrosion resistance, microstructure and fatigue resistance of each steel

Steel code	Volume percentage of austenite/%	Tensile strength/MPa	Elongation/%	Fatigue life under the stress corresponding to 50% of tensile strength/cycles	
A	5	565	41	1.23E+06	Invented steel
A	4.5	560	40	1.45E+06	Invented steel
A	0	520	31	3.20E+05	Comparative steel
B	6	595	40	1.01E+06	Invented steel
B	5.5	590	39	1.17E+06	Invented steel
B	0	600	30	1.59E+05	Comparative steel
C	4	555	42	1.10E+06	Invented steel
C	0	435	32	3.60E+05	Comparative steel
D	8	795	33	1.20E+06	Invented steel
D	0	825	28	1.07E+06	Invented steel
E	0	615	33	1.90E+06	Invented steel
E	0	610	33	1.10E+06	Invented steel
E	0	620	32	1.50E+06	Invented steel
E	0	615	32	1.40E+06	Invented steel
E	0	615	33	1.10E+06	Invented steel

Table 2-1-6 (Continued): Plating wettability, corrosion resistance, microstructure and fatigue resistance of each steel

Steel					
E	0	620	33	1.20E+06	Invented steel
E	0	630	31	2.70E+05	Comparative steel
F	7	675	37	2.01E+06	Invented steel
F	6	670	36	1.70E+06	Invented steel
G	4	635	34	1.60E+06	Invented steel
G	3	630	34	1.85E+05	Comparative steel
H	11	815	33	2.00E+06	Invented steel
I	6	790	30	1.00E+06	Invented steel
I	6	795	30	1.20E+06	Invented steel
I	7	825	29	1.01E+06	Invented steel
I	6	795	30	1.20E+06	Invented steel
I	6	800	30	1.15E+06	Invented steel
I	6	810	29	1.03E+06	Invented steel

(Note) The underlined numerals are the conditions which are outside the range according to the present invention.

(Example) "4.55E – 03" means 4.55×10^{-3}.
* The sum of the volume percentage of each phase is 100%, and the phases which are hardly observed and identified by an optical microscope, such as carbides, oxides, sulfides, etc., are included in the volume percentage of the main phase.

Table 2-2-1 (Continued): Plating wettability, corrosion resistance, microstructure and fatigue resistance of each steel

Steel code	Treatment number	Application of alloying heat treatment after plating treatment	Appearance after repeated salt splay test	Depth of grain boundary oxidized layer/μm
I	2	Yes	Rust formed	1.15
J	1	No	Rust not formed	0.65
J	2	Yes	Rust not formed	0.7
J	3	Yes	Rust formed	1.54
K	1-1	No	Rust not formed	0.05
K	1-2	No	Rust not formed	0.04
K	1-3	No	Rust not formed	0.05
K	2-1	Yes	Rust not formed	0.04
K	2-2	Yes	Rust not formed	0.07
K	2-3	Yes	Rust not formed	0.04
L	1-1	Yes	Rust not formed	0.04
L	1-2	Yes	Rust not formed	0.06
L	1-3	Yes	Rust not formed	0.05

Table 2-2-2 (Continued): Plating wettability, corrosion resistance, microstructure and fatigue resistance of each steel

L	1-4	Yes	Rust not formed	0.03
M	1	Yes	Rust not formed	0.03
N	1	Yes	Rust not formed	0.02
O	1	Yes	Rust not formed	0.08
P	1	Yes	Rust not formed	0.25
Q	1	Yes	Rust not formed	0.07
CA	1	Yes	Rust formed	1.26
CB	1	Yes	Rust not formed	0.65
CC	1	No	Rust formed	1.65
CD	1		Many cracks occurred at hot-rolling	
CE	1		Many cracks occurred at cold-rolling	

Table 2-2-3 (Continued): Plating wettability, corrosion resistance, microstructure and fatigue resistance of each steel

Steel code	Kind of main phase	Volume percentage of ferrite, or ferrite and bainite/%*	Average grain size of main phase/μm	Depth of grain boundary oxidized layer divided by average grain size of main phase	Volume percentage of martensite/%
I	Ferrite	94	5	2.30E-01	1
J	Ferrite	95	9	7.22E-02	1
J	Ferrite	95	9	7.78E-02	1
J	Ferrite	100	15	1.03E-01	0
K	Ferrite	90.2	11	4.55E-03	0
K	Ferrite	91	10	4.00E-03	0
K	Ferrite	90.5	10	5.00E-03	0
K	Ferrite	91	10	4.00E-03	0
K	Ferrite	91	9	7.78E-03	0
K	Ferrite	90.5	9	4.44E-03	0
L	Ferrite	91.5	11	3.64E-03	0
L	Ferrite	92	10	6.00E-03	0
L	Ferrite	92	9	5.56E-03	0

Table 2-2-4 (Continued): Plating wettability, corrosion resistance, microstructure and fatigue resistance of each steel

L	Ferrite	92.5	10	3.00E-03	0
M	Ferrite	91.5	12	2.50E-03	0
N	Ferrite	92	9	2.22E-03	0
O	Ferrite	91	10	8.00E-03	0
P	Ferrite and bainite	Ferrite: 65%, bainite: 23%	4	6.25E-02	0
Q	Ferrite and bainite	Ferrite: 55%, bainite: 37%	3	2.33E-02	4
CA	Ferrite	100	11	1.15E-01	0
CB	Bainite		Immeasurable	Immeasurable	Immeasurable
CC	Ferrite	100	5	3.30E-01	0
CD					
CE					

Table 2-2-5 (Continued): Plating wettability, corrosion resistance, microstructure and fatigue resistance of each steel

Steel code	Volume percentage of austenite/%	Tensile strength/MPa	Elongation/%	Fatigue life under the stress corresponding to 50% of tensile strength/cycles	
I	5	780	28	3.90E+05	Comparative steel
J	4	675	33	1.40E+06	Invented steel
J	4	670	33	1.33E+06	Invented steel
J	0	590	25	2.50E+05	Comparative steel
K	9.8	720	34	1.38E+06	Invented steel
K	9	700	33	1.22E+06	Invented steel
K	9.5	715	34	1.10E+06	Invented steel
K	9	720	33	1.40E+06	Invented steel
K	9	695	34	1.13E+06	Invented steel
K	9.5	700	34	1.36E+06	Invented steel
L	8.5	620	39	1.07E+06	Invented steel
L	8	600	38	1.10E+06	Invented steel
L	8	595	38	1.07E+06	Invented steel
L	7.5	590	38	1.37E+06	Invented steel
M	8.5	645	36	2.23E+06	Invented steel
N	8	675	35	2.10E+06	Invented steel
O	9	650	35	2.20E+06	Invented steel
P	12	790	30	2.70E+06	Invented steel

Table 2-2-6 (Continued): Plating wettability, corrosion resistance, microstructure and fatigue resistance of each steel

Q	4	845	28	2.10E+06	Invented steel
CA	0	620	22	9.45E+04	Comparative steel
CB	0	840	10	7.50E+05	Comparative steel
CC	0	645	21	1.20E+05	Comparative steel
CD					Comparative steel
CE					Comparative steel

(Note) The underlined numerals are the conditions which are outside the range according to the present invention.

(Example) "4.55E – 03" means 4.55×10^{-3}.

* The sum of the volume percentage of each phase is 100%, and the phases which are hardly observed and identified by an optical microscope, such as carbides, oxides, sulfides, etc., are included in the volume percentage of the main phase.

** With regard to the main phases of the steels P and Q, since bainite can be clearly identified by an optical microscope, the volume percentage thereof is shown in the table. With regard to other steels, since the distribution of bainite is very fine and the volume percentage is as low as less than 20%, the quantitative measurement thereof is unreliable and thus it is not shown in the table.

Table 3-1 (Continued): Plating property of each steel

Steel code-Treatment number	Al content in plated layer %	Mn content in plated layer %	Fe content in plated layer %	Value calculated by expression (1)	Other elements in plated layer %
C-1	1	1	15	1.77	
C-2	0.5	0.01	7	-4.35	
E-1	0.05	0.5	12	7.76	
E-1-1	0.17	0.04	9	0.51	Si: 0.02
E-1-2	0.18	0.03	9	0.26	Y: 0.02, Nd: 0.04
E-1-3	0.17	0.03	9	0.38	La: 0.02
E-1-4	0.15	0.02	9	0.51	B: 0.005
E-1-5	0.2	0.08	9	0.63	Rb: 0.02
E-2	0.25	0.01	8	-0.87	
G-1	0.3	0.3	11	2.05	
G-2	0.2	0.01	8	-0.33	
H-1	0.5	0.5	7	1.26	
I-1-1	0.1	0.05	7	0.63	Cs: 0.04

Table 3-2 (Continued): Plating property of each steel

Steel code-Treatment number	Al content in plated layer %	Mn content in plated layer %	Fe content in plated layer %	Value calculated by expression (1)	Other elements in plated layer %
I-1-2	0.15	0.1	8	0.63	K: 0.02, Ni: 0.05
I-1-3	0.14	0.1	7	0.76	Ag: 0.01, Co: 0.01
I-1-4	0.3	0.25	8	0.63	Ni: 0.02, Cu: 0.03
I-1-5	0.35	0.27	9	0.26	Na: 0.02, Cr: 0.01
I-2	0.5	0.1		-3.74	
J-1	1	1		0.24	
J-2	1	1	8	0.24	
J-3	0.5	0	4	-6.02	
K-1-1	1	0.9		0.69	Be: 0.005
K-1-2	0.8	0.7		0.69	Ti: 0.01, In: 0.01

Table 3-3 (Continued): Plating property of each steel

Steel code-Treatment number	Al content in plated layer %	Mn content in plated layer %	Fe content in plated layer %	Value calculated by expression (1)	Other elements in plated layer %
K-1-3	0.9	0.8		0.69	Cd: 0.02
K-2-1	0.9	0.8	9	0.69	Pb: 0.03
K-2-2	1	0.95	8	1.32	To: 0.02
K-2-3	1	0.9	8	0.69	W: 0.02, Hf: 0.02
L-1-1	0.3	0.15	10	0.60	Mo: 0.01
L-1-2	0.25	0.14	10	1.10	Zr: 0.01, Ti: 0.01
L-1-3	0.3	0.2	9	1.23	Ge: 0.01
L-1-4	0.3	0.15	11	0.60	Ta: 0.01, V: 0.01
M-1	0.3	0.4	11	3.73	
N-1	0.4	0.3	11	1.23	
O-1	0.5	0.5	12	2.48	
P-1	0.1	0.3	11	4.98	
Q-1	0.15	0.2	10	3.10	

Table 3-4 (Continued): Plating property of each steel

Occurrence of non-plating defect	Appearance after repeated salt splay test	Remarks
No	Rust not formed	Invented steel
Yes	Rust formed	Comparative steel
No	Rust not formed	Invented steel
No	Rust not formed	Invented steel
No	Rust not formed	Invented steel
No	Rust not formed	Invented steel
No	Rust not formed	Invented steel
No	Rust not formed	Invented steel
Yes	Rust formed	Comparative steel
No	Rust not formed	Invented steel
Yes	Rust formed	Comparative steel
No	Rust not formed	Invented steel
No	Rust not formed	Invented steel

Table 3-5 (Continued): Plating property of each steel

Occurrence of non-plating defect	Appearance after repeated salt splay test	Remarks
No	Rust not formed	Invented steel
No	Rust not formed	Invented steel
No	Rust not formed	Invented steel
No	Rust not formed	Invented steel
Yes	Rust formed	Comparative steel
No	Rust not formed	Invented steel
No	Rust not formed	Invented steel
Yes	Rust formed	Comparative steel
No	Rust not formed	Invented steel
No	Rust not formed	Invented steel

Table 3-6 (Continued): Plating property of each steel

Occurrence of non-plating defect	Appearance after repeated salt splay test	Remarks
No	Rust not formed	Invented steel
No	Rust not formed	Invented steel
No	Rust not formed	Invented steel
No	Rust not formed	Invented steel
No	Rust not formed	Invented steel
No	Rust not formed	Invented steel
No	Rust not formed	Invented steel
No	Rust not formed	Invented steel
No	Rust not formed	Invented steel
No	Rust not formed	Invented steel
No	Rust not formed	Invented steel
No	Rust not formed	Invented steel
No	Rust not formed	Invented steel

(Note) The remainder element in plated layer is zinc.
The underlined numerals are the conditions which
are outside the range according to the present
invention.

From Table 3, it can be understood that, even in the
case of the steel sheets containing relatively large
amounts of Si, the steel sheets according to the present
invention, wherein the compositions in the plated layers
5   and the steel sheets are regulated, do not form non-
plating defects and have good corrosion resistance.

        Further, it can be understood that, when the fourth
elements ("other elements in plated layer" in Table 3)
are contained in a plated layer, the plating properties
10   are good even in the case where the value determined by
the left side of the equation 1 is small.

        Table 4 shows the influence of the production
conditions. In the case of steel sheets whose production
conditions do not satisfy the prescribed requirements,
15   even having the compositions within the prescribed range,
the depth of the grain boundary oxidized layers is large
and their fatigue life is short. Further, it is
understood that, conversely, even though the production
conditions satisfy the prescribed requirements, in the
20   case where the compositions of the steel sheets deviate
from the prescribed range, the fatigue life is also
short.

        Table 5 shows the influence of the shape of the
oxides. In the steel sheets according to the present
25   invention, rust is not formed and also the fatigue
strength exceeds 2×10^6 cycles of bending, and therefore
the steel sheets have good material quality.

Table 4-1-1 (Continued): Production method and each property

Steel code	Treatment number	Ac₃ (calculated) −30 (°C)/°C	0.1x(Ac₃-Ac₁)+Ac₁ (calculated)/°C	Maximum temperature during annealing/°C	Resident time in the temperature range from 0.1x(Ac₃-Ac₁)+Ac₁ (°C) to Ac₃−30 (°C) min	Primary cooling rate/°C/s
A	1	1340	783	830	1.4	3
A	2	1340	783	830	1.4	3
A	3	1340	783	950	4.3	1
B	1	1241	782	820	2.9	0.5
B	2	1241	782	820	2.9	0.5
B	3	1241	782	1000	75	0.05
C	1	1064	772	820	2	1
C	2	1064	772	1070	498	0.01
D	1	1366	783	830	2	1

Table 4-1-2 (Continued): Production method and each property

					2	1
D	2	1366	783	830	2	1
E	1	836	741	800	1.8	8
E	1-1	836	741	800	1.8	8
E	1-2	836	741	800	1.8	8
E	1-3	836	741	800	1.8	8
E	1-4	836	741	800	1.8	8
E	1-5	836	741	800	1.8	8
E	2	836	741	850	184	0.01
F	1	1391	794	850	1.5	3
F	2	1391	794	850	1.5	3

Table 4-1-3 (Continued): Production method and each property

G	1	823	743	800	2.1	1
G	2	823	743	850	179	0.01
H	1	1382	775	830	2.5	1
I	1	1318	807	850	1.9	1
I	1-1	1318	807	850	1.9	1
I	1-2	1318	807	850	1.9	1
I	1-3	1318	807	850	1.9	1
I	1-4	1318	807	850	1.9	1
I	1-5	1318	807	850	1.9	1
I	2	1318	807	950	49	0.05

Table 4-1-4 (Continued): Production method and each property

Steel code	Primary cooling halt temperature/°C	Secondary cooling rate/°C/s	Retaining conditions including zinc plating treatment	Alloying temperature/°C
A	700	7	For 30 seconds at a temperature of 475 to 460°C	
A	680	10	For 30 seconds at a temperature of 475 to 460°C	510
A	750	1	For 30 seconds at a temperature of 475 to 460°C	550
B	680	5	For 30 seconds at a temperature of 465 to 460°C	510
B	680	5	For 30 seconds at a temperature of 465 to 460°C	
B	730	120	For 30 seconds at a temperature of 465 to 460°C	
C	680	10	For 15 seconds at a temperature of 475 to 460°C	510
C	810	1	For 15 seconds at a temperature of 475 to 460°C	510
D	700	5	For 40 seconds at a temperature of 475 to 460°C	515

Table 4-1-5 (Continued): Production method and each property

D	700	5	For 5 seconds at a temperature of 475 to 460°C	515
E	680	15	For 10 seconds at a temperature of 470 to 460°C	505
E	680	15	For 10 seconds at a temperature of 470 to 460°C	505
E	680	15	For 10 seconds at a temperature of 470 to 460°C	505
E	680	15	For 10 seconds at a temperature of 470 to 460°C	505
E	680	15	For 10 seconds at a temperature of 470 to 460°C	505
E	680	15	For 10 seconds at a temperature of 470 to 460°C	505
E	750	15	For 10 seconds at a temperature of 470 to 460°C	505
F	680	7	For 30 seconds at a temperature of 470 to 460°C	
F	680	7	For 30 seconds at a temperature of 470 to 460°C	500

Table 4-1-6 (Continued): Production method and each property

G	670	6	For 30 seconds at a temperature of 475 to 460°C	500
G	750	6	For 30 seconds at a temperature of 475 to 460°C	500
H	670	10	For 100 seconds at a temperature of 465 to 460°C	
I	700	10	For 30 seconds at a temperature of 475 to 460°C	520
I	700	10	For 30 seconds at a temperature of 475 to 460°C	520
I	700	10	For 30 seconds at a temperature of 475 to 460°C	520
I	700	10	For 30 seconds at a temperature of 475 to 460°C	520
I	700	10	For 30 seconds at a temperature of 475 to 460°C	520
I	700	10	For 30 seconds at a temperature of 475 to 460°C	520
I	780	10	For 30 seconds at a temperature of 475 to 460°C	

Table 4-1-7 (Continued): Production method and each property

Steel code	Depth of grain boundary oxidized layer/μm	Appearance after repeated salt spray test	Fatigue life under the stress corresponding to 50% of tensile strength/cycles	
A	0.05	Rust not formed	1.23E+06	Invented steel
A	0.07	Rust not formed	1.45E+06	Invented steel
A	0.85	Rust not formed	3.20E+05	Comparative steel
B	0.09	Rust not formed	1.01E+06	Invented steel
B	0.13	Rust not formed	1.17E+06	Invented steel
B	1.05	Rust not formed	1.59E+05	Comparative steel
C	0.15	Rust not formed	1.10E+06	Invented steel
C	0.56	Rust formed	3.60E+05	Comparative steel
D	0.11	Rust not formed	1.20E+06	Invented steel

Table 4-1-8 (Continued): Production method and each property

D	0.08	Rust not formed	1.07E+06	Invented steel
E	0.23	Rust not formed	1.90E+06	Invented steel
E	0.3	Rust not formed	1.10E+06	Invented steel
E	0.24	Rust not formed	1.50E+06	Invented steel
E	0.2	Rust not formed	1.40E+06	Invented steel
E	0.33	Rust not formed	1.10E+06	Invented steel
E	0.35	Rust not formed	1.20E+06	Invented steel
E	1.23	Rust formed	2.70E+05	Comparative steel
F	0.09	Rust not formed	2.01E+06	Invented steel
F	0.08	Rust not formed	1.70E+06	Invented steel

Table 4-1-9 (Continued): Production method and each property

G	0.07	Rust not formed	1.60E+06	Invented steel
G	<u>1.1</u>	Rust formed	1.65E+05	Comparative steel
H	0.05	Rust not formed	2.00E+06	Invented steel
I	0.42	Rust not formed	1.00E+06	Invented steel
I	0.3	Rust not formed	1.20E+06	Invented steel
I	0.35	Rust not formed	1.01E+06	Invented steel
I	0.3	Rust not formed	1.20E+06	Invented steel
I	0.28	Rust not formed	1.15E+06	Invented steel
I	0.25	Rust not formed	1.03E+06	Invented steel
I	<u>1.15</u>	Rust formed	4.90E+05	Comparative steel

(Note) The underlined numerals are the conditions which are outside the range according to the present invention.

(Example) "4.55E – 03" means 4.55×10^{-3}.

Table 4-2-1 (Continued): Production method and each property

Steel code	Treatment number	Ac$_3$ (calculated) -30 (°C)/°C	0.1×(Ac$_3$-Ac$_1$)+Ac$_1$ (calculated)/°C	Maximum temperature during annealing/°C	Resident time in the temperature range from 0.1×(Ac$_3$-Ac$_1$)+Ac$_1$ (°C) to Ac$_3$-30 (°C) min	Primary cooling rate/°C/s
J	1	1259	828	850	1.4	1
J	2	1259	828	850	1.4	1
J	3	1259	828	1000	59	0.05
K	1-1	997	763	850	3.2	1
K	1-2	997	763	850	3.2	1
K	1-3	997	763	850	3.2	1
K	2-1	997	763	850	3.2	1
K	2-2	997	763	850	3.2	1
K	2-3	997	763	850	3.2	1
L	1-1	1162	765	830	2.1	3
L	1-2	1162	765	830	2.1	3

Table 4-2-2 (Continued): Production method and each property

L	1-3	1162	765	830	2.1	3
L	1-4	1162	765	830	2.1	3
M	1	1150	756	830	1.5	5
N	1	1225	763	830	1.5	5
O	1	1208	760	830	1.5	5
P	1	984	750	830	1.5	5
Q	1	1067	770	830	1.5	5
CA	1	939	849	880	1.6	1
CB	1	909	740	850	3.2	1
CC	1	1176	818	900	8	0.2
CD	1	Many cracks occurred at hot-rolling				
CE	1	Many cracks occurred at cold-rolling				

Table 4-2-3 (Continued): Production method and each property

Steel code	Primary cooling halt temperature/°C	Secondary cooling rate/°C/s	Retaining conditions including zinc plating treatment	Alloying temperature/°C
J	680	10	For 30 seconds at a temperature of 475 to 460°C	
J	680	10	For 30 seconds at a temperature of 475 to 460°C	520
J	600	0.1	For 30 seconds at a temperature of 465 to 460°C	580
K	680	7	For 30 seconds at a temperature of 475 to 460°C	Not applied
K	680	7	For 30 seconds at a temperature of 475 to 460°C	Not applied
K	680	7	For 30 seconds at a temperature of 475 to 460°C	Not applied
K	680	7	For 30 seconds at a temperature of 475 to 460°C	505
K	680	7	For 30 seconds at a temperature of 475 to 460°C	505
K	680	7	For 30 seconds at a temperature of 475 to 460°C	505
L	680	10	For 30 seconds at a temperature of 465 to 460°C	500
L	680	10	For 30 seconds at a temperature of 465 to 460°C	500

Table 4-2-4 (Continued): Production method and each property

L	680	10	For 30 seconds at a temperature of 465 to 460°C	500
L	680	10	For 30 seconds at a temperature of 465 to 460°C	500
M	680	5	For 30 seconds at a temperature of 460 to 455°C	500
N	680	5	For 30 seconds at a temperature of 460 to 455°C	500
O	680	5	For 30 seconds at a temperature of 460 to 455°C	500
P	680	5	For 60 seconds at a temperature of 460 to 455°C	500
Q	680	5	For 90 seconds at a temperature of 460 to 455°C	500
CA	700	1	For 300 seconds at a temperature of 465 to 460°C	550
CB	700	30	For 5 seconds at a temperature of 475 to 460°C	550
CC	700	1	For 5 seconds at a temperature of 475 to 460°C	
CD				
CE				

— 54/4 —

Table 4-2-5 (Continued): Production method and each property

Steel code	Depth of grain boundary oxidized layer/μm	Appearance after repeated salt spray test	Fatigue life under the stress corresponding to 50% of tensile strength/cycles	
J	0.65	Rust not formed	1.40E+06	Invented steel
J	0.7	Rust not formed	1.33E+06	Invented steel
J	1.54	Rust formed	2.50E+05	Comparative steel
K	0.05	Rust not formed	1.38E+06	Invented steel
K	0.04	Rust not formed	1.22E+06	Invented steel
K	0.05	Rust not formed	1.10E+06	Invented steel
K	0.04	Rust not formed	1.40E+06	Invented steel
K	0.07	Rust not formed	1.13E+06	Invented steel
L	0.04	Rust not formed	1.36E+06	Invented steel
L	0.04	Rust not formed	1.07E+06	Invented steel
L	0.06	Rust not formed	1.10E+06	Invented steel
L	0.05	Rust not formed	1.07E+06	Invented steel
L	0.03	Rust not formed	1.37E+06	Invented steel

Table 4-2-6 (Continued): Production method and each property

M	0.03	Rust not formed	2.23E+06	Invented steel
N	0.02	Rust not formed	2.10E+06	Invented steel
O	0.08	Rust not formed	2.20E+06	Invented steel
P	0.25	Rust not formed	2.70E+06	Invented steel
Q	0.07	Rust not formed	2.10E+06	Invented steel
CA	1.26	Rust formed	9.45E+04	Comparative steel
CB	0.65	Rust not formed	7.50E+05	Comparative steel
CC	1.65	Rust formed	1.20E+05	Comparative steel
CD				Comparative steel
CE				Comparative steel

(Note) The underlined numerals are the conditions which are outside the range according to the present invention.

(Example) "4.55E – 03" means 4.55×10^{-3}.

Table 5-1 (Continued)

Steel code	Treatment number	Area percentage of oxide in the range from the interface between plated layer and steel sheet 10 μm depth in steel	Ratio of area percentages: $(MnO + Al_2O_3)/SiO_2$	Type of oxide existing in steel in the range from the interface between plated layer and steel sheet to 10 μm depth in steel
M	1	35	70	MnO, Al_2O_3, SiO_2
N	1	20	20	MnO, Al_2O_3, SiO_2
O	1	25	250	MnO, Al_2O_3, SiO_2, La_2O_3, Ce_2O_3
P	1	45	5	MnO, Al_2O_3, SiO_2, Y_2O_3
Q	1	15	50	MnO, Al_2O_3, SiO_2
CA	1	8	0.01	$MnSiO_3$, SiO_2

Table 5-2 (Continued)

Steel code	Appearance after repeated salt splay test	Fatigue life under the stress corresponding to 50% of tensile strength	
M	Rust not formed	2.23E+06	Invented steel
N	Rust not formed	2.10E+06	Invented steel
O	Rust not formed	2.20E+06	Invented steel
P	Rust not formed	2.70E+06	Invented steel
Q	Rust not formed	2.10E+06	Invented steel
CA	Rust formed	9.45E+04	Comparative steel

(Note) The underlined numerals are the conditions which are outside the range according to the present invention.

(Example) "2.23E + 6" means 2.23×10^6.

- 56 -

Example 2 of Embodiment 1

The present invention will hereunder be explained in detail based on Example 2 of Embodiment 1.

Steels having chemical compositions shown in Table 6 were heated to the temperature of 1,200°C; the hot-rolling of the steels was finished at a temperature of not less than the Ar_3 transformation temperature; and the hot-rolled steel sheets were cooled and then coiled at a temperature of not less than the bainite transformation commencement temperature which was determined by the chemical composition of each steel, pickled, and cold-rolled into cold-rolled steel sheets 1.0 mm in thickness.

After that, the Ac_1 transformation temperature and the Ac_3 transformation temperature were calculated from the components (in mass %) of each steel according to the following equations:

$Ac_1 = 723 - 10.7 \times Mn\% - 16.9 \times Ni\% + 29.1 \times Si\% + 16.9 \times Cr\%$,

$Ac_3 = 910 - 203 \times (C\%)^{1/2} + 15.2 \times Ni\% + 44.7 \times Si\% + 104 \times V\% + 31.5 \times Mo\% - 30 \times Mn\% - 11 \times Cr\% - 20 \times Cu\% + 700 \times P\% + 400 \times Al\% + 400 \times Ti\%$.

The steel sheets were plated by: heating them to the annealing temperature calculated from the Ac_1 transformation temperature and the Ac_3 transformation temperature and retaining them in the N_2 atmosphere containing 10% of H_2; thereafter, cooling them up to 680°C at a cooling rate of 0.1 to 10°C/sec.; successively cooling them to the plating bath temperature at a cooling rate of 1 to 20°C/sec.; and dipping them in the zinc plating bath at 460°C for 3 seconds, wherein the compositions of the plating bath were varied.

Further, as the Fe-Zn alloying treatment, some of the steel sheets were retained in the temperature range from 300 to 550°C for 15 seconds to 20 minutes after they were zinc plated and Fe contents in the plated layers were adjusted so as to be 5 to 20% in mass. The plating

properties were evaluated by visually observing the state
of dross entanglement on the surface and measuring the
area of non-plated portions. The compositions of the
plated layers were determined by dissolving the plated
layers in 5% hydrochloric acid solution containing an
inhibitor and chemically analyzing the solution.

JIS #5 specimens for tensile test were prepared from
the zinc plated steel sheets (rolled in the skin-pass
line at the reduction rate of 0.5 - 2.0%) and mechanical
properties thereof were measured. Then, the plating
adhesion after severe deformation was evaluated by
applying 60° bending and bending-back forming to a steel
sheet after giving the tensile strain of 20%. The
plating adhesiveness was evaluated relatively by sticking
a vinyl tape to the bent portion after bending and
bending-back forming and peeling it off, and then
measuring the rate of the exfoliated length per unit
length. The production conditions are shown in Table 8.

As shown in Table 7, in the case of the steels
according to the present invention, namely, D1 to D8
(Nos. 1, 2, 5 to 8, 10 to 14), non-plating defects are
not observed, the strength and the elongation are well
balanced, and the plating exfoliation rate is as low as
not more than 1% even when bending and bending-back
forming is applied after giving the tensile strain of
20%. On the other hand, in the case of the comparative
steels, namely, C1 to C5 (Nos. 17 to 21), cracks were
generated abundantly during the hot-rolling for producing
the test specimens and the producibility was poor. The
hot-rolled steel sheets were cold-rolled and annealed
after cracks were removed by grinding the hot-rolled
steel sheets obtained, and then used for the material
quality tests. However, some of the steel sheets (C2 and
C4) were very poor in plating adhesiveness after heavy
working or could not withstand the forming of 20%.

As shown in Table 8, in Nos. 3, 9, 19 and 21, which
do not satisfy the equation 1, the plating wettability

deteriorates and the plating adhesion after revere
deformation is inferior. Also, in the case that the
regulation on the microstructure of a steel sheet is not
satisfied, the plating adhesiveness after heavy working

5   is inferior.

In case of No. 4, since the secondary cooling rate
is slow, martensite and austenite are not generated but
pearlite is generated instead, and the plating
adhesiveness after heavy working is inferior.

Table 6-1 (Continued): Chemical composition, producibility and plating wettability

Steel code	C	Si	Mn	Al	Mo	Cr	Ni	Cu
D1	0.15	0.45	0.95	1.12				
D2	0.16	0.48	0.98	0.95	0.15			
D3	0.13	1.21	1.01	0.48	0.12			
D4	0.09	0.49	1.11	1.51	0.19			
D5	0.06	0.89	1.21	0.62	0.09	0.09		
D6	0.11	1.23	1.49	0.31			0.74	0.42
D7	0.22	1.31	1.09	0.75	0.23			
D8	0.07	0.91	1.56	0.03				
D9	0.05	0.91	1.68	0.03	0.55	1.65		
C1	0.42	0.32	2.81	4.56				
C2	0.27	1.22	1.97	0.03	6.52			
C3	0.05	7.41	0.6	0.05				8.54
C4	0.08	0.21	0.4	0.06				
C5	0.15	3.61	1.32	0.02				

Table 6-2 (Continued): Chemical composition, producibility and plating wettability

Steel code	Co	Nb	Ti	V	B	
D1						Invented steel
D2						
D3						
D4						
D5						
D6				0.005		
D7	0.08					
D8		0.01	0.01			
D9					0.0026	
C1						Comparative steel
C2						
C3						
C4		3.22				
C5					0.5	

The shaded numerals in the table are the conditions which are outside the range according to the present invention.

Table 7-1 (Continued): Content of Al, Mn and Fe in plated layer and plating property

Steel code	No	Al content in plated layer %	Mn content in plated layer %	Fe content in plated layer %**	Value calculated by expression (1)	Application of alloying treatment	Occurrence of non-plating defect on steel sheet before working	Mechanical property TS/MPa	EL/%
D1	1	0.1	0.8	10	10.1	Yes	No	575	39
D1	2	0.1	0.8		10.1	No	No	585	42
D1	3	0.18	0		0.17	No	Trivial	580	41
D1	4	0.1	0.8	11	10.1	Yes	No	530	31
D2	5	0.03	0.1	8	2.98	Yes	No	605	36
D2	6	0.03	0.1		2.98	No	No	615	37
D3	7	0.04	0.2	10	3.53	Yes	No	610	36
D3	8	0.04	0.2		3.53	No	No	620	36
D3	9	0.3	0	8	2.22	Yes	Frequent	615	36
D4	10	0.02	0.05	9	2.27	Yes	No	565	40
D5	11	1	1	15	1.78	Yes	No	635	33
D6	12	0.15	0.1	10	0.89	Yes	Trivial	680	33
D7	13	0.04	0.5	15	6.97	Yes	Trivial	810	32

Table 7-2 (Continued): Content of Al, Mn and Fe in plated layer and plating property

D7	14	0.04	0.5	15	6.97	No	Trivial	890	18
D8	15	0.4	0.8		6.24	No	Trivial	795	30
D9	16	0.5	0.8		5.7	No	Trivial	645	27
C1	17	0.4	0.8	10	5.81	Yes	Trivial	775	22
C2	18	0.04	0.5		7.23	No	Trivial	995	12
C3	19	0.01	0.01		4.48	No	Poor plating wettability		
C4	20	0.01	0.01	12	2.75	Yes	No	895	13
C5	21	0.01	0.01		0.76	Yes	Poor plating wettability		

Table 7-3 (Continued): Content of Al, Mn and Fe in plated layer and plating property

Steel code	No	Volume percentage of ferrite /%	Volume percentage of austenite/% ***	Volume percentage of martensite/% ***	Volume percentage of bainite /% ***	Microstructure Structure of remainder portion/% ***	Average grain size of ferrite /μm	Average grain size of austenite/μm	Average grain size of martensite/μm	Ratio of average grain size of ferrite to that of second phase
D1	1	91.6	4.9	0	3.5	***	12.5	2.2		0.176
D1	2	90.8	5.3	0	3.9	***	12.2	2.5		0.205
D1	3	91.2	5.1	0	3.7	***	11.8	2.3		0.195
D1	4	85	0	0	0	Pearlite 15%	13.5			
D2	5	90.5	5.6	0	3.9	***	10.1	2.3		0.228
D2	6	89.5	6.2	0	4.3	***	10.2	2.5		0.245
D3	7	89.8	6.4	0	3.8	***	8.9	2.6		0.292
D3	8	88.8	6.7	0	4.5	***	8.7	2.7		0.310
D3	9	89.5	6.4	0	4.1	***	8.5	2.6		0.306
D4	10	93.7	3.5	0	2.8	***	11.5	2.3		0.200
D5	11	88.8	0	8.1	3.1	***	7.5			0.453
D6	12	85.4	8.1	0	6.5	***	5.3	1.9	3.4	0.358
D7	13	82.5	9.7	0	7.8	***	4.6	1.8		0.391

WO 02/101112 PCT/JP02/05627

− 60/3 −

Table 7-4 (Continued): Content of Al, Mn and Fe in plated layer and plating property

D7	14	Main phase is composed of the mixture of ferrite and bainite.*									
D8	15	83.5	0	11.2	5.3	***	3.9			2	0.513
D9	16	89.5	0	10.5	0	***	3.5			1.8	0.514
C1	17	77	0	0	23	***	3.4				
C2	18	Main phase is composed of the mixture of ferrite and bainite.*									
C3	19										
C4	20	Main phase is composed of the mixture of ferrite and bainite.*									
C5	21										

SUBSTITUTE SHEET (RULE 26)

Table 7-5 (Continued): Content of Al, Mn and Fe in plated layer and plating property

Steel code	No	Exfoliation rate of plated layer after giving 20% tensile strain and then applying 60° bending and bending-back forming/%	
D1	1	0	Invented steel
D1	2	0.1	Invented steel
D1	3	12	Comparative steel
D1	4	4	Comparative steel
D2	5	0	Invented steel
D2	6	0.1	Invented steel
D3	7	0	Invented steel
D3	8	0.2	Invented steel
D3	9	46	Comparative steel
D4	10	0	Invented steel
D5	11	0.3	Invented steel
D6	12	0.5	Invented steel
D7	13	0.4	Invented steel
D7	14		Comparative steel

Table 7-6 (Continued): Content of Al, Mn and Fe in plated layer and plating property

D8	15	0.5	Invented steel
D9	16	0.7	Invented steel
C1	17	75	Comparative steel
C2	18		Comparative steel
C3	19		Comparative steel
C4	20		Comparative steel
C5	21		Comparative steel

The shaded numerals in the table are the conditions which are outside the range according to the present invention.

* Main phase is composed of the mixture of ferrite and bainite and it is difficult to quantitatively identify them. Further, the rupture elongation is not more than 20%, which means low ductility, and therefore it is impossible to evaluate the plating adhesiveness after heavy working.

** In case that an alloying treatment is not applied, Fe is scarcely included in the plated layer.

*** The sum of the volume percentage of each phase is 100%, and the phases which are hardly observed and identified by an optical microscope, such as carbides, oxides, sulfides, etc., are included in the volume percentage of the main phase.

Table 8-1 (Continued): Production condition and plating adhesiveness after heavy working

Steel code	No	Annealing condition: °C × min.	Primary cooling rate: °C/s	Primary cooling halt temperature: °C	Secondary cooling rate: °C/s
D1	1	800°C × 3 min.	1	680	10
D1	2	800°C × 3 min.	1	680	10
D1	3	800°C × 3 min.	1	680	0.5
D1	4	800°C × 3 min.	1	680	10
D2	5	800°C × 3 min.	1	680	10
D2	6	800°C × 3 min.	1	680	10
D3	7	810°C × 3 min.	1	680	5
D3	8	810°C × 3 min.	1	680	5
D3	9	830°C × 3 min.	1	680	5
D4	10	830°C × 3 min.	0.5	680	3
D5	11	830°C × 3 min.	0.5	680	7
D6	12	800°C × 3 min.	0.3	650	8
D7	13	800°C × 3 min.	1	680	10
D7	14	1200°C × 0.5 min.	70	680	70
D8	15	860°C × 3 min.	1	680	10
D9	16	860°C × 3 min.	0.5	650	3
C1	17	850°C × 3 min.	5	680	30
C2	18	850°C × 3 min.	1	690	10
C3	19	1000°C × 3 min.	5	680	10
C4	20	850°C × 3 min.	5	680	30
C5	21	950°C × 3 min.	1	680	30

Table 8-2 (Continued): Production condition and plating adhesiveness after heavy working

Steel code	No	Secondary cooling halt temperature: °C	Retaining conditions including zinc plating treatment	Alloying processing temperature: °C
D1	1	465	For 18 seconds at a temperature of 465 to 460°C	515
D1	2	465	For 23 seconds at a temperature of 465 to 460°C	No
D1	3	465	For 23 seconds at a temperature of 465 to 460°C	No
D1	4	465	For 18 seconds at a temperature of 465 to 460°C	600
D2	5	470	For 15 seconds at a temperature of 465 to 460°C	520
D2	6	470	For 25 seconds at a temperature of 470 to 460°C	No
D3	7	470	For 18 seconds at a temperature of 470 to 460°C	510
D3	8	470	For 33 seconds at a temperature of 470 to 460°C	No
D3	9	470	For 25 seconds at a temperature of 470 to 460°C	510
D4	10	475	For 20 seconds at a temperature of 475 to 460°C	515
D5	11	475	For 5 seconds at a temperature of 475 to 460°C	520
D6	12	480	For 20 seconds at a temperature of 480 to 460°C	520
D7	13	470	For 25 seconds at a temperature of 470 to 460°C	520
D7	14	470	For 25 seconds at a temperature of 470 to 460°C	No
D8	15	480	For 5 seconds at a temperature of 480 to 460°C	No
D9	16	480	For 5 seconds at a temperature of 470 to 460°C	No
C1	17	470	For 15 seconds at a temperature of 470 to 460°C	510
C2	18	470	For 5 seconds at a temperature of 470 to 460°C	No
C3	19	470	For 15 seconds at a temperature of 470 to 460°C	No
C4	20	470	For 15 seconds at a temperature of 470 to 460°C	510
C5	21	470	For 15 seconds at a temperature of 470 to 460°C	510

Table 8-3 (Continued): Production condition and plating adhesiveness after heavy working

Steel code	No	Alloying processing time:	Exfoliation rate of plated layer after giving 20% tensile strain and then applying 60° bending and bending-back forming	
D1	1	25	0	Invented steel
D1	2	No	0.1	Invented steel
D1	3	No	12	Comparative steel
D1	4	25	4	Comparative steel
D2	5	25	0	Invented steel
D2	6	No	0.1	Invented steel
D3	7	25	0	Invented steel
D3	8	No	0.2	Invented steel
D3	9	25	46	Comparative steel
D4	10	25	0	Invented steel
D5	11	25	0.3	Invented steel
D6	12	25	0.5	Invented steel
D7	13	25	0.4	Invented steel
D7	14	No	Unbearable to 20% tensile stress	Comparative steel
D8	15	No	0.5	Invented steel
D9	16	No	0.7	Invented steel
C1	17	25	Unbearable to 20% tensile stress	Comparative steel
C2	18	No	Unbearable to 20% tensile stress	Comparative steel
C3	19	No	Non-plating defects generated prior to tensile test	Comparative steel
C4	20	25	Unbearable to 20% tensile stress	Comparative steel
C5	21	25	Non-plating defects generated prior to tensile test	Comparative steel

The shaded portions in the table are the conditions which are outside the range according to the present invention. (refer to Table 7 with regard to Nos. 9 and 17 to 21)

Primary cooling rage: cooling rate in the temperature range from after annealing up to 650 to 700°C

Secondary cooling rate: cooling rate in the temperature range from 650 to 700°C to plating bath

- 62 -

Example 3 of Embodiment 1

The present invention will hereunder be explained in detail based on Example 3 of Embodiment 1.

Steels having chemical compositions shown in Table 9 were heated to the temperature of 1,200°C; the hot-rolling of the steels was finished at a temperature of not less than the Ar_3 transformation temperature; and the hot-rolled steel sheets were cooled and then coiled at a temperature of not less than the bainite transformation commencement temperature which was determined by the chemical composition of each steel, pickled, and cold-rolled into cold-rolled steel sheets 1.0 mm in thickness.

After that, the Ac_1 transformation temperature and the Ac_3 transformation temperature were calculated from the components (in mass %) of each steel according to the following equations:

$$Ac_1 = 723 - 10.7 \times Mn\% + 29.1 \times Si\%,$$

$$Ac_3 = 910 - 203 \times (C\%)^{1/2} + 44.7 \times Si\% + 31.5 \times Mo\% - 30 \times Mn\% - 11 \times Cr\% + 400 \times Al\%.$$

The steel sheets were plated by: heating them to the annealing temperature calculated from the Ac_1 transformation temperature and the Ac_3 transformation temperature and retaining them in the N_2 atmosphere containing 10% of H_2; thereafter, cooling them up to 680°C at a cooling rate of 0.1 to 10°C/sec.; successively cooling them to the plating bath temperature at a cooling rate of 1 to 20°C/sec.; and dipping them in the zinc plating bath of 460°C for 3 seconds, wherein the compositions of the plating bath were varied.

Further, as the Fe-Zn alloying treatment, some of the steel sheets were retained in the temperature range from 300 to 550°C for 15 seconds to 20 minutes after they were zinc plated and Fe contents in the plated layers were adjusted so as to be 5 to 20% in mass. The plating properties were evaluated by visually observing the state of dross entanglement on the surface and measuring the

area of non-plated portions. The compositions of the
plated layers were determined by dissolving the plated
layers in 5% hydrochloric acid solution containing an
inhibitor and chemically analyzing the solution.

5   JIS #5 specimens for tensile test were prepared from
the zinc plated steel sheets (rolled in the skin-pass
line at the reduction rate of 0.5 - 2.0%) and mechanical
properties thereof were measured. Then, the plating
adhesion after severe deformation was evaluated by

10   applying 60° bending and bending-back forming to a steel
sheet after giving the tensile strain of 20%. The
plating adhesiveness was evaluated relatively by sticking
a vinyl tape to the bent portion after bending and
bending-back forming and peeling it off, and then

15   measuring the rate of the exfoliated length per unit
length. The production conditions are shown in Table 11.
       As shown in Table 10, in the case of the steels
according to the present invention, namely, D1 to D12
(Nos. 1, 2, 5, 12, 13, 20, 22 to 24, 32, 34 to 36, 39 and

20   42), non-plating defects are not observed, the strength
and the elongation are well balanced, and the plating
exfoliation rate is as low as not more than 1% even when
bending and bending-back forming is applied after giving
the tensile strain of 20%. Further, it is understood

25   that, when the other elements in plated layer as shown in
Table 10 are contained in a plated layer, the plating
properties are good even in the case where the value
determined by left side of the equation 1 is relatively
small.

30   On the other hand, in the case of the comparative
steels, namely, C1 to C5 (Nos. 44 to 48), cracks were
generated abundantly during the hot-rolling for producing
the test specimens and the producibility was poor. The
hot-rolled steel sheets were cold-rolled and annealed

35   after cracks were removed by grinding the hot-rolled
steel sheets obtained, and then used for the material
quality tests. However, some of the steel sheets (C2 and

C4) were very poor in plating adhesiveness after heavy working or could not withstand the forming of 20%.

As shown in Table 10, in Nos. 3, 21, 46 and 48, which do not satisfy the equation 1, the plating wettability deteriorates and the plating adhesiveness after heavy working is inferior. Also, in the case that the regulation on the microstructure of a steel sheet is not satisfied, the plating adhesion after revere deformation is inferior.

In case of No. 3, as the secondary cooling rate is slow, martensite and austenite are not generated but pearlite is generated instead, and the plating adhesion after severe deformation is inferior.

Table 9-1 (Continued): Chemical composition, producibility and plating wettability

Steel code	C	Si	Mn	Al	Mo	Cr	Ni	Cu	Co	Nb	Ti	V	B
D1	0.15	0.45	0.95	1.12									
D2	0.16	0.48	0.98	0.95	0.15								
D3	0.13	1.21	1.01	0.48	0.12								
D4	0.03	0.49	1.11	1.51	0.19								
D5	0.03	0.69	1.21	0.62	0.09	0.09							
D6	0.11	1.23	1.49	0.31			0.74	0.42				0.005	
D7	0.22	1.31	1.09	0.75	0.23				0.08				
D8	0.07	0.91	1.56	0.03						0.01	0.01		
D9	0.05	0.91	1.68	0.03	0.55	1.65							0.0026
D10	0.18	0.11	1.1	0.67	0.08								
D11	0.17	0.21	0.9	1.2	0.38	0.1							
D12	0.21	0.11	1.05	0.78									
C1	0.12	0.32	2.81	4.56									
C2	0.27	1.22	1.97	0.03	6.52								
C3	0.05	7.41	0.6	0.03				0.54					
C4	0.08	0.21	0.4	0.05						3.22			
C5	0.15	3.61	1.32	0.02									0.5

Table 9-2 (Continued): Chemical composition, producibility and plating wettability

Steel code	Zr	Hf	Ta	W	P	S	Y	REM	
D1					0.02	0.005			Invented steel
D2					0.01	0.008			
D3					0.01	0.007			
D4					0.02	0.001			
D5					0.03	0.004			
D6					0.01	0.003			
D7					0.01	0.004			
D8					0.02	0.004			
D9					0.01	0.002			
D10	0.01			0.05	0.02	0.03		0.0007	
D11		0.01	0.02		0.03	0.02			
D12				0.025	0.01	0.03	0.009		
C1									Comparative steel
C2									
C3									
C4									
C5									

The underlined numerals in the table are the conditions which are outside the range according to the present invention.

Table 10-1-1 (Continued): Content of Al, Mn and Fe in plated layer and plating property

Steel code	No	Al content in plated layer %	Mn content in plated layer %	Fe content in plated layer % **	Value calculated by expression (1)	Other elements in plated layer	Application of alloying treatment	Occurrence of non-plating defect on steel sheet before working	TS/MPa	EL/%
D1	1	0.1	0.8	10	10.1		Yes	No	575	39
D1	2	0.1	0.8		10.1		No	No	585	42
D1	3	0.18	0		0.17		No	Trivial	580	41
D1	4	0.1	0.8	11	10.1		Yes	No	530	31
D2	5	0.03	0.1	8	2.98		Yes	No	605	36
D2	6	0.04	0.02	10	1.855	Mo: 0.01	Yes	No	605	36
D2	7	0.04	0.01	9	1.73	Ca: 0.9, Mg: 0.005	Yes	No	605	36
D2	8	0.04	0.01	9	1.73	Ag: 0.5, Ni: 0.1	Yes	No	605	36
D2	9	0.03	0.01	9	1.855	Na 0.01, Ca: 0.01	Yes	No	605	36

Table 10-1-2 (Continued): Content of Al, Mn and Fe in plated layer and plating property

D2	10	0.04	0.01	9	1.73	Pb: 0.4	Yes	No	605	35
D2	11	0.03	0.05	8	2.355	Ta: 0.02	Yes	No	605	36
D2	12	0.03	0.1		2.98		No	No	615	37
D3	13	0.01	0.2	10	3.53		Yes	No	610	36
D3	14	0.3	0.4	8	2.779	Si: 0.01	Yes	No	610	36
D3	15	0.3	0.2	10	0.279	Ti: 0.08	Yes	Trivial	610	36
D3	16	0.1	0.2	9	2.779	Nd: 0.04	Yes	No	610	36
D3	17	0.15	0.2	9	2.154	Ba: 0.01	Yes	No	610	36
D3	18	0.2	0.2	10	1.529	In: 0.7	Yes	No	610	36
D3	19	0.4	0.3	10	0.279	K: 0.04	Yes	No	610	36
D3	20	0.04	0.2		3.53		No	No	620	36
D3	21	0.3	0	8	2.22		Yes	Frequent	615	36

Table 10-1-3 (Continued): Content of Al, Mn and Fe in plated layer and plating property

D4	22	0.02	0.05	9	2.27		Yes	No	665	40
D6	23	1	1	15	1.78		Yes	No	635	33
D8	24	0.15	0.1	10	0.89		Yes	Trivial	680	33
D8	25	0.15	0.2	10	2.143	Ca: 0.07	Yes	No	680	33
D8	26	0.15	0.25	10	2.788	Rb: 0.01	Yes	No	680	33
D8	27	0.2	0.1	10	0.288	Cd: 0.01	Yes	Trivial	680	33
D8	28	0.2	0.1	10	0.288	Cr: 0.03	Yes	Trivial	680	33
D8	29	0.65	0.05	10	0.288	Cu: 0.5, Ni: 0.2	Yes	No	680	33
D8	30	0.25	0.16	9	0.288	Ti: 0.05	Yes	No	680	33

Table 10-1-4 (Continued): Content of Al, Mn and Fe in plated layer and plating property

Steel code	No	Microstructure								Ratio of average grain size of ferrite to that of second phase
		Volume percentage of ferrite/%	Volume percentage of austenite/% ***	Volume percentage of martensite/% ***	Volume percentage of bainite/% ***	Structure of remainder portion/% ***	Average grain size of ferrite/μm	Average grain size of austenite/μm	Average grain size of martensite/μm	
D1	1	91.6	4.9	0	3.5	***	12.5	2.2		0.176
D1	2	90.8	6.3	0	3.9	***	12.2	2.5		0.205
D1	3	91.2	5.1	0	3.7	***	11.8	2.3		0.195
D1	4	85	0	0	0	Pearlite 15%	13.5			
D2	5	90.5	5.8	0	3.9	***	10.1	2.3		0.228
D2	6	90.5	5.6	0	3.9	***	10.1	2.5		0.228
D2	7	90.5	5.6	0	3.9	***	10.1	2.3		0.228
D2	8	90.5	5.6	0	3.9	***	10.1	2.3		0.228
D2	9	90.5	5.6	0	3.8	***	10.1	2.3		0.228

Table 10-1-5 (Continued): Content of Al, Mn and Fe in plated layer and plating property

D2	10	90.5	5.6	0	3.9	***	10.1	2.3		0.228
D2	11	90.5	5.6	0	3.9	***	10.1	2.3		0.228
D2	12	89.5	6.2	0	4.3	***	10.2	2.5		0.245
D3	13	89.8	6.4	0	3.8	***	8.9	2.6		0.292
D3	14	89.8	6.4	0	3.8	***	8.9	2.6		0.292
D3	15	89.8	6.4	0	3.8	***	8.9	2.6		0.292
D3	16	89.8	6.4	0	3.8	***	8.9	2.6		0.292
D3	17	89.8	6.4	0	3.8	***	8.9	2.6		0.292
D3	18	89.6	6.4	0	3.8	***	8.9	2.6		0.292
D3	19	89.8	6.4	0	3.8	***	8.9	2.6		0.292
D3	20	88.8	5.7	0	4.5	***	9.7	2.7		0.310
D3	21	89.5	6.4	0	4.1	***	8.5	2.8		0.306
D4	22	93.7	3.5	0	2.8	***	11.5	2.3		0.200

Table 10-1-6 (Continued): Content of Al, Mn and Fe in plated layer and plating property

	No.							3.		3.4		
D6	23	88.8	0	6.1	3.1		7.5			3.4		0.453
D8	24	85.4	8.1	0	6.5	***	5.3				1.9	0.358
D8	25	85.4	8.1	0	6.5	***	5.3				1.9	0.358
D8	26	85.4	8.1	0	6.5	***	6.3				1.9	0.358
D8	27	85.4	8.1	0	6.5	***	5.3				1.9	0.358
D8	28	85.4	8.1	0	6.5	***	6.3				1.9	0.358
D8	29	85.4	8.1	0	6.5	***	5.3				1.9	0.358
D8	30	85.4	8.1	0	6.5	***	6.3				1.9	0.358

Table 10-1-7 (Continued): Content of Al, Mn and Fe in plated layer and plating property

Steel code	No	Exfoliation rate of plated layer after giving 20% tensile strain and then applying 60° bending and bending-back forming/%	
D1	1	0	Invented steel
D1	2	0.1	Invented steel
D1	3	12	Comparative steel
D1	4	4	Comparative steel
D2	5	0	Invented steel
D2	6	0	Invented steel
D2	7	0	Invented steel
D2	8	0	Invented steel
D2	9	0	Invented steel

Table 10-1-8 (Continued): Content of Al, Mn and Fe in plated layer and plating property

D2	10	0	Invented steel
D2	11	0	Invented steel
D2	12	0.1	Invented steel
D3	13	0	Invented steel
D3	14	0	Invented steel
D3	15	0.1	Invented steel
D3	16	0	Invented steel
D3	17	0	Invented steel
D3	18	0	Invented steel
D3	19	0	Invented steel
D3	20	0.2	Invented steel

Table 10-1-9 (Continued): Content of Al, Mn and Fe in plated layer and plating property

		46	
D3	21		Comparative steel
D4	22	0	Invented steel
D6	23	0.3	Invented steel
D8	24	0.5	Invented steel
D8	25	0	Invented steel
D8	26	0	Invented steel
D8	27	0.1	Invented steel
D8	28	0.1	Invented steel
D8	29	0	Invented steel
D8	30	0	Invented steel

The underlined numerals in the table are the conditions which are outside the range according to the present invention.

* Main phase is composed of the mixture of ferrite and bainite and it is difficult to quantitatively identify them. Further, the rupture elongation is not more than 20%, which means low ductility, and therefore it is impossible to evaluate the plating adhesiveness after heavy working.

** In case that an alloying treatment is not applied, Fe is scarcely included in the plated layer.

*** The sum of the volume percentage of each phase is 100%, and the phases which are hardly observed and identified by an optical microscope, such as carbides, oxides, sulfides, etc., are included in the volume percentage of the main phase.

Table 10-2-1 (Continued)

Steel code	No	Al content in plated layer %	Mn content in plated layer %	Fe content in plated layer %**	Value calculated by expression (1)	Other elements in plated layer	Application of alloying treatment	Occurrence of non-plating defect on steel sheet before working	Mechanical property TS/MPa	Mechanical property EL/%
D6	31	0.1	0.1	10	1.518	V: 0.05	Yes	No	880	33
D7	32	0.04	0.5	15	6.97		Yes	Trivial	810	32
D7	33	0.04	0.5	15	6.97		No	Trivial	890	18
D8	34	0.4	0.8		6.24		No	Trivial	795	30
D9	35	0.5	0.8		5.7		No	Trivial	845	27
D10	36	0.5	0.7	11	4.99	La: 0.005	Yes	No	620	33
D10	37	0.5	0.4	10	1.24	Zr: 0.01, W: 0.01	Yes	Trivial	620	33
D10	38	0.4	0.25	9	0.615	K: 0.04	Yes	No	620	33
D11	39	0.3	0.2		1.05	Hf: 0.01	No	No	670	31
D11	40	0.3	0.15		0.425	Mo: 0.01, Ta: 0.02	No	No	670	31

Table 10-2-2 (Continued)

D11	41	0.25	0.1		0.425	Co: 0.2, B: 0.005	No	Trivial	670	31
D12	42	0.05	0.02	11	2.167	Y: 0.01	Yes	No	620	37
D12	43	0.1	0.01	11	1.417	Mo: 0.02, K: 0.02	Yes	No	620	37
C1	44	0.4	0.8	10	5.81		Yes	Trivial	775	22
C2	45	0.04	0.5		7.23		No	Trivial	995	12
C3	46	0.01	0.01		4.46		No	Poor plating wettability		
C4	47	0.01	0.01	12	2.75		Yes	No	895	13
C5	48	0.01	0.01		0.75		Yes	Poor plating wettability		

Table 10-2-3 (Continued)

Steel code	No	Microstructure								
		Volume percentage of ferrite/%	Volume percentage of austenite/% ***	Volume percentage of martensite/% ***	Volume percentage of bainite/% ***	Structure of remainder portion/% ***	Average grain size of ferrite /μm	Average grain size of austenite/μm	Average grain size of martensite/μm	Ratio of average grain size of ferrite to that of second phase
D6	31	85.4	8.1	0	6.5	***	6.3	1.9		0.358
D7	32	82.5	9.7	0	7.8	***	4.6	1.8		0.391
D7	33	Main phase is composed of the mixture of ferrite and bainite.*								
D8	34	83.5	0	11.2	5.3	***	3.9		2	0.513
D9	35	89.5	0	10.5	0	***	3.5		1.8	0.514
D10	36	92.5	4	0	3.5	***	11	2.8		0.255
D10	37	92.5	4	0	3.5	***	11	2.8		0.255
D10	38	92.5	4	0	3.5	***	11	2.8		0.255
D11	39	89.3	0	9.2	1.5		7		2.2	0.314
D11	40	89.3	0	9.2	1.5		7		2.2	0.314

Table 10-2-4 (Continued)

D11	41	89.3	0	9.2	1.5	7		2.2	0.314
D12	42	88.5	7.5	0	4	8.5	2.5		0.294
D12	43	88.5	7.5	0	4	8.5	2.5		0.294
C1	44	77	0	0	23	3.4			
C2	45	Main phase is composed of the mixture of ferrite and bainite.* ***							
C3	46								
C4	47	Main phase is composed of the mixture of ferrite and bainite.*							
C5	48								

Table 10-2-5 (Continued)

Steel code	No	Exfoliation rate of plated layer after giving 20% tensile strain and then applying 60° bending and bending-back forming/%	
D6	31	0	Invented steel
D7	32	0.4	Invented steel
D7	33		Comparative steel
D8	34	0.5	Invented steel
D9	35	0.7	Invented steel
D10	36	0	Invented steel
D10	37	0	Invented steel

Table 10-2-6 (Continued)

D10	38	0	Invented steel
D11	39	0	Invented steel
D11	40	0	Invented steel
D11	41	0.1	Invented steel
D12	42	0	Invented steel
D12	43	0	Invented steel
C1	44	75	Comparative steel
C2	45		Comparative steel
C3	46		Comparative steel
C4	47		Comparative steel
C5	48		Comparative steel

The underlined numerals in the table are the conditions which are outside the range according to the present invention.

*   Main phase is composed of the mixture of ferrite and bainite and it is difficult to quantitatively identify them. Further, the rupture elongation is not more than 20%, which means low ductility, and therefore it is impossible to evaluate the plating adhesiveness after heavy working.

**   In case that an alloying treatment is not applied, Fe is scarcely included in the plated layer.

*** The sum of the volume percentage of each phase is 100%, and the phases which are hardly observed and identified by an optical microscope, such as carbides, oxides, sulfides, etc., are included in the volume percentage of the main phase.

Table 11-1 (Continued): Production condition and plating adhesiveness after heavy working

Steel code	No	Annealing condition: °C × min.	Primary cooling rate: °C/s	Primary cooling halt temperature: °C	Secondary cooling rate: °C/s	Secondary cooling halt temperature: °C
D1	1	800°C × 3 min.	1	680	10	465
D1	2	800°C × 3 min.	1	680	10	465
D1	3	800°C × 3 min.	1	680	0.5	465
D1	4	800°C × 3 min.	1	680	10	465
D2	5	800°C × 3 min.	1	680	10	470
D2	12	800°C × 3 min.	1	680	10	470
D3	13	810°C × 3 min.	1	680	5	470
D3	20	810°C × 3 min.	1	680	5	470

Table 11-2 (Continued): Production condition and plating adhesiveness after heavy working

D3	21	810°C × 3 min.	1	680	5	470
D4	22	830°C × 3 min.	0.5	680	3	475
D5	23	830°C × 3 min.	0.5	680	7	475
D6	24	830°C × 3 min.	0.3	650	8	480
D7	32	800°C × 3 min.	1	680	10	470
D7	33	1200°C × 0.5 min.	70	680	70	470
D8	34	860°C × 3 min.	1	680	10	480
D9	35	860°C × 3 min.	0.5	650	3	480
D10	36	840°C × 3 min.	1	680	10	460

Table 11-3 (Continued): Production condition and plating adhesiveness after heavy working

D11	39	850°C × 3 min.	1	680	30	460
D12	42	830°C × 3 min.	1	680	10	460
C1	44	850°C × 3 min.	5	680	30	470
C2	45	850°C × 3 min.	1	690	10	470
C3	46	1000°C × 3 min.	5	680	10	470
C4	47	850°C × 3 min.	5	680	30	470
C5	48	950°C × 3 min.	1	680	30	470

Table 11-4 (Continued): Production condition and plating adhesiveness after heavy working

Steel code	No	Retaining conditions including zinc plating treatment	Alloying processing temperature: °C	Alloying processing time:
D1	1	For 18 seconds at a temperature of 465 to 460°C	515	25
D1	2	For 23 seconds at a temperature of 465 to 460°C	No	No
D1	3	For 23 seconds at a temperature of 465 to 460°C	No	No
D1	4	For 18 seconds at a temperature of 465 to 460°C	600	25
D2	5	For 15 seconds at a temperature of 470 to 460°C	520	25
D2	12	For 25 seconds at a temperature of 470 to 460°C	No	No
D3	13	For 18 seconds at a temperature of 470 to 460°C	510	25
D3	20	For 33 seconds at a temperature of 470 to 460°C	No	No

Table 11-5 (Continued): Production condition and plating adhesiveness after heavy working

D3	21	For 25 seconds at a temperature of 470 to 460°C	510	25
D4	22	For 20 seconds at a temperature of 475 to 460°C	515	25
D5	23	For 5 seconds at a temperature of 475 to 460°C	520	25
D6	24	For 20 seconds at a temperature of 480 to 460°C	520	25
D7	32	For 25 seconds at a temperature of 470 to 460°C	520	25
D7	33	For 25 seconds at a temperature of 470 to 460°C	No	No
D8	34	For 5 seconds at a temperature of 480 to 460°C	No	No
D9	35	For 5 seconds at a temperature of 480 to 460°C	No	No
D10	36	For 20 seconds at the temperature of 460°C	510	25

Table 11-6 (Continued): Production condition and plating adhesiveness after heavy working

D11	39	For 5 seconds at the temperature of 460°C	No	No
D12	42	For 20 seconds at the temperature of 460°C	510	25
C1	44	For 15 seconds at a temperature of 470 to 460°C	510	25
C2	45	For 5 seconds at a temperature of 470 to 460°C	No	No
C3	46	For 15 seconds at a temperature of 470 to 460°C	No	No
C4	47	For 15 seconds at a temperature of 470 to 460°C	510	25
C5	48	For 15 seconds at a temperature of 470 to 460°C	510	25

Table 11-7 (Continued): Production condition and plating adhesiveness after heavy working

Steel code	No	Exfoliation rate of plated layer after giving 20% tensile strain and then applying 60° bending and bending-back forming	
D1	1	0	Invented steel
D1	2	0.1	Invented steel
D1	3	12	Comparative steel
D1	4	4	Comparative steel
D2	5	0	Invented steel
D2	12	0.1	Invented steel
D3	13	0 - 0.1	Invented steel
D3	20	0.2	Invented steel

Table 11-8 (Continued): Production condition and plating adhesiveness after heavy working

D3	21	46	Comparative steel
D4	22	0	Invented steel
D5	23	0.3	Invented steel
D6	24	0 – 0.5	Invented steel
D7	32	0.4	Invented steel
D7	33	Unbearable to 20% tensile stress	Comparative steel
D8	34	0.5	Invented steel
D9	35	0.7	Invented steel

Table 11-9 (Continued): Production condition and plating adhesiveness after heavy working

D10	36	0	Invented steel
D11	39	0	Invented steel
D12	42	0 - 0.1	Invented steel
C1	44	Unbearable to 20% tensile stress	Comparative steel
C2	45	Unbearable to 20% tensile stress	Comparative steel
C3	46	Non-plating defects generated prior to tensile test	Comparative steel
C4	47	Unbearable to 20% tensile stress	Comparative steel
C5	48	Non-plating defects generated prior to tensile test	Comparative steel

The underlined numerals in the table are the conditions which are outside the range according to the present invention.
Primary cooling rate: cooling rate in the temperature range from after annealing up to 650 to 700°C

Secondary cooling rate: cooling rate in the temperature range from 650 to 700°C to plating bath temperature to plating bath temperature +100°C.

Example of Embodiment 2

        The present invention will hereunder be explained in
detail based on Example of Embodiment 2.

        Steels having chemical compositions shown in Table

5   12 were heated to the temperature of 1,180 to 1,250°C;
the hot-rolling of the steels was finished at a
temperature of 880 to 1,100°C; and the hot-rolled steel
sheets were cooled and then coiled at a temperature of
not less than the bainite transformation commencement

10   temperature which was determined by the chemical
composition of each steel, pickled, and cold-rolled into
cold-rolled steel sheets 1.0 mm in thickness.

        After that, the Ac_1 transformation temperature and
the Ac_3 transformation temperature were calculated from

15   the components (in mass %) of each steel according to the
following equations:

        $Ac_1 = 723 - 10.7 \times Mn\% + 29.1 \times Si\%$,

        $Ac_3 = 910 - 203 \times (C\%)^{1/2} + 44.7 \times Si\% + 31.5 \times Mo\% -$
$30 \times Mn\% - 11 \times Cr\% + 400 \times Al\%$.

20

        The steel sheets were plated by: heating them to the
annealing temperature calculated from the Ac_1
transformation temperature and the Ac_3 transformation
temperature and retaining them in the N_2 atmosphere

25   containing 10% of H_2; thereafter, cooing them in the
temperature range from 650 to 700°C at a cooling rate of
0.1 to 10°C/sec.; successively cooling them to the
plating bath temperature at a cooling rate of 0.1 to
20°C/sec.; and dipping them in the zinc plating bath of

30   460 to 470°C for 3 seconds, wherein the compositions of
the plating bath were varied, rolled in the skin-pass
line at the reduction rate of 0.5 - 2.0%.

        Further, as the Fe-Zn alloying treatment, some of
the steel sheets were retained in the temperature range

35   from 400 to 550°C for 15 seconds to 20 minutes after they
were plated and Fe contents in the plated layers were
adjusted so as to be 5 to 20% in mass. The plating

appearance was evaluated by visually observing the state of dross entanglement on the surface and measuring the area of non-plated portions. The compositions of the plated layers were determined by dissolving the plated layers in 5% hydrochloric acid solution containing an inhibitor and chemically analyzing the solution, and the results are shown in Table 13.

From Tables 13 and 14, in the steels according to the present invention, which satisfy the expression (2), the all appearance evaluation ranks are 5, and the strength and the elongation are well balanced. On the other hand, in the comparative steels which do not satisfy the ranges specified in the present invention, the appearance evaluation ranks are low without exception, and the strength and the elongation are badly balanced. Further, in the steels produced within the ranges specified in the claims of the present invention, the microstructures are composed of the aforementioned structures, and the steels are excellent in appearance and the balance between strength and elongation.

Table 12-1 (Continued): Chemical composition

Steel code	C	Si	Mn	AL	Mo	P	S	Cr	Ni	Cu	Co	W	Nb	Ti	V
A	0.19	0.009	1.1	0.95	0.13	0.02	0.005								
B	0.15	0.09	1.25	1.1	0.21	0.01	0.004								
C	0.18	0.005	0.9	1.05	0.14	0.01	0.006								
D	0.17	0.005	0.8	0.65	0.05	0.01	0.006	0.05				0.11			
E	0.15	0.05	0.81	1.52	0.22	0.015	0.002		0.42	0.25	0.01				
F	0.22	0.008	1.73	0.67	0.22	0.025	0.003						0.01	0.01	
G	0.08	0.007	1.23	1.34	0.13	0.01	0.005							0.01	0.01

Table 12-2 (Continued): Chemical composition

H	0.09	0.007	1.41	1.8	0.05	0.02	0.004							
I	0.24	0.01	0.87	1.63	0.21	0.02	0.003							
J	0.14	0.08	1.12	0.52	0.05	0.01	0.002				0.15	0.05		
CA	0.12	9.52	1.85	0.03	0.1	0.01	0.003							
CB	0.19	0.08	2.56	0.03	4.5	0.02	0.004							
CC	0.13	0.15	1.68	0.03	0.78	0.01	0.004						0.18	
CD	0.06	0.52	2.98	0.05	0.95	0.02	0.005		0.6	5.8				0.57
CE	0.23	0.01	2.61	0.04	0.5	0.02	0.002	2.3	0.3					

Table 12-3 (Continued): Chemical composition

Steel code	Zr	Hf	Ta	B	Mg	Ca	Y	Ce	Rem	Remarks
A										Invented steel
B										Invented steel
C										Invented steel
D										Invented steel
E						0.0008			0.0003	Invented steel
F					0.0005					Invented steel
G	0.01	0.005	0.005					0.0006	0.0005	Invented steel

Table 12-4 (Continued): Chemical composition

H	0.001		0.0003		Invented steel
I					Invented steel
J					Invented steel
CA					Comparative steel
CB					Comparative steel
CC		0.02			Comparative steel
CD				0.64	Comparative steel
CE	0.15				Comparative steel

(Note) The underlined numerals are the conditions which are outside the range according to the present invention.

Table 13-1-1 (Continued): Plating wettability, corrosion
                          resistance, microstructure and
                          fatigue life of each steel

Steel code	Treatment number	Mn content in plated layer %	Al content in plated layer %	Mo content in plated layer %	Fe content in plated layer %	Value calculated by expression (1)
A	1	0.01	0.1	0.0001		0.43
A	2	0.05	0.15	0.001	12	0.38
A	3	0.04	0.6	0.001	11	−0.07
B	4	0.03	0.3	0.001		0.141
B	5	0.11	0.4	0.002	10	0.041
B	6	0.04	0.4	≤0.0001		0.041
C	7	0.1	0.3	0.002	12	0.245
C	8	0.04	0.8	0.003	11	−0.26
D	9	0.7	0.5	≤0.0001		0.051
D	10	0.6	0.4	0.002	10	0.151
E	11	0.2	0.3	0.005	11	0.205
E	12	0.15	0.4	0.002	10	0.105
E	13	0.3	0.3	0.005	10	0.205
F	14	0.5	0.45	0.001		0.046
F	15	0.1	0.05	0.003	9	0.446

Table 13-1-2 (Continued): Plating wettability, corrosion
                          resistance, microstructure and
                          fatigue life of each steel

Steel code	Treatment number	Mn content in plated layer %	Al content in plated layer %	Mo content in plated layer %	Fe content in plated layer %	Value calculated by expression (1)
G	16	1	0.5	0.002	10	0.025
G	17	1	0.4	0.002	10	0.125
H	18	0.5	0.7	0.0003		-0.19
H	19	0.4	0.35	0.0002	10	0.165
H	20	0.5	0.45	0.0002	9	0.065
I	21	0.7	0.1	0.001	11	0.442
I	22	0.7	0.5	0.003	12	0.042
I	23	1	0.4	0.002	12	0.142
I	24	0.05	0.45	0.004	11	0.092
I	25	0.5	0.3	0.007	12	0.242
I	26	0.5	0.35	0.001		0.192
I	27	0.6	0.13	$\leq$0.0001		0.412
J	28	0.05	0.34	0.0002	11	0.118

Table 13-1-3 (Continued): Plating wettability, corrosion
                          resistance, microstructure and
                          fatigue life of each steel

Steel code	Treatment number	Mn content in plated layer %	Al content in plated layer %	Mo content in plated layer %	Fe content in plated layer %	Value calculated by expression (1)
J	29	0.06	0.2	<u>≤0.0001</u>	10	0.258
J	30	0.06	0.45	0.0001		0.008
CA	31	0.1	0.2	0.007	9	-3.22
CB	32	1.5	0.3	0.08	8	0.078
CC	33	0.5	0.4	0.007		-0.04
CD	34	Many cracks occurred during hot-rolling				
CE	35	Many cracks occurred during hot-rolling				

Table 13-1-4 (Continued): Plating wettability, corrosion resistance, microstructure and fatigue life of each steel

Other elements in plated layer %	Application of alloying heat treatment after plating treatment	Appearance evaluation rank	
	No	5	Invented steel
	Yes	5	Invented steel
	Yes	3	Comparative steel
	No	5	Invented steel
Si: 0.001	Yes	5	Invented steel
	No	3	Comparative steel
	Yes	5	Invented steel
	Yes	2	Comparative steel
Cr: 0.004, W: 0.005	No	3	Comparative steel
Cr: 0.005, W: 0.007	Yes	5	Invented steel
K: 0.01	Yes	5	Invented steel
Ag: 0.004	Yes	5	Invented steel
Ni: 0.01, Cu: 0.01, Co: 0.002	Yes	5	Invented steel
Ti: 0.002, Cs: 0.003	No	5	Invented steel
Rb: 0.002	Yes	5	Invented steel

Table 13-1-5 (Continued): Plating wettability, corrosion
                          resistance, microstructure and
                          fatigue life of each steel

Other elements in plated layer %	Application of alloying heat treatment after plating treatment	Appearance evaluation rank	
V: 0.003, Zr: 0.003, Hf: 0.002, Ta: 0.002	Yes	5	Invented steel
V: 0.002, Zr: 0.002, Nd: 0.007	Yes	5	Invented steel
B: 0.002, Y: 0.003	No	3	Comparative steel
B: 0.003, Y: 0.002	Yes	5	Invented steel
Na: 0.007	Yes	5	Invented steel
Cd: 0.01	Yes	5	Invented steel
La: 0.02	Yes	5	Invented steel
Tl: 0.02	Yes	5	Invented steel
In: 0.005	Yes	5	Invented steel
Be: 0.01	Yes	5	Invented steel
Pb: 0.02	No	5	Invented steel
	No	4	Comparative steel
	No	5	Invented steel

Table 13-1-6 (Continued): Plating wettability, corrosion
                          resistance, microstructure and
                          fatigue life of each steel

Other elements in plated layer %	Application of alloying heat treatment after plating treatment	Appearance evaluation rank	
W: 0.005, Co: 0.02	Yes	_4_	Comparative steel
W: 0.01, Co: 0.03, Tc: 0.002, Ge: 0.008	Yes	5	Invented steel
	Yes	_2_	Comparative steel
Ag: 0.01	Yes	5	Comparative steel
	No	_3_	Comparative steel
			Comparative steel
			Comparative steel

5   (Note) The underlined bold type numerals are the
           conditions which are outside the range according
           to the present invention.
    * The sum of the volume percentage of each phase is
       100%, and the phases which are hardly observed and
10   identified by an optical microscope, such as carbides,
       oxides, sulfides, etc., are included in the volume
       percentage of the main phase. In case that the main
       phase is composed of bainite, since the structure is
       very fine, it is difficult to quantitatively measure
15   each grain size and the volume percentage of each
       phase.

Table 13-2-1 (Continued)

Steel code	Treatment number	Kind of main phase	Volume percentage of ferrite/% *	Average grain size of main phase/μm	Volume percentage of martensite/%
A	1	Ferrite	88	11	0
A	2	Ferrite	88.5	9	0
A	3	Ferrite	Pearlite generated	21	0
B	4	Ferrite	90.5	12	0
B	5	Ferrite	91.5	14	0
B	6	Ferrite	35	11	65
C	7	Ferrite	90.5	12	0
C	8	Ferrite	91	10	0
D	9	Ferrite	Pearlite generated	11	0
D	10	Ferrite	89	11	0
E	11	Ferrite	88	6	0
E	12	Ferrite	85.5	7	0
E	13	Ferrite	88.5	6	0

Table 13-2-2 (Continued)

F	14	Ferrite	86	5	0
F	15	Ferrite	84.5	6	0
G	16	Ferrite	88	5	10
G	17	Ferrite	88	5	11
H	18	Ferrite	87	6	10
H	19	Ferrite	88	5	9
H	20	Ferrite	89	5	9
I	21	Ferrite	83	7	0
I	22	Ferrite	84	6	0
I	23	Ferrite	82	7	0
I	24	Ferrite	83	7	0
I	25	Ferrite	85.5	7	0

Table 13-2-3 (Continued)

I	26	Ferrite	79	8	0
I	27	Ferrite	82	8	0
J	28	Ferrite	90.5	10	0
J	29	Ferrite	84.5	15	0
J	30	Ferrite	90.5	11	0
CA	31	Ferrite	100	10	0
CB	32	Bainite	Immeasurable	Immeasurable	Immeasurable
CC	33	Bainite	Immeasurable	Immeasurable	Immeasurable
CD	34	Many cracks occurring bat-rolling			
CE	35	Many cracks occurring bat-rolling			

Table 13-2-4 (Continued)

Steel code	Treatment number	Volume percentage of austenite/%	Volume percentage of bainite/% *	Average grain size of martensite or austenite/%	Value calculated by expression (2)
A	1	8	4	2.5	2.3225
A	2	7.5	4	2	2.48083
A	3	0	0		
B	4	6	3.5	3	3.11417
B	5	5.5	3	3	3.40205
B	6	0	0		
C	7	6.5	3	2	2.87058
C	8	6	3	1.9	3.11417
D	9	0	0		
D	10	6	5	2.2	3.11417
E	11	7	5	1.8	2.66179
E	12	7.5	6	1.5	2.48083
E	13	6.5	5	2	2.87058

Table 13-2-5 (Continued)

F	14		8	6		1.8		2.3225
F	15		9	6.5		1.9		2.05861
G	16		0	2		0.75		
G	17		0	1		0.8		
H	18		0	3		1.2		
H	19		0	3		0.8		
H	20		0	2		0.75		
I	21		12	5		1.5		1.53083
I	22		11	5		1.3		1.67477
I	23		12	6		1.5		1.53083
I	24		12	5		1.4		1.53083
I	25		10	4.5		1.3		1.8475

Table 13-2-6 (Continued)

I	26	14	7	1.2	1.30464
I	27	12	6	1.2	1.53083
J	28	6.5	3	2	2.87058
J	29	9.5	6	2	1.9475
J	30	6	3.5	1.8	3.11417
CA	31	0	0		
CB	32	Immeasurable	Immeasurable		
CC	33	Immeasurable	Immeasurable		
CD	34				
CE	35				

Table 13-2-7 (Continued)

Steel code	Treatment number	Tensile strength/MPa	Elongation/%	Tensile strength (MPa)× elongation (%)	
A	1	635	39	24765	Invented steel
A	2	630	38	23940	Invented steel
A	3	530	36	19080	Comparative steel
B	4	550	42	23100	Invented steel
B	5	540	43	23220	Invented steel
B	6	825	15	12375	Comparative steel
C	7	595	40	23800	Invented steel
C	8	590	40	23600	Comparative steel
D	9	540	33	17820	Comparative steel
D	10	590	39	23010	Invented steel
E	11	700	33	23100	Invented steel
E	12	700	33	23100	Invented steel
E	13	680	34	23120	Invented steel

Table 13-2-8 (Continued)

F	14	795	32	25440	Invented steel
F	15	780	31	24180	Invented steel
G	16	805	24	19320	Invented steel
G	17	820	23	18860	Invented steel
H	18	815	23	18745	Comparative steel
H	19	790	24	18960	Invented steel
H	20	785	24	18840	Invented steel
I	21	780	29	22620	Invented steel
I	22	785	29	22765	Invented steel
I	23	790	28	22120	Invented steel
I	24	780	29	22620	Invented steel
I	25	780	29	22620	Invented steel

Table 13-2-9 (Continued)

I	26	805	28	22540	Invented steel
I	27	790	29	22910	Comparative steel
J	28	605	39	23595	Invented steel
J	29	580	36	20880	Comparative steel
J	30	595	39	23205	Invented steel
CA	31	620	22		Comparative steel
CB	32	1155	4		Comparative steel
CC	33	965	7		Comparative steel
CD	34				Comparative steel
CE	35				Comparative steel

(Note) The underlined bold type numerals are the conditions which are outside the range according to the present invention.

* The sum of the volume percentage of each phase is 100%, and the phases which are hardly observed and identified by an optical microscope, such as carbides, oxides, sulfides, etc., are included in the volume percentage of the main phase. In case that the main phase is composed of bainite, since the structure is very fine, it is difficult to quantitatively measure each grain size and the volume percentage of each phase.

Table 14-1 (Continued): Production method and each property

Steel code	Treatment number	Heating temperature prior to hot-rolling/°C	Finishing temperature of hot-rolling/°C	AC_3 (calculated+50 (°C))/°C	$0.1 \times (AC_3-AC_1)+AC_1$ (calculated)/°C	Maximum temperature during annealing/°C	Primary cooling rate/°C/s	Primary cooling halt temperature/°C
A	1	1200	900	1223	758	830	3	700
A	2	1200	900	1223	758	830	3	680
A	3	1200	900	1223	758	830	3	600
B	4	1220	910	1295	765	820	1	680
B	5	1220	910	1295	765	820	1	680
B	6	1120	820	1295	765	1300	50	680
C	7	1200	890	1272	763	820	1	680
C	8	1200	890	1272	763	820	1	680
D	9	1200	910	1114	749	830	1	700
D	10	1200	910	1114	749	830	1	700
E	11	1200	895	1474	787	850	0.5	680

Table 14-2 (Continued): Production method and each property

E	12	1200	895	1474	787	850	0.5	680
E	13	1200	895	1474	787	850	0.5	690
F	14	1230	920	1088	738	850	2	690
F	15	1230	920	1088	738	850	2	660
G	16	1200	900	1406	775	810	8	660
G	17	1200	900	1406	775	810	10	700
H	18	1210	890	1579	790	850	10	680
H	19	1210	890	1579	790	850	10	680
H	20	1210	890	1579	790	850	10	670
I	21	1190	890	1494	787	850	1	690
I	22	1190	890	1494	787	840	1	680

Table 14-3 (Continued): Production method and each property

I	23	1190	890	1494	787	830	1	670
I	24	1190	890	1494	787	820	1	670
I	25	1190	890	1494	787	810	1	670
I	26	1190	890	1494	787	850	1	690
I	27	1190	890	1494	787	1050	0.01	690
J	28	1230	920	1064	743	850	1	700
J	29	1300	970	1064	743	950	0.02	710
J	30	1230	920	1064	743	850	1	680
CA	31	1200	900	1007	821	820	1	700
CB	32	1200	890	952	718	820	5	700
CC	33	1200	910	880	721	820	5	700
CD	34	1200	Many cracks occurred during hot-rolling and cold-rolling disfavor					
CE	35	1200	Many cracks occurred during hot-rolling and cold-rolling disfavor					

Table 14-4 (Continued): Production method and each property

Steel code	Treatment number	Secondary cooling rate/°C/s	Retaining conditions including zinc plating treatment	Alloying temperature/°C	Mn content in plated layer %	Al content in plated layer %
A	1	7	For 15 seconds at a temperature of 465 to 455°C		0.01	0.1
A	2	10	For 15 seconds at a temperature of 465 to 455°C	510	0.05	0.15
A	3	0.03	For 15 seconds at a temperature of 465 to 455°C	580	0.04	0.6
B	4	5	For 30 seconds at a temperature of 465 to 460°C		0.03	0.3
B	5	5	For 30 seconds at a temperature of 465 to 460°C	510	0.11	0.4
B	6	150	For 3 seconds at a temperature of 465 to 460°C		0.04	0.4
C	7	10	For 15 seconds at a temperature of 475 to 460°C	510	0.1	0.3
C	8	10	For 15 seconds at a temperature of 475 to 460°C	510	0.04	0.8
D	9	5	For 300 seconds at a temperature of 540 to 460°C		0.7	0.5
D	10	7	For 5 seconds at a temperature of 475 to 460°C	500	0.8	0.4
E	11	5	For 30 seconds at a temperature of 465 to 460°C	505	0.2	0.3

Table 14-5 (Continued): Production method and each property

E	12	5	For 30 seconds at a temperature of 465 to 460°C	505	0.15	0.4
E	13	5	For 30 seconds at a temperature of 465 to 460°C	505	0.3	0.3
F	14	15	For 60 seconds at a temperature of 470 to 460°C		0.5	0.45
F	15	15	For 30 seconds at a temperature of 470 to 460°C	505	0.1	0.05
G	16	20	For 3 seconds at a temperature of 470 to 460°C	505	1	0.5
G	17	20	For 3 seconds at a temperature of 470 to 460°C	505	1	0.4
H	18	15	For 5 seconds at a temperature of 470 to 460°C		0.5	0.7
H	19	20	For 3 seconds at a temperature of 470 to 460°C	500	0.4	0.35
H	20	15	For 3 seconds at a temperature of 475 to 460°C	500	0.5	0.45
I	21	10	For 100 seconds at a temperature of 465 to 460°C	510	0.7	0.1
I	22	10	For 60 seconds at a temperature of 465 to 460°C	510	0.7	0.5

Table 14-6 (Continued): Production method and each property

I	23	10	For 30 seconds at a temperature of 465 to 460°C	520	1	0.4
I	24	10	For 15 seconds at a temperature of 465 to 460°C	520	0.05	0.45
I	25	10	For 15 seconds at a temperature of 465 to 460°C	520	0.5	0.3
I	26	10	For 100 seconds at a temperature of 465 to 460°C		0.5	0.35
I	27	10	For 15 seconds at a temperature of 465 to 460°C		0.5	0.13
J	28	10	For 30 seconds at a temperature of 475 to 460°C		0.05	0.34
J	29	7	For 50 seconds at a temperature of 475 to 460°C	515	0.06	0.2
J	30	10	For 30 seconds at a temperature of 475 to 460°C	515	0.06	0.45
CA	31	1	For 30 seconds at a temperature of 475 to 460°C	520	0.1	0.2
CB	32	30	For 30 seconds at a temperature of 465 to 460°C	520	1.5	0.3
CC	33	30	For 30 seconds at a temperature of 475 to 460°C		0.5	0.4
CD	34					
CE	35					

Table 14-7 (Continued): Production method and each property

Steel code	Treatment number	Mo content in plated layer %	Fe content in plated layer %	Value calculated by expression (1)	Appearance evaluation rank	Tensile strength/ MPa	Elongation/ %	Steel code	
A	1	0.0001		0.4299	5	635	39	A	Invented steel
A	2	0.001	12	0.3799	5	630	38	A	Invented steel
A	3	0.001	11	-0.07	3	530	36	A	Comparative steel
B	4	0.001		0.1406	5	550	42	B	Invented steel
B	5	0.002	10	0.0406	5	540	43	B	Invented steel
B	6	≤0.0001		0.0406	3	825	15	B	Comparative steel
C	7	0.002	12	0.245	5	595	40	C	Invented steel
C	8	0.003	11	-0.26	2	590	40	C	Comparative steel
D	9	≤0.0001		0.0506	3	540	33	D	Comparative steel
D	10	0.002	10	0.1506	5	590	39	D	Invented steel
E	11	0.005	11	0.205	5	700	33	E	Invented steel

Table 14-8 (Continued): Production method and each property

E	12	0.002	10	0.105	5	700	33	E	Invented steel
E	13	0.005	10	0.205	5	680	34	E	Invented steel
F	14	0.001		0.0459	5	795	32	F	Invented steel
F	15	0.003	9	0.4459	5	780	31	F	Invented steel
G	16	0.002	10	0.0247	5	805	24	G	Invented steel
G	17	0.002	10	0.1247	5	820	23	G	Invented steel
H	18	0.0003		-0.19	3	815	23	H	Comparative steel
H	19	0.0002	10	0.1647	5	790	24	H	Invented steel
H	20	0.0002	9	0.0647	5	785	24	H	Invented steel
I	21	0.001	11	0.4417	5	780	29	I	Invented steel
I	22	0.003	12	0.0417	5	785	29	I	Invented steel

Table 14-9 (Continued): Production method and each property

I	23	0.002	12	0.1417	5	780	28	I	Invented steel
I	24	0.004	11	0.0917	5	780	29	I	Invented steel
I	25	0.007	12	0.2417	5	780	29	I	Invented steel
I	26	0.001		0.1917	5	805	28	I	Invented steel
I	27	<u>≤0.0001</u>	11	0.4117	<u>4</u>	790	29	I	Comparative steel
J	28	0.0002	10	0.1178	5	605	39	J	Invented steel
J	29	<u>≤0.0001</u>		0.2578	<u>4</u>	580	38	J	Comparative steel
J	30	0.0001		0.0078	6	595	39	J	Invented steel
CA	31	0.007	9	-3.223	<u>2</u>	620	22	CA	Comparative steel
CB	32	0.08	8	0.0778	5	1155	4	CB	Comparative steel
CC	33	0.007		-0.043	<u>3</u>	985	7	CC	Comparative steel
CD	34							CD	Comparative steel
CE	35							CE	Comparative steel

(Note) The underlined bold type numerals are the conditions which are outside the range according to the present invention.

Example of Embodiment 3

The present invention will hereunder be explained in detail based on Example of Embodiment 3.

Steels having chemical compositions shown in Table 15 were heated to the temperature of 1,200 to 1,250°C; the heated steels were rough-rolled at a total reduction rate of not less than 60% and at a temperature of not less than 1,000°C; then the hot-rolling of the steels was finished; and the hot-rolled steel sheets were cooled and then coiled at a temperature of not less than the bainite transformation commencement temperature which was determined by the chemical composition of each steel, pickled, and cold-rolled into cold-rolled steel sheets 1.0 mm in thickness.

After that, the Ac_1 transformation temperature and the Ac_3 transformation temperature were calculated from the components (in mass %) of each steel according to the following equations:

$$Ac_1 = 723 - 10.7 \times Mn\% + 29.1 \times Si\%,$$

$$Ac_3 = 910 - 203 \times (C\%)^{1/2} + 44.7 \times Si\% + 31.5 \times Mo\% - 30 \times Mn\% - 11 \times Cr\% + 400 \times Al\%.$$

The steel sheets were: heated to the annealing temperature calculated from the Ac_1 transformation temperature and the Ac_3 transformation temperature and retained in the N_2 atmosphere containing 10% of H_2; after the annealing, cooled, when the highest attained temperature during annealing is defined as Tmax (°C), in the temperature range from Tmax - 200°C to Tmax - 100°C at a cooling rate of Tmax/1,000 to Tmax/10 °C/sec.; successively, cooled in the temperature range from the plating bath temperature - 30°C to the plating bath temperature + 50°C at a cooling rate of 0.1 to 100°C/sec.; then dipped in the plating bath; and retained in the temperature range from the plating bath temperature - 30°C to the plating bath temperature + 50°C for 2 to 200 seconds including the dipping time.

Thereafter, as the Fe-Zn alloying treatment, some of the steel sheets were retained in the temperature range from 400 to 550°C for 15 seconds to 20 minutes after they were plated and Fe contents in the plated layers were adjusted so as to be 5 to 20% in mass, further, rolled in the skin-pass line at the reduction rate of 0.5 - 2.0%. The steel sheets were subjected to full flat bending (R=1t) and to a JASO cyclic corrosion test up to 150 cycles as a means of evaluating the corrosion resistance in an environment containing chlorine, and the progress of corrosion was evaluated. The compositions of the plated layers were determined by dissolving the plated layers in 5% hydrochloric acid solution containing an inhibitor and chemically analyzing the solution, and the results are shown in Table 16.

From Tables 16 and 17, in the steels according to the present invention, which satisfy the expression (3), all the corrosion evaluation ranks are 4 or 5, and the strength and the elongation are well balanced.

On the other hand, in the comparative steels which do not satisfy the ranges specified in the present invention, since they do not satisfy the regulations on a microstructure or the regulations on production conditions, the strength and the elongation are badly balanced without exception. In the steels of Nos. 3, 13 and 20, which are the comparative steels, the corrosion evaluation ranks are 4 or 5. However, in case of Nos. 13 and 20, the balance between the strength and the elongation is inferior, and in case of No. 3, the tensile strength is low. Further, in the steels produced within the ranges specified in the claims of the present invention, the microstructures are composed of the aforementioned structures, and the steels are excellent in appearance and the balance between strength and elongation.

Table 15-1 (Continued): Chemical composition

Steel code	C	Si	Mn	AL	Mo	P	S	Cr	Ni	Cu	Co	W	Nb
A	0.18	0.005	1.12	0.69	0.17	0.01	0.005						
B	0.15	0.009	0.91	1.33	0.22	0.01	0.004						
C	0.13	0.08	0.98	0.36	0.09	0.01	0.006	0.12			0.37	0.05	
D	0.1	0.09	1.32	0.55	0.05	0.02	0.004		0.83	0.44			
E	0.12	0.05	1.75	0.03	0.02	0.015	0.002						0.01
F	0.07	0.008	2.33	0.03	0.04	0.025	0.003						
G	0.21	0.012	1.16	1.67	0.18	0.01	0.005						
H	0.24	0.005	0.78	0.85	0.17	0.02	0.004						
O	0.002	0.008	0.08	0.05	2.5	0.008	0.004						
JJ	0.08	0.15	1.31	0.03	0.01	0.01	0.004						0.15
KK	0.08	0.33	2.98	0.05	0.9	0.02	0.005		3.5	8.8			
LL	0.11	0.01	1.05	0.04	0.8	0.02	0.002	2.98	1.5				
M	0.19	0.01	1.21	1.51	0.13	0.01	0.005						
N	0.23	0.008	1.43	1.45	0.18	0.01	0.006						
O	0.18	0.02	1.31	1.52	0.11	0.01	0.004						

Table 15-2 (Continued): Chemical composition

Steel code	Ti	V	Zr	Hf	Ta	B	Mg	Ca	Y	Ca	Rem	Remarks
A												Invented steel
B												Invented steel
C							0.0003	0.001				Invented steel
D						0.0003				0.0005		Invented steel
E	0.01								0.0004		0.0003	Invented steel
F		0.05	0.005	0.01								Invented steel
G					0.01							Invented steel
H												Invented steel
O	0.05											Comparative steel
JJ		0.88										Comparative steel
KK						0.15	0.015					Comparative steel
LL											0.55	Comparative steel
M												Invented steel
N												Invented steel
O												Invented steel

(Note) The underlined numerals are the conditions which are outside the range according to the present invention.

Table 16-1-1 (Continued): Plating wettability, corrosion resistance, microstructure and fatigue life of each steel

Steel code	Treatment number	Al content in plated layer %	Mo content in plated layer % *	Mo content in steel %	Value calculated by expression (1) #	Application of alloying heat treatment after plating treatment	Fe content in plated layer %	Corrosion resistance evaluation rank after JASO 150 cycle test	
A	1	0.012	0.0002	0.17	1.42E-01	No		5	Invented steel
A	2	0.34	0.001	0.17	4.01E+00	Yes	9	5	Invented steel
A	3	0.37	0.001	0.17	4.36E+00	Yes	10	5	Comparative steel
B	4	0.46	0.003	0.22	4.20E+00	Yes	9.5	5	Invented steel
B	5	0.03	0.0001	0.22	2.73E-01	No		4	Invented steel
B	6	0.001	<u>0</u>	0.22	<u>9.09E-03</u>	No		<u>2</u>	Comparative steel
C	7	0.015	0.0001	0.09	3.34E-01	No		4	Invented steel
C	8	0.044	0.003	0.09	1.01E+00	Yes	11	5	Invented steel
D	9	0.6	0.0001	0.05	2.40E+01	No		4	Invented steel
D	10	0.55	0.001	0.05	2.20E+01	Yes	10.5	4	Invented steel
E	11	0.013	0.0004	0.02	1.32E+00	No		5	Invented steel

Table 16-1-2 (Continued): Plating wettability, corrosion resistance, microstructure and fatigue life of each steel

Steel code	Treatment number	Al content in plated layer %	Mo content in plated layer %*	Mo content in steel %	Value calculated by expression (1) #	Application of alloying heat treatment after plating treatment	Fe content in plated layer %	Corrosion resistance evaluation rank after JASO 150 cycle test	
E	12	0.05	0.003	0.02	5.15E+00	Yes	12	4	Invented steel
F	13	0.3	0.005	0.02	3.03E+01	No		4	Comparative steel
F	14	0.009	0.0001	0.04	4.53E-01	No		5	Invented steel
F	15	0.074	0.003	0.04	3.78E+00	Yes	8.5	4	Invented steel
G	16	0.018	0.0001	0.18	2.01E-01	No		4	Invented steel
G	17	0.51	0.002	0.18	5.68E+00	Yes	10	5	Invented steel
H	18	0.051	0.0002	0.17	6.01E-01	No		5	Invented steel
H	19	0.42	0.001	0.17	4.95E+00	Yes	10	5	Invented steel
H	20	0.55	0.002	0.17	6.48E+00	Yes	9	5	Comparative steel
II	21	0.011	0	2.5	8.80E-03	No		2	Comparative steel
JJ	22	0.56	0.007	0.005	2.25E+02	Yes	11	3	Comparative steel

Table 16-1-3 (Continued): Plating wettability, corrosion resistance, microstructure and fatigue life of each steel

Steel code	Treatment number	Al content in plated layer %**	Mo content in plated layer %*	Mo content in steel %	Value calculated by expression (1) #	Application of alloying heat treatment after plating treatment	Fe content in plated layer %	Corrosion resistance evaluation rank after JASO 150 cycle test	
KK	23	Many cracks occurred during hot-rolling							Comparative steel
LL	24	Many cracks occurred during hot-rolling							Comparative steel
M1	25	0.015	0.0005	0.13	2.35E-01	Yes	10	5	Invented steel
M2	26	0.005	0.0003	0.13	7.92E-02	No		5	Invented steel
N	27	0.013	0.0010	0.18	1.5E-01	Yes	9	5	Invented steel
O	28	0.011	0.0006	0.11	2.05E-01	Yes	10	5	Invented steel

(Note) The underlined bold type numerals are the conditions which are outside the range according to the present invention.

* The value is regarded as 0 when Mo content is less than 0.0001%.

** The sum of the volume percentage of each phase is 100%, and the phases which are hardly observed and identified by an optical microscope, such as carbides, oxides, sulfides, etc., are included in the volume percentage of the main phase. In case that the main phase is composed of bainite, since the structure is very fine, it is difficult to quantitatively measure each grain size and the volume percentage of each phase.

"1.42E – 01" means 1.42×10^{-1}.

Table 16-2-1 (Continued): Plating wettability, corrosion resistance, microstructure and fatigue life of each steel

Steel code	Treatment number	Kind of main phase	Volume percentage of ferrite	Average grain size of main phase/μm	Volume percentage of martensite/%
A	1	Ferrite	86.5	13	0
A	2	Ferrite	88	14	0
A	3	Ferrite and pearlite	Pearlite generated	22	0
B	4	Ferrite	89	15	0
B	5	Ferrite	90	16	0
B	6	Ferrite	95.7	9	1
C	7	Ferrite	91.5	11	0
C	8	Ferrite	91	13	0
D	9	Ferrite	80	8	0
D	10	Ferrite	81.5	7.5	0
E	11	Ferrite	86	5	9
E	12	Ferrite	85.5	5.5	8.5
F	13	Ferrite and bainite	15	4	34
F	14	Ferrite	77	4	17
F	15	Ferrite	79	5	16
G	16	Ferrite	87	12	0
G	17	Ferrite	87.5	10	0

Table 16-2-2 (Continued): Plating wettability, corrosion resistance, microstructure and fatigue life of each steel

		Microstructure			
H	18	Ferrite	81.5	8	0
H	19	Ferrite	83	7	0
H	20	Ferrite and pearlite	Pearlite generated	7	0
II	21	Ferrite	100	18	0
JJ	22	Ferrite	199	8	0
KK	23				
LL	24				
M1	25	Ferrite	85	12	1
M2	26	Ferrite	85	12	0
N	27	Ferrite	77	9	1
O	28	Ferrite	87	11	0

Table 16-2-3 (Continued): Plating wettability, corrosion resistance, microstructure and fatigue life of each steel

Steel code	Treatment number	Volume percentage of austenite/%	Volume percentage of bainite	Average grain size of martensite or austenite/μ	Value calculated by expression (2)	Ratio f grain size of main phase to that of second phase
A	1	8.5	5	2.5	2.15176	0.19231
A	2	7.5	4.5	2	2.432	0.14286
A	3	0	0			0
B	4	7	4	3.2	2.17089	0.21333
B	5	6.5	3.5	2.8	2.34067	0.175
B	6	1.5	1.8	1.2	9.83376	0.13333
C	7	5.5	3	2.2	2.415523	0.2
C	8	8	3	1.9	2.22417	0.14615
D	9	111	9	1.5	1.15773	0.1875
D	10	10.5	8	1.7	1.21643	0.22667
E	11	0	5	1.2		0.24
E	12	0	6	0.9		0.16364
F	13	0	51	2.5		0.625
F	14	0	6	0.7		0.175
F	15	0	5	0.6		0.12
G	16	9	4	1.9	2.385	0.15833
G	17	8.5	4	1.8	2.51676	0.18

Table 16-2-4 (Continued): Plating wettability, corrosion resistance, microstructure and fatigue life of each steel

H	18	15.5	3	1.2	1.6082	0.15
H	19	14	3	0.8	1.7691	0.11429
H	20	0	0			0
II	21	0	0			0
JJ	22	0	0			0
KK	23					
LL	24					
M1	25	9.5	4.5	2.0	2.13125	0.1667
M2	26	10.5	4.5	2.0	1.9608	0.1667
N	27	15.0	7.0	1.9	1.8194	0.2111
O	28	9.5	3.5	1.8	2.0584	0.1636

Table 16-2-5 (Continued): Plating wettability, corrosion resistance, microstructure and fatigue life of each steel

Steel code	Treatment number	Tensile strength/MPa	Elongation	Tensile strength (MPA)×elongation(%)	
A	1	645	37	23865	Invented steel
A	2	640	38	24320	Invented steel
A	3	540	34	18360	Comparative steel
B	4	580	39	22620	Invented steel
B	5	585	38	22230	Invented steel
B	6	600	27	16200	Comparative steel
C	7	575	40	23000	Invented steel
C	8	570	40	22800	Invented steel
D	9	785	28	21980	Invented steel
D	10	780	28	21840	Invented steel
E	11	880	23	20240	Invented steel
E	12	885	23	20355	Invented steel
F	13	945	10	9450	Comparative steel

Table 16-2-6 (Continued): Plating wettability, corrosion resistance, microstructure and fatigue life of each steel

F	14	910	22	20020	Invented steel
F	15	890	23	20470	Invented steel
G	16	625	37	23125	Invented steel
G	17	615	37	22755	Invented steel
H	18	815	23	18745	Invented steel
H	19	790	24	18960	Invented steel
H	20	565	30	16950	Comparative steel
II	21	305	51	15555	Comparative steel
JJ	22	570	25	14250	Comparative steel
KK	23				Comparative steel
LL	24				Comparative steel
M1	25	620	36	22320	Invented steel
M2	26	615	37	22755	Invented steel
N	27	790	27	21330	Invented steel
O	28	595	38	22610	Invented steel

(Note) The underlined bold type numerals are the conditions which are outside the range according to the present invention.

* The value is regarded as 0 when Mo content is less than 0.0001%.

** The sum of the volume percentage of each phase is 100%, and the phases which are hardly observed and identified by an optical microscope, such as carbides, oxides, sulfides, etc., are included in the volume percentage of the main phase. In the case that the main phase is composed of bainite, since the structure is very fine, it is difficult to quantitatively measured each grain size and the volume percentage of each phase.

Table 17-1-1 (Continued): Production method and each property

Steel code	Treatment number	Heating temperature prior to hot-rolling/°C	Total reduction rate in rough hot-rolling/%	Finishing temperature of rough hot-rolling/°C	Ac₃ (calculated) +50 (°C)/°C	Ac₃ (calculated °C)/°C	0.12×(Ac₃-Ac₁)+Ac₁ (calculated)/°C
A	1	1230	90	1020		1122	769
A	2	1230	90	1020		1122	769
A	3	1230	90	1020		1122	769
B	4	1220	88	1020		1393	803
B	5	1220	88	1020		1393	803
B	6	1120	50	930		1393	803
C	7	1250	85	1095		1006	758
C	8	1210	92	1050		1006	758
D	9	1220	91	1030		1082	764
D	10	1220	91	1030		1082	764
E	11	1245	85	1070		852	731
E	12	1245	85	1070		852	731

Table 17-1-2 (Continued): Production method and each property

Steel code	Treatment number	Maximum temperature during annealing: Tmax (°C)/°C	Primary cooling rate/°C/s	Primary cooling halt temperature/°C	Secondary cooling rate/°C/s	Retaining conditions including zinc plating treatment
A	1	830	1	680	7	For 35 seconds at a temperature of 465 to 455°C
A	2	830	1	680	10	For 15 seconds at a temperature of 465 to 455°C
A	3	830	1	580	0.01	For 15 seconds at a temperature of 465 to 455°C
B	4	820	1	680	5	For 30 seconds at a temperature of 465 to 460°C
B	5	820	1	680	5	For 30 seconds at a temperature of 465 to 460°C
B	6	770	120	680	150	For 3 seconds at a temperature of 465 to 450°C
C	7	850	3	670	10	For 60 seconds at a temperature of 475 to 460°C
C	8	820	0.1	690	5	For 45 seconds at a temperature of 475 to 460°C
D	9	835	2	700	5	For 300 seconds at a temperature of 455 to 460°C
D	10	835	5	675	7	For 50 seconds at a temperature of 475 to 460°C
E	11	825	5	690	10	For 10 seconds at a temperature of 465 to 460°C
E	12	825	3	690	30	For 3 seconds at a temperature of 465 to 460°C

WO 02/101112

Table 17-1-3 (Continued): Production method and each property

Steel code	Treatment number	Alloying temperature /°C	Value calculated by expression (1)#	Corrosion resistance evaluation rank after JASO 150 cycle test	Tensile strength /MPa	Elongation /%	Steel code	
A	1		1.42E-01	5	645	37	A	Invented steel
A	2	500	4.01E+00	5	640	38	A	Invented steel
A	3	575	4.36E+00	5	540	34	A	Comparative steel
B	4		4.20E+00	5	580	39	B	Invented steel
B	5	510	2.73E+00	4	590	38	B	Invented steel
B	6		9.09E-03	2	595	30	B	Comparative steel
C	7		3.34E-01	4	575	40	C	Invented steel
C	8	500	1.01E+00	5	570	40	C	Invented steel
D	9		2.40E+01	4	795	33	D	Invented steel
D	10	500	2.20E+01	4	800	32	D	Invented steel
E	11		1.32E+00	5	880	23	E	Invented steel
E	12	500	5.15E+00	4	885	23	E	Invented steel

Table 17-2-1 (Continued): Production method and each property (Continue)

Steel code	Treatment number	Heating temperature prior to hot-rolling/°C	Total reduction rate in rough hot-rolling/%	Finishing temperature of rough hot-rolling/°C	Ac₃ (calculated +50(°C)/°C
F	13	1240	88	1030	854
F	14	1240	88	1030	854
F	15	1240	88	1030	854
G	16	1200	90	1010	1506
G	17	1200	90	1010	1506
H	18	1210	92	1025	1183
H	19	1210	92	1025	1183
H	20	1210	92	1025	1183
II	21	1200	93	1030	1049
JJ	22	1250	95	1000	882
M1	23	1200	90	1050	1444
M2	24	1200	90	1050	1444
N	25	1200	90	1050	1406
O	26	1200	90	1050	1447

Table 17-2-2 (Continued): Production method and each property (Continue)

Steel code	Treatment number	$0.12 \times (AC_3 - AC_1) + AC_1$ (calculated)/°C	Maximum temperature during annealing: Tmax (°C)/°C	Primary cooling rate /°C/s	Primary cooling halt temperature/°C	Secondary cooling rate /°C/s
F	13	725	980	10	730	50
F	14	725	820	2	660	3
F	15	725	820	2	665	7
G	16	815	850	5	680	8
G	17	815	850	3	700	20
H	18	779	830	10	680	15
H	19	779	830	10	680	20
H	20	779	770	0.03	710	0.05
II	21	770	800	0.1	650	10
JJ	22	742	830	0.05	680	0.3
M1	23	792	800	2	670	5
M2	24	792	800	2	670	5
N	25	786	800	2	670	5
O	26	792	800	2	670	5

Table 17-2-3 (Continued): Production method and each property (Continue)

Steel code	Treatment number	Retaining conditions including zinc plating treatment	Alloying temperature/°C	Value calculated by expression (1)#
F	13	For 100 seconds at a temperature of 450 to 460°C		3.03E+01
F	14	For 160 seconds at a temperature of 450 to 460°C		4.53E-01
F	15	For 15 seconds at a temperature of 470 to 460°C	505	3.78E+00
G	16	For 20 seconds at a temperature of 470 to 460°C		2.01E-01
G	17	For 10 seconds at a temperature of 470 to 460°C	510	5.68E+00
H	18	For 5 seconds at a temperature of 470 to 460°C		6.01E-01
H	19	For 3 seconds at a temperature of 470 to 460°C	500	4.95E+00
H	20	For 3 seconds at a temperature of 475 to 460°C	540	6.48E+00
II	21	For 5 seconds at a temperature of 465 to 460°C	510	8.80E-03
JJ	22	For 60 seconds at a temperature of 465 to 460°C	545	2.25E+02
M1	23	For 30 seconds at a temperature of 460 to 450°C	525	2.35E-01
M2	24	For 60 seconds at a temperature of 460 to 450°C	-	7.92E-02
N	25	For 60 seconds at a temperature of 460 to 450°C	500	1.50E-01
O	26	For 60 seconds at a temperature of 460 to 450°C	500	2.05E-01

Table 17-2-4 (Continued): Production method and each property (Continue)

Steel code	Treatment number	Corrosion resistance evaluation rank after JASO 150 cycle test	Tensile strength/MPa	Elongation/%	Steel code	
F	13	4	945	10	E	Comparative steel
F	14	5	910	22	F	Invented steel
F	15	4	890	23	F	Invented steel
G	16	4	625	37	G	Invented steel
G	17	5	615	37	G	Invented steel
H	18	5	615	23	H	Invented steel
H	19	5	790	24	H	Invented steel
H	20	5	565	30	H	Comparative steel
II	21	2	305	51	II	Comparative steel
JJ	22	3	570	25	JJ	Comparative steel
M1	23	5	620	36	M1	Invented steel
M2	24	5	615	37	M2	Invented steel
N	25	5	790	27	N	Invented steel
O	26	5	595	38	O	Invented steel

(Note) The underlined bold type numerals are the conditions which are outside the range according to the present invention.

"1.42E - 01" means 1.42×10^{-1}.

Industrial Applicability

     The present invention provides: a high-strength
high-ductility hot-dip galvanized steel sheet and hot-dip
galvannealed steel sheet having high fatigue resistance
5   and corrosion resistance; a high-strength hot-dip
galvanized steel sheet excellent in ductility, which
improves non-plating defects and plating adhesion after
severe deformation, and a method of producing the same; a
high-strength high-ductility hot-dip galvanized steel
10   sheet having high fatigue resistance and corrosion
resistance; a high-strength hot-dip galvanized steel
sheet excellent in appearance and workability, which
suppresses the generation of non-plating defects, and a
method of producing the same; and a high-strength hot-dip
15   galvannealed steel sheet and a high-strength hot-dip
galvanized steel sheet, which suppress non-plating
defects and surface defects and have both corrosion
resistance, in particular corrosion resistance, in an
environment containing chlorine ion, and high ductility,
20   and a method of producing the same.

- 83 -

CLAIMS

1.   A high-strength high-ductility hot-dip
galvanized steel sheet and hot-dip galvannealed steel
sheet having high fatigue resistance and corrosion
resistance, the hot-dip galvanized or galvannealed steel
sheet having a plated layer on the surface of the base
layer consisting of a steel sheet, characterized in that
the maximum depth of the grain boundary oxidized layer
formed at the interface between the plated layer and the
base layer is not more than 0.5 μm.

2.   A high-strength high-ductility hot-dip
galvanized steel sheet and hot-dip galvannealed steel
sheet having high fatigue resistance and corrosion
resistance, the hot-dip galvanized or galvannealed steel
sheet having a zinc plated layer on the surface of the
base layer consisting of a steel sheet, characterized in
that the maximum depth of the grain boundary oxidized
layer at the interface between the plated layer and the
base layer is not more than 1 μm and the average grain
size of the main phase in the microstructure of the base
layer is not more than 20 μm.

3.   A high-strength high-ductility hot-dip
galvanized steel sheet and hot-dip galvannealed steel
sheet having high fatigue resistance and corrosion
resistance, the hot-dip galvanized or galvannealed steel
sheet having a plated layer on the surface of the base
layer consisting of a steel sheet, according to claim 1
or 2, characterized in that the value obtained by
dividing the maximum depth of the grain boundary oxidized
layer formed at the interface between the plated layer
and the base layer by the average grain size of the main
phase in the microstructure of the base layer is not more
than 0.1.

4.   A high-strength high-ductility hot-dip
galvanized steel sheet and hot-dip galvannealed steel
sheet having high fatigue resistance and corrosion

resistance according to any one of claims 1 to 3, characterized in that the steel sheet contains, in its microstructure, ferrite or ferrite and bainite 50 to 97% in volume as the main phase, and either or both of

5   martensite and austenite 3 to 50% in total volume as the second phase.

5.   A high-strength high-ductility hot-dip galvanized steel sheet and hot-dip galvannealed steel sheet having high fatigue resistance and corrosion

10   resistance according to any one of claims 1 to 4, characterized in that: the plated layer contains, in mass,

Al: 0.001 to 0.5%, and

Mn: 0.001 to 2%,

15   with the balance consisting of Zn and unavoidable impurities; and Si content: X (in mass %), Mn content: Y (in mass %) and Al content: Z (in mass %) in the steel sheet, and Al content: A (in mass %) and Mn content: B (in mass %) in the plated layer satisfy the following

20   equation 1:

$$3-(X+Y/10+Z/3)-12.5\times(A-B) \geqq 0 \ldots 1$$

6.   A high-strength high-ductility hot-dip galvannealed steel sheet having high fatigue resistance and corrosion resistance according to claim 5,

25   characterized in that the plated layer contains Fe at 5 to 20% in mass.

7.   A high-strength hot-dip galvanized steel sheet having high plating adhesion after severe deformation and ductility, the hot-dip galvanized steel sheet having a

30   plated layer containing, in mass,

Al: 0.001 to 0.5%, and

Mn: 0.001 to 2%,

with the balance consisting of Zn and unavoidable impurities, on the surface of a steel sheet consisting

35   of, in mass,

C: 0.0001 to 0.3%,

Si: 0.01 to 2.5%,

Mn: 0.01 to 3%,

Al: 0.001 to 4%, and

the balance consisting of Fe and unavoidable impurities,

characterized in that: Si content: X (in mass %), Mn

content: Y (in mass %) and Al content: Z (in mass %) in

the steel, and Al content: A (in mass %) and Mn content:

B (in mass %) in the plated layer satisfy the following

equation 1; and the microstructure of the steel sheet has

the main phase comprising ferrite at 70 to 97% in volume

and the average grain size of a main phase being not more

than 20 μm, and a second phase comprising austenite

and/or martensite at 3 to 30% in volume and the average

grain size of the second phase being not more than 10 μm:

$$3-(X+Y/10+Z/3)-12.5\times(A-B) \geqq 0 \ \dots \ 1$$

8.   A high-strength hot-dip galvannealed steel

sheet having high plating adhesion after severe

deformation and ductility according to claim 7,

characterized in that the plated layer further contains

Fe at 5 to 20% in mass.

9.   A high-strength hot-dip galvanized steel sheet

and hot-dip galvannealed steel sheet having high plating

adhesion after severe deformation and ductility according

to claim 7 or 8, characterized in that the average grain

size of austenite and/or martensite which constitute(s)

the second phase of the steel sheet is 0.01 to 0.7 times

the average grain size of ferrite.

10.   A high-strength hot-dip galvanized steel sheet

and hot-dip galvannealed steel sheet having high plating

adhesion after severe deformation and ductility according

to any one of claims 7 to 9, characterized in that the

microstructure of the steel sheet: has a main phase

comprising ferrite at 50 to 95% in volume and the average

grain size of the main phase being not more than 20 μm,

and a second phase comprising austenite and/or martensite

at 3 to 30% in volume and the average grain size of the

second phase being not more than 10 μm; and further
contains bainite at 2 to 47% in volume.

11. A high-strength hot-dip galvanized steel sheet
and hot-dip galvannealed steel sheet having high plating
adhesion after severe deformation and ductility according
to any one of claims 7 to 10, characterized in that the
steel further contains Mo at 0.001 to 5% in mass.

12. A high-strength hot-dip galvanized steel sheet
and hot-dip galvannealed steel sheet having high plating
adhesion after severe deformation and ductility according
to any one of claims 7 to 11, characterized in that the
steel further contains P at 0.0001 to 0.1% and S at
0.0001 to 0.01%, in mass.

13. A high-strength hot-dip galvanized steel sheet
and hot-dip galvannealed steel sheet having high fatigue
resistance and corrosion resistance according to any one
of claims 7 to 12, characterized in that the Si content
in the steel is 0.001 to 2.5%.

14. A high-strength hot-dip galvannealed steel
sheet having superior appearance and workability, the
hot-dip galvannealed steel sheet having a plated layer
containing, in mass,

       Mn: 0.001 to 3%,
       Al: 0.001 to 4%,
       Mo: 0.0001 to 1%, and
       Fe: 5 to 20%,
with the balance consisting of Zn and unavoidable
impurities, on the surface of a steel sheet consisting
of, in mass,
       C: 0.0001 to 0.3%,
       Si: 0.001 to less than 0.1%,
       Mn: 0.01 to 3%,
       Al: 0.001 to 4%,
       Mo: 0.001 to 1%,
       P: 0.0001 to 0.3%,
       S: 0.0001 to 0.1%, and
the balance consisting of Fe and unavoidable impurities,

characterized in that: Mn content: X (in mass %) and Si
content: Y (in mass %) in the steel, and Al content: Z
(in mass %) in the plated layer satisfy the following
equation 2:

5          $0.6-(X/18+Y+Z) \geqq 0 \ldots 2$

          15. A high-strength hot-dip galvanized steel sheet
having superior appearance and workability, the hot-dip
galvanized steel sheet having a plated layer containing,
in mass,

10   Mn: 0.001 to 3%,
          Al: 0.001 to 4%,
          Mo: 0.0001 to 1%, and
          Fe: less than 5%,
with the balance consisting of Zn and unavoidable

15 impurities, on the surface of a steel sheet consisting
of, in mass,
          C: 0.0001 to 0.3%,
          Si: 0.001 to less than 0.1%,
          Mn: 0.01 to 3%,

20   Al: 0.001 to 4%,
          Mo: 0.001 to 1%,
          P: 0.0001 to 0.3%,
          S: 0.0001 to 0.1%, and
the balance consisting of Fe and unavoidable impurities,

25 characterized in that: Mn content: X (in mass %) and Si
content: Y (in mass %) in the steel, and Al content: Z
(in mass %) in the plated layer satisfy the following
equation 2:
          $0.6-(X/18+Y+Z) \geqq 0 \ldots 2$

30   16. A high-strength high-ductility hot-dip
galvannealed steel sheet having high corrosion
resistance, the hot-dip galvannealed steel sheet having a
plated layer containing, in mass,
          Al: 0.001 to 4%, and

35   Fe: 5 to 20%,
with the balance consisting of Zn and unavoidable

impurities, on the surface of a steel sheet consisting
of, in mass,

C: 0.0001 to 0.3%,

Si: 0.001 to less than 0.1%,

Mn: 0.001 to 3%,

Al: 0.001 to 4%,

Mo: 0.001 to 1%,

P: 0.001 to 0.3%,

S: 0.0001 to 0.1%, and

the balance consisting of Fe and unavoidable impurities,
characterized in that: Al content: A (in mass %) and Mo
content: B (in mass %) in the plated layer, and Mo
content: C (in mass %) in the steel satisfy the following
equation 3; and the microstructure of the steel consists
of the main phase comprising ferrite or ferrite and
bainite 50 to 97% in volume and the balance consisting of
a complex structure containing either or both of
martensite and retained austenite 3 to 50% in volume:

$$100 \geqq (A/3+B/6)/(C/6) \geqq 0.01 \ldots 3$$

17.   A high-strength high-ductility hot-dip
galvanized steel sheet having high corrosion resistance,
the hot-dip galvanized steel sheet having a plated layer
containing, in mass,

Al: 0.001 to 4%, and

Fe: less than 5%,

with the balance consisting of Zn and unavoidable
impurities, on the surface of a steel sheet consisting
of, in mass,

C: 0.0001 to 0.3%,

Si: 0.001 to less than 0.1%,

Mn: 0.001 to 3%,

Al: 0.001 to 4%,

Mo: 0.001 to 1%,

P: 0.001 to 0.3%,

S: 0.0001 to 0.1%, and

the balance consisting of Fe and unavoidable impurities,
characterized in that: Al content: A (in mass %) and Mo

content: B (in mass %) in the plated layer, and Mo
content: C (in mass %) in the steel satisfy the following
equation 3; and the microstructure of the steel consists
of the main phase comprising ferrite or ferrite and

5 bainite 50 to 97% in volume and the balance consisting of
a complex structure containing either or both of
martensite and retained austenite at 3 to 50% in volume:

$$100 \geq (A/3+B/6)/(C/6) \geq 0.01 \ldots 3$$

18. A high-strength hot-dip galvanized steel sheet

10 and hot-dip galvannealed steel sheet having superior
appearance and workability according to any one of claims
14 to 17, characterized in that the microstructure of the
steel consists of the main phase comprising ferrite or
ferrite and bainite at 50 to 97% in volume and the

15 balance consisting of a complex structure containing
either or both of martensite and retained austenite at 3
to 50% in total volume.

19. A high-strength hot-dip galvanized steel sheet
and hot-dip galvannealed steel sheet having superior

20 appearance and workability according to any one of claims
14 to 18, characterized in that the microstructure of the
steel sheet has a main phase comprising ferrite at 70 to
97% in volume and the average grain size of the main
phase being not more than 20 μm, and a second phase

25 comprising austenite and/or martensite at 3 to 30% in
volume and the average grain size of the second phase
being not more than 10 μm.

20. A high-strength hot-dip galvanized steel sheet
and hot-dip galvannealed steel sheet having superior

30 appearance and workability according to any one of claims
14 to 19, characterized in that: the second phase of the
steel sheet is composed of austenite; and C content: C
(in mass %) and Mn content: Mn (in mass %) in the steel,
and the volume percentage of austenite: Vγ (in %) and the

35 volume percentage of ferrite and bainite: Vα (in %)
satisfy the following equation 4:

$(V\gamma + V\alpha)/V\gamma \times C + Mn/8 \geqq 2.0 \ldots 4$

21. A high-strength hot-dip galvanized steel sheet and hot-dip galvannealed steel sheet having superior appearance and workability according to any one of claims 14 to 20, characterized in that the microstructure of the steel sheet: has a main phase comprising ferrite at 50 to 95% in volume and the average grain size of the main phase being not more than 20 µm, and a second phase comprising austenite and/or martensite at 3 to 30% in volume and the average grain size of the second phase being not more than 10 µm; and further contains bainite at 2 to 47% in volume.

22. A high-strength high-ductility hot-dip galvanized steel sheet and hot-dip galvannealed steel sheet having high corrosion resistance according to any one of claims 14 to 21, characterized in that the average grain size of austenite and/or martensite which constitute(s) the second phase of the steel sheet is 0.01 to 0.6 times the average grain size of ferrite.

23. A high-strength hot-dip galvanized steel sheet having high plating adhesion after severe deformation and ductility according to any one of claims 1 to 22, characterized in that the plated layer further contains, in mass, one or more of,

Ca: 0.001 to 0.1%,

Mg: 0.001 to 3%,

Si: 0.001 to 0.1%,

Mo: 0.001 to 0.1%,

W: 0.001 to 0.1%,

Zr: 0.001 to 0.1%,

Cs: 0.001 to 0.1%,

Rb: 0.001 to 0.1%,

K: 0.001 to 0.1%,

Ag: 0.001 to 5%,

Na: 0.001 to 0.05%,

Cd: 0.001 to 3%,

Cu: 0.001 to 3%,

Ni: 0.001 to 0.5%,

Co: 0.001 to 1%,

La: 0.001 to 0.1%,

5   Tl: 0.001 to 8%,

Nd: 0.001 to 0.1%,

Y: 0.001 to 0.1%,

In: 0.001 to 5%,

Be: 0.001 to 0.1%,

10   Cr: 0.001 to 0.05%,

Pb: 0.001 to 1%,

Hf: 0.001 to 0.1%,

Tc: 0.001 to 0.1%,

Ti: 0.001 to 0.1%,

15   Ge: 0.001 to 5%,

Ta: 0.001 to 0.1%,

V: 0.001 to 0.2%, and

B: 0.001 to 0.1%.

24.   A high-strength hot-dip galvanized steel sheet
20   and hot-dip galvannealed steel sheet having superior
appearance and workability according to any one of claims
1 to 23, characterized in that the steel further
contains, in mass, one or more of,

Cr: 0.001 to 25%,

25   Ni: 0.001 to 10%,

Cu: 0.001 to 5%,

Co: 0.001 to 5%, and

W: 0.001 to 5%.

25.   A high-strength hot-dip galvanized steel sheet
30   and hot-dip galvannealed steel sheet having superior
appearance and workability according to any one of claims
1 to 24, characterized in that the steel further
contains, in mass, one or more of Nb, Ti, V, Zr, Hf and
Ta at 0.001 to 1% in total.

35   26.   A high-strength hot-dip galvanized steel sheet
and hot-dip galvannealed steel sheet having superior
appearance and workability according to any one of claims

1 to 25, characterized in that the steel yet further contains B at 0.0001 to 0.1% in mass.

27. A high-strength hot-dip galvanized steel sheet and hot-dip galvannealed steel sheet having superior appearance and workability according to any one of claims 1 to 26, characterized in that the steel yet further contains one or more of Y, Rem, Ca, Mg and Ce at 0.0001 to 1% in mass.

28. A high-strength high-ductility hot-dip galvanized steel sheet and hot-dip galvannealed steel sheet having high fatigue resistance and corrosion resistance according to any one of claims 1 to 27, characterized in that: the steel contains one or more of SiO_2, MnO and Al_2O_3 at 0.1 to 70% in total area percentage in the range from the interface between the plated layer and the steel sheet to the depth of 10 μm; and the following equation 5 is satisfied:

{MnO (in area percentage)+Al_2O_3 (in area percentage)}/SiO_2 (in area percentage) ≧ 0.1 ... 5

29. A high-strength high-ductility hot-dip galvanized steel sheet and hot-dip galvannealed steel sheet having high fatigue resistance and corrosion resistance according to any one of claims 1 to 28, characterized in that the steel contains one or more of Y_2O_3, ZrO_2, HfO_2, TiO_3, La_2O_3, Ce_2O_3, CeO_2, CaO and MgO at 0.0001 to 10.0% in total area percentage in the range from the interface between the plated layer and the steel sheet to the depth of 10 μm.

30. A method of producing a high-strength hot-dip galvanized steel sheet and hot-dip galvannealed steel sheet having high plating adhesion after severe deformation and ductility during heavy working, characterized by: casting a steel comprising the chemical components according to any one of claims 1 to 29 or once cooling the cast slab after the casting; then heating the cast slab again; thereafter, hot-rolling the cast slab

into a hot-rolled steel sheet and coiling it, and then
pickling and cold-rolling the hot-rolled steel sheet;
thereafter, annealing the cold-rolled steel sheet for 10
seconds to 30 minutes in the temperature range from not

5   less than $0.1 \times (Ac_3 - Ac_1) + Ac_1$ (°C) to not more than $Ac_3 + 50$
(°C); then cooling the steel sheet to the temperature
range from 650 to 700°C at a cooling rate of 0.1 to
10°C/sec.; thereafter, cooling the steel sheet to the
temperature range from the plating bath temperature to

10   the plating bath temperature + 100°C at a cooling rate of
1 to 100°C/sec.; keeping the steel sheet in the
temperature range from the zinc plating bath temperature
to the zinc plating bath temperature + 100°C for 1 to
3,000 seconds including the subsequent dipping time;

15   dipping the steel sheet in the zinc plating bath; and,
after that, cooling the steel sheet to room temperature.

        31.   A method of producing a high-strength hot-dip
galvanized steel sheet and hot-dip galvannealed steel
sheet according to any one of the claims 1 to 29, which

20   hot-dip galvanized steel sheet being excellent in
appearance and workability, characterized by: casting a
steel comprising the chemical components according to any
one of claims 1 to 29 or once cooling the cast slab after
the casting; then heating the cast slab again to a

25   temperature of 1,180 to 1,250°C; finishing the hot-
rolling at a temperature of 880 to 1,100°C; then pickling
and cold-rolling the coiled hot-rolled steel sheet;
thereafter, annealing the cold-rolled steel sheet for 10
seconds to 30 minutes in the temperature range from not

30   less than $0.1 \times (Ac_3 - Ac_1) + Ac_1$ (°C) to not more than $Ac_3 + 50$
(°C); then cooling the steel sheet to the temperature
range from 650 to 700°C at a cooling rate of 0.1 to
10°C/sec.; thereafter, cooling the steel sheet to the
temperature range from the plating bath temperature -

35   50°C to the plating bath temperature + 50°C at a cooling
rate of 0.1 to 100°C/sec.; then dipping the steel sheet
in the plating bath; keeping the steel sheet in the

temperature range from the plating bath temperature -
50°C to the plating bath temperature + 50°C for 2 to 200
seconds including the dipping time; and, thereafter,
cooling the steel sheet to room temperature.

5   32.   A method of producing a high-strength high-
ductility hot-dip galvanized steel sheet and hot-dip
galvannealed steel sheet according to any one of claims 1
to 29, the hot-dip galvanized steel sheet being excellent
in corrosion resistance, characterized by: casting a
10   steel comprising the chemical components according to any
one of claims 1 to 29 or once cooling the cast slab after
the casting; then heating the cast slab again to a
temperature of 1,200 to 1,300°C; then rough-rolling the
heated slab at the total reduction rate of 60 to 99% and
15   at a temperature of 1,000 to 1,150°C; then pickling and
cold-rolling the finished and coiled hot-rolled steel
sheet; thereafter, annealing the cold-rolled steel sheet
for 10 seconds to 30 minutes in the temperature range
from not less than $0.12 \times (Ac_3 - Ac_1) + Ac_1$ (°C) to not more
20   than $Ac_3 + 50$ (°C); then, after the annealing, cooling the
steel sheet, when the highest attained temperature during
annealing is defined as Tmax (°C), to the temperature
range from Tmax - 200°C to Tmax - 100°C at a cooling rate
of Tmax/1,000 to Tmax/10 °C/sec.; thereafter, cooling the
25   steel sheet to the temperature range from the plating
bath temperature - 30°C to the plating bath temperature +
50°C at a cooling rate of 0.1 to 100°C/sec.; then dipping
the steel sheet in the plating bath; keeping the steel
sheet in the temperature range from the plating bath
30   temperature - 30°C to the plating bath temperature + 50°C
for 2 to 200 seconds including the dipping time; and,
thereafter, cooling the steel sheet to room temperature.

         33.   A method of producing a high-strength high-
ductility hot-dip galvanized steel sheet and hot-dip
35   galvannealed steel sheet having high fatigue resistance
and corrosion resistance, characterized by: casting a
steel comprising the chemical components according to any

one of claims 1 to 29 or once cooling the cast slab after
the casting; then heating the cast slab again;
thereafter, hot-rolling the cast slab into a hot-rolled
steel sheet and coiling it, and then pickling and cold-
5   rolling the hot-rolled steel sheet; thereafter, annealing
the cold-rolled steel sheet controlling the annealing
temperature so that the highest temperature during
annealing may fall within the range from not less than
$0.1 \times (Ac_3 - Ac_1) + Ac_1$ (°C) to not more than $Ac_3 - 30$ (°C);
10   then cooling the steel sheet to the temperature range
from 650 to 710°C at a cooling rate of 0.1 to 10°C/sec.;
thereafter, cooling the steel sheet to the temperature
range from the zinc plating bath temperature to the zinc
plating bath temperature + 100°C at a cooling rate of 1
15   to 100°C/sec.; keeping the steel sheet in the temperature
range from the zinc plating bath temperature to the zinc
plating bath temperature + 100°C for 1 to 3,000 seconds
including the subsequent dipping time; dipping the steel
sheet in the zinc plating bath; and, after that, cooling
20   the steel sheet to room temperature.

        34. A high-strength hot-dip galvanized steel sheet
and hot-dip galvannealed steel sheet having high fatigue
resistance, corrosion resistance, and plating adhesion
after severe deformation and ductility and a method of
25   producing the same, according to any one of claims 30 to
33, characterized by: after dipping the steel sheet in
the zinc plating bath, applying an alloying treatment to
the steel sheet at a temperature of 300 to 550°C and
cooling it to room temperature.